



# AEROSPACE MATERIAL SPECIFICATIONS

## AMS 4388B

Superseding AMS 4388A

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

Issued 1-15-59

Revised 5-1-68

### MAGNESIUM ALLOY EXTRUSIONS 3.0Th - 1.5Mn (HM31A-F)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, rods, wire, and shapes.
3. **APPLICATION:** Primarily for components requiring weldability and good strength to weight ratio up to 600 F (316 C).
4. **COMPOSITION:**

	min	max
Thorium	2.5	3.5
Manganese	1.2	--
Other Impurities, each	--	0.10
Other Impurities, total	--	0.30
Magnesium	remainder	

5. **CONDITION:** As extruded.
- 5.1 Unless otherwise specified, extrusions shall be supplied with the as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.

6. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

6.1 **Tensile Properties:**

	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 6,500,000)		Elongation % in 2 in. or 4D, min
		psi, min	Extension Under Load in. in 2 in.	
Bars, Rods, Wire, and Solid Shapes, Cross Sectional Area Up to 4 sq. in., excl	37,000	26,000	0.0120	4

- 6.1.1 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.
- 6.1.2 If sizes other than those shown are ordered, tensile property requirements shall be as agreed upon by purchaser and vendor.
7. **QUALITY:** Material shall be uniform in quality and condition, clean, sound, and free from segregation and foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against any infringement of patents."