



AEROSPACE MATERIAL SPECIFICATION	AMS4392™	REV. A
	Issued 2010-12 Reaffirmed 2016-05 Revised 2024-04	
Superseding AMS4392		
Magnesium Alloy Welding Wire, 4.2Zn - 1.2 Rare Earths - 0.7Zr (ZE41A) (Composition similar to UNS M16410)		

RATIONALE

AMS4392A results from a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (see 3.7, 4.4.1, 5.5.1, and 8.4), provide options for weld wire cut lengths (see 3.6.2), update Applicable Documents (see Section 2) and Ordering Information (see 8.5), and allow the use of the immediate prior specification revision (see 8.3).

1. SCOPE

1.1 Form

This specification covers a magnesium alloy in the form of welding wire (see 8.5).

1.2 Application

This wire has been used typically as filler metal for gas-metal-arc and gas-tungsten-arc welding of magnesium alloys of similar composition, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2813 Packaging and Marking of Packages of Welding Wire, Standard Method

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4392A>

- ARP1876 Weldability Test for Weld Filler Metal Wire
- ARP4926 Alloy Verification and Chemical Composition Inspection of Welding Wire
- AS7766 Terms Used in Aerospace Metals Specifications

2.2 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight as shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Zinc	3.5	5.0
Total Rare Earths (see 3.1.1)	0.75	1.75
Zirconium, total	0.40	1.0
Manganese (see 3.1.2)		0.15
Copper (see 3.1.2)	--	0.10
Nickel (see 3.1.2)	--	0.01
Other Elements, each (see 3.1.2)	--	0.10
Other Elements, total (see 3.1.2)	--	0.30
Magnesium	remainder	

- 3.1.1 Total rare earths (TRE) are principally a mixture of cerium, lanthanum, neodymium, and praseodymium. The cerium content shall not be less than 45% of TRE.
- 3.1.2 Determination not required for routine acceptance.
- 3.1.3 Chemical analysis of initial ingot, bar, or rod stock is acceptable provided the processes used for manufacture and cleaning are controlled to ensure conformance to composition requirements and the facility employs procedures to ensure traceability of wire to the originally analyzed ingot.

3.2 Condition

Wire for cut lengths shall be extruded and for spooled wire shall be extruded and sized. Drawn wire may be supplied if acceptable to the purchaser.

3.3 Fabrication

- 3.3.1 Butt welding is permissible provided both ends to be joined are identified by chemical analysis or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.
- 3.3.2 Oxides, dirt, and extruding compounds shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Properties

Wire shall conform to the following requirements:

3.4.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5 Quality

Wire, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter

Shall conform to the tolerances as shown in Table 2.

Table 2A - Tolerances, inch/pound units

Form	Nominal Diameter Inches	Tolerance, Inches Plus	Tolerance, Inches Minus
Cut Lengths	0.062 to 0.250, incl	0.007	0.007
Spools	0.040 to 0.125, incl	0.003	0.004
	Over 0.125 to 0.187, Incl	0.007	0.007

Table 2B - Tolerances, SI units

Form	Nominal Diameter Millimeters	Tolerance, Millimeters Plus	Tolerance, Millimeters Minus
Cut Lengths	1.57 to 6.35, incl	0.18	0.18
Spools	1.00 to 3.17, incl	0.076	0.10
	Over 3.17 to 4.75, incl	0.18	0.18

3.6.2 Length

Cut lengths shall be furnished in 18-, 27-, or 36-inch (457-, 686-, or 914-mm) lengths, or other lengths when specified by the purchaser, and shall not vary more than +0, -0.5 inch (+0, -13 mm) from the length ordered (see 8.5).

3.7 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of wire shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (see 3.1) and sizes and tolerances (see 3.6) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests

Weldability (see 3.4.1) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The producer of wire shall furnish with each shipment a report stating that the wire conforms to the composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS4392A, nominal size, and quantity.

4.4.1 When material produced to this specification has exceptions taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS4392A(EXC) because of the following exceptions:" and the specific exceptions shall be listed (see 5.5.1).

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

5. PREPARATION FOR DELIVERY

5.1 Wire shall be supplied on spools in one continuous length for machine welding or in cut lengths for manual welding, as ordered.

5.2 Wire on each spool shall be of one continuous length from the same heat of alloy. Packages of cut lengths shall not contain wire from more than one heat of alloy.

5.3 Wire furnished on spools shall be closely wound in layers, but adjacent turns within a layer need not necessarily be touching. Wire shall be wound so as to avoid producing kinks, waves, and sharp bends, and shall be free to unwind without restriction caused by overlapping or wedging.

5.4 Wire from each spool or package of cut lengths shall be alloy verified by a method acceptable to the purchaser. The alloy verification procedures of ARP4926 are recommended.

5.4.1 An 8-inch (203-mm) length of wire shall be made accessible at both ends of each spool for alloy verification.

5.5 Packaging and Marking

Shall be in accordance with AMS2813.

5.5.1 When technical exceptions are taken (see 4.4.1), the material shall be identified with AMS4392A(EXC).

6. ACKNOWLEDGMENT

A producer shall mention this specification number in all quotations and when acknowledging purchase orders.