



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

AMS 4396A

Superseding AMS 4396

Issued 7-15-63

Revised 5-1-68

MAGNESIUM WIRE, WELDING 3.3Ce - 2.5Zn - 0.7Zr (EZ33A)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for inert gas arc welding.

3. COMPOSITION:

∅	min	max
Cerium (Total Rare Earths)	2.5	4.0
Zinc	2.0	3.1
Zirconium, total	0.45	1.0
Zirconium, soluble	0.45	--
Copper, if determined	--	0.10
Nickel, if determined	--	0.01
Other Impurities, total	--	0.30
Magnesium	remainder	

3.1 Soluble zirconium is that portion of zirconium which is soluble in 1:4 hydrochloric acid held below its boiling point. Routine determinations for soluble zirconium are not required.

4. CONDITION:

4.1 Unless otherwise specified, wire for cut lengths shall be extruded; for spooled wire, shall be extruded and sized. Wire shall be furnished on disposable spools for machine welding and in cut lengths for manual welding operations, as ordered.

4.2 Extruding compounds, oxide, and dirt shall be removed.

5. TECHNICAL REQUIREMENTS:

5.1 Welding: Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds.

5.2 Spooled Wire: Shall conform to the following unless otherwise agreed upon by purchaser and vendor.

5.2.1 Layer Winding: Wire shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching; shall be wound so as to avoid producing kinks, waves, and sharp bends; and shall be free to unwind without restriction caused by overlapping or wedging. The outside end of the spooled wire shall be so treated that it may be readily located.

5.2.2 Wire on each spool shall be in one continuous length.

6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

SAE TECHNICAL BOARD RULES TO VIEW THE FULL PDF OF AMS4396A