

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4420D

Issued 12-5-39

Revised 6-1-49

MAGNESIUM ALLOY CASTINGS, SAND

AZ63

As Cast

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **COMPOSITION:**

Aluminum	5.30 - 6.70
Zinc	2.50 - 3.50
Manganese	0.20 min
Silicon	0.30 max
Copper	0.25 max
Nickel	0.01 max
Other Impurities, total	0.30 max
Magnesium	remainder

3. **CONDITION:** As cast.

4. **TECHNICAL REQUIREMENTS:**

4.1 **Casting:**

4.1.1 All metal which is poured into castings shall conform in composition to Section 2 above. The molten metal shall be subjected to superheating or other grain-refining treatment.

4.1.2 A melt shall be the metal withdrawn from a batch furnace charge of 2000 pounds or less as melted for pouring castings, or when permitted by the purchaser, a melt shall be 3000 pounds or less of metal withdrawn from one continuous furnace in not more than 4 consecutive hours.

4.2 **Test Specimens:** Tensile test specimens, and chemical analysis specimens when required, shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings.

4.2.1 **Tensile Test Specimens:** Shall be standard (0.5-inch diameter at the reduced parallel section) and shall be cast to size in molds made with the regular foundry mix of green sand, without using chills. Metal for the specimens shall be part of the melt which is used for the castings and shall be subjected to the same super heating or other grain-refining treatment given the metal for the castings.

4.2.2 **Chemical Analysis Specimens:** When required by purchaser, shall be of size and shape agreed upon by purchaser and vendor.

4.3 **Physical Properties:**

ed and practices recommended are advisory only. Their standard or recommended practice and no commitment and its Committee will not investigate or consider themselves against liability for infringement of patents.

of the SAE Technical Board provides that: "All technical reports, including standard technical reports, are entirely voluntary. There is no agreement to adhere to or be guided by any technical report. In formulating and approving technical reports, the SAE Technical Board and its committees are responsible for the accuracy of the information which may apply to the subject matter. Prospective users of the report are responsible for their own interpretation of the report."

Click to view the full PDF of AMS 4420D

4.3.1 Tensile test specimens shall conform to the following requirements:

Tensile Strength, psi	24,000 min
Elongation, % in 2 in.	4 min
Hardness, Brinell 500 kg load and 10 mm ball	48 min

4.3.2 Hardness of castings, except at sprues and risers, shall be not lower than Brinell 48 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 57 using 1000 kg load and 10 mm ball.

4.3.3 If castings are cut for examination, not less than four, and preferably ten, tensile test specimens taken from thick and thin sections of castings shall be tested. Average hardness of such specimens shall be as specified in 4.3.2. Average tensile properties shall conform to the following requirements:

Tensile Strength, psi	18,000 min
Elongation, % in 2 in.	1.0 min

Note: Conformance to these requirements may be used as basis for acceptance of castings.

5. QUALITY:

- 5.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.
- 5.2 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal defects, is established for each pattern, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 5.3 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 5.4 Castings shall not be repaired by plugging, welding or other methods, without written permission from the purchaser.
- 5.5 Castings shall not be impregnated, chemically treated or coated to prevent leaking, unless specified or allowed by written permission which states the method to be used. Impregnated castings shall be marked IMP.

6. REPORTS:

- 6.1 Unless otherwise specified, the vendor of castings shall furnish with each shipment three copies of a notarized report of the results of tests to determine conformance of the castings to the requirements of this specification. This report shall show the chemical composition of the castings, physical properties of the tensile test specimens, melt numbers, material specification number, purchase order number, part number, and quantity. If the accuracy of control is adequate, each melt need not be analyzed, but the frequency of analysis shall be as agreed upon by purchaser and vendor.