

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS4422G

Issued 12-5-39

Revised 12-1-51

MAGNESIUM ALLOY CASTINGS, SAND
AZ63
Solution Treated

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

Aluminum	5.3 - 6.7
Zinc	2.5 - 3.5
Manganese	0.15 min
Silicon	0.3 max
Copper	0.25 max
Nickel	0.01 max
Other Impurities, total	0.3 max
Magnesium	remainder

3. CONDITION: Solution heat treated.

4. TECHNICAL REQUIREMENTS:

4.1 Casting:

4.1.1 The molten metal shall be subjected to superheating or other grain-refining treatment.

4.1.2 A melt shall be the metal withdrawn from a batch furnace charge of 2000 pounds or less as melted for pouring castings, or when permitted by purchaser, a melt shall be 3000 pounds or less of metal withdrawn from one continuous furnace in not more than 4 consecutive hours.

4.2 Test Specimens: Tensile test specimens, and chemical analysis specimens when required, shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings.

4.2.1 Tensile Test Specimens: Shall be standard (0.5-inch diameter at the reduced parallel section) and shall be cast to size in molds made with the regular foundry mix of green sand, without using chills. Metal for the specimens shall be part of the melt which is used for the castings and shall be subjected to the same superheating or other grain-refining treatment given the metal for the castings.

4.2.2 Chemical Analysis Specimens: when required by purchaser, shall be of size and shape agreed upon by purchaser and vendor.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.3 Heat Treatment: All castings and tensile test specimens representing them shall be heat treated as follows:

4.3.1 Tensile test specimens from each melt, together with production castings, shall be heated to the proper temperature and for the proper time for solution treatment and cooled in air. At least one set of tensile test specimens shall be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than 3 hours.

4.4 Tensile Properties:

4.4.1 Tensile Test Specimens:

Tensile Strength, psi	34,000	min
Elongation, % in 2 in.	7	min

4.4.2 Tensile Properties of Castings: When tensile properties of actual castings are determined for acceptance, not less than 4, and preferably 10, tensile test specimens shall be cut from thick and thin sections. The average value of all specimens selected shall conform to the following:

Tensile Strength, psi	25,500	min
Elongation, % in 2 in.	1.75	min

4.4.2.1 Conformance to these requirements may be used as basis for acceptance of castings.

4.5 Hardness of Castings: Except at sprues and risers the castings shall have hardness of Brinell 48-60, using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 57-72 using 1000 kg load and 10 mm ball.

5. QUALITY:

- 5.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.
- 5.2 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal defects, is established for each pattern, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 5.3 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 5.4 Castings shall not be repaired by plugging, welding or other methods, without written permission from purchaser.
- 5.5 Castings shall not be impregnated, chemically treated or coated to prevent leaking, unless specified or allowed by written permission which states the method to be used. Impregnated castings shall be marked IMP.