

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 4439F

Issued NOV 1970
Revised JAN 2007

Superseding AMS 4439E

Magnesium Alloy Castings
4.2Zn - 1.2Rare Earths - 0.7Zr (ZE41A-T5)
Precipitation Heat Treated

(Composition similar to UNS M16410)

RATIONALE

AMS 4439F results from a Five Year Review and update of this specification. The title has been changed to from 1.2 Ce to 1.2 Rare Earths. The chemistry table has been changed from Cerium [total rare earths] to Total Rare Earths.

1. SCOPE

1.1 Form

This specification covers a magnesium alloy in the form of castings.

1.2 Application

These castings have been used typically for components requiring uniform medium strength up to 320 °F (160 °C), pressure tightness, good fatigue and creep characteristics, and that may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2175	Casting, Classification and Inspection of
AMS 2360	Room Temperature Tensile Properties of Castings
AMS 2475	Protective Treatments, Magnesium Alloys
AMS 2694	Repair Welding of Aerospace Castings
AMS 2768	Heat Treatment of Magnesium Alloy Castings
AMS 2804	Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 557	Tension Testing Wrought and Cast Aluminum and Magnesium-Alloy Products
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM E 35	Chemical Analysis of Magnesium and Magnesium Alloys
ASTM E 155	Standard Reference Radiographs for Inspection of Aluminum and Magnesium Castings
ASTM E 1417	Liquid Penetrant Examination
ASTM E 1742	Radiographic Examination

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 35, by spectrochemical methods, or by other analytical methods acceptable to purchaser (See 3.4.1).

TABLE 1 - COMPOSITION

Element	min	max
Zinc	3.5	5.0
Total Rare Earths (3.1.1)	0.75	1.75
Zirconium, total	0.40	1.0
Zirconium, soluble (3.1.2, 3.1.3)	0.40	--
Manganese (3.1.3)	--	0.15
Copper (3.1.3)	--	0.10
Nickel (3.1.3)	--	0.01
Other Elements, each (3.1.3)	--	0.10
Other Elements, total (3.1.3)	--	0.30
Magnesium	remainder	

3.1.1 Total Rare Earths (TRE) are principally a mixture of Cerium, Lanthanum, Neodymium and Praseodymium. The Cerium content shall not be less than 45% of TRE.

3.1.2 Soluble zirconium is that portion of the zirconium soluble in 1:4 hydrochloric acid held below its boiling point.

3.1.3 Determination not required for routine acceptance.

3.2 Condition

Precipitation heat treated.

3.3 Casting

Castings shall be produced from metal conforming to 3.1 determined by analyses of a specimen (3.4.1) cast after the last melt addition.

3.4 Test Specimens

Chemical analysis specimens and tensile specimens shall be cast as follows:

3.4.1 Chemical Analysis Specimens

Shall be cast from each melt after the last melt addition and shall be tested to qualify the melt lot as in 3.1.

3.4.2 Tensile Specimens

Shall be prepared as follows and tested for conformance to 3.6.1:

- 3.4.2.1 Unless specimens cut from castings are specified by the purchaser, separately cast specimens, conforming to ASTM B 557, shall be cast from each melt after the last melt addition. Specimens shall be cast in molds representing the mold used for castings. Chills are not permitted on test specimen cavity except on the end face of the specimen when approved in accordance with 4.4.2. Tensile specimens shall be processed with each heat treat lot.
- 3.4.2.2 When purchaser specifies specimens cut from castings or from integrally-cast coupons, such specimens shall be removed after heat treatment, shall be machined to conform to ASTM B 557, and shall be either 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens.

3.5 Heat Treatment

Shall be in accordance with AMS 2768. Unless specimens cut from castings or from integrally-cast coupons are specified, at least one set of tensile specimens shall, during each stage of heat treatment, be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than three hours.

3.6 Properties

Castings, integrally-cast coupons, and representative separately-cast tensile specimens shall conform to the following requirements:

3.6.1 Tensile Properties

Shall be as follows, determined in accordance with ASTM B 557: conformance to the requirements of 3.6.1.1 shall be used as the basis for acceptance of castings except when purchaser specifies that specimens shall be cut from castings (See 3.6.1.2) or from integrally-cast coupons (See 3.6.1.2).

3.6.1.1 Separately-Cast Specimens

Shall have the properties shown in Table 2.

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	29.0 ksi (200 MPa)
Yield Strength at 0.2% Offset	19.5 ksi (134 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	2.5%

3.6.1.2 Specimens Cut From Castings or From Integrally-Cast Coupons

When specified by purchaser, specimens obtained by sampling in accordance with 4.3.4 shall meet the requirements of Table 3, unless otherwise specified as in 3.6.1.2.1.

TABLE 3 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	26.0 ksi (179 MPa)
Yield Strength at 0.2% Offset	17.5 ksi (121 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	2.0%

- 3.6.1.2.1 Properties other than those shown in Table 3 may be specified for specific casting locations. Properties may be designated in accordance with AMS 2360.

3.7 Quality

- 3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.
- 3.7.1.1 Castings shall have smooth surfaces sufficiently cleaned to permit fluorescent penetrant inspection.
- 3.7.1.2 Castings cleaned by blasting shall be pickled in a sulfuric or sulfuric-nitric acid solution to remove not less than 0.002 inch (0.05 mm) of metal prior to protective treatment as in 5.2.
- 3.7.2 Castings shall be produced under radiographic control. This control shall consist of 100% radiographic inspection of castings until process control factors (4.4.2) have been established to ensure production of acceptable castings. Unless otherwise specified by the purchaser, continued radiographic inspection of production castings shall be performed at a frequency determined by the vendor to ensure continued maintenance of internal quality.
- 3.7.3 Methods of inspection and frequency of inspection shall be as agreed upon by purchaser and vendor. A "Casting Class" of AMS 2175 may be selected to specify the method and frequency of inspection.
- 3.7.4 When acceptance standards are not specified, Grade C of AMS 2175 shall apply. ASTM E 155 may be used to define radiographic acceptance standards.
- 3.7.5 Radiographic inspection shall be conducted in accordance with ASTM E 1742, unless otherwise specified by purchaser.
- 3.7.6 When specified by purchaser, castings shall be fluorescent penetrant inspected using a method specified by the purchaser, or, if not specified, a method in accordance with ASTM E 1417.
- 3.7.7 Castings shall not be peened, plugged, impregnated, or welded unless authorized by purchaser.
- 3.7.7.1 When authorized by purchaser, welding in accordance with AMS 2694 or other welding program approved by the purchaser may be used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Except as specified in 4.2.1.1, composition (3.1), tensile properties of separately-cast specimens (3.6.1.1), or, when specified, tensile properties of specimens cut from castings or integrally-cast coupons (3.6.1.2), and quality (3.7) are acceptance tests and shall be performed to represent each melt or lot as applicable.

- 4.2.1.1 Tensile properties of specimens cut from castings or from integrally-cast coupons shall be determined when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings or from integrally-cast coupons are determined.

4.2.2 Periodic Tests

Radiographic inspection (3.7.2) following the establishment of process control, is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests

All technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

Shall be in accordance with the following:

- 4.3.1 One chemical analysis specimen in accordance with 3.4.1 from each melt for conformance to 3.1.
- 4.3.2 One separately-cast tensile specimen in accordance with 3.4.2 from each heat treat lot except when purchaser requires properties of specimens machined from castings or from integrally-cast coupons.
- 4.3.3 One or more preproduction castings in accordance with 4.4.1 of each part number.
- 4.3.4 Except as permitted by 4.3.4.1, one or more castings from each heat treat lot when tensile properties of specimens machined from castings are required. For determining conformance to the requirements of 3.6.1.2, if specimen locations are not shown on the drawing, two specimens from the thickest section and two from the thinnest section shall be cut from a casting or castings from each lot.
- 4.3.4.1 When permitted by purchaser, tensile specimens conforming to ASTM B 557 excised from integrally-cast coupons may be used in lieu of separately-cast specimens (4.3.2) or specimens cut from a casting or castings (4.3.4). Size, number, and location of integrally-cast coupons shall be as specified by purchaser.

4.4 Approval

- 4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the process control factors that will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. Vendor shall establish a single procedure for production of separately-cast tensile specimens. Method for production of separately-cast tensile specimens shall be consistent for all material cast to this specification. Control factors for separately-cast tensile specimens must generally represent, but need not be identical to, those factors used for castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, test specimens, sample castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.
- 4.4.2.1 Process control factors for producing castings include, but are not limited to, the following; supplier's procedures shall identify tolerances, ranges, and/or control limits, as applicable:

Type of furnace

Furnace atmosphere

Maximum amount of alloy per melt lot

Ladle addition or grain-refining procedure

Mold composition and molding practice

Gating and risering practices

Core composition and fabrication method, when applicable

Metal pouring temperature; variation of ± 50 °F (± 28 °C) from established limit is permissible

Alloy additions, fluxing, deoxidation, and gas removal procedures

Solidification and cooling procedures

Precipitation heat treatment cycle

Cleaning operations

Methods of inspection

Radiographic inspection sampling plan, if used.