



AEROSPACE MATERIAL SPECIFICATION	AMS4474™	REV. A
	Issued 2012-10 Revised 2015-08	
Superseding AMS4474		
Aluminum Alloy, Sheet and Plate 4.0Cu - 1.0Li - 0.40Mg - 0.35Ag - 0.13Zr (2195-T8) Solution Heat Treated, Cold Worked, and Artificially Aged (Composition similar to UNS A92195)		

RATIONALE

AMS4474A revises Properties (3.4.1.1, Table 2), and Reports (4.4.1) as a result of increasing the product thickness range.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate with a thickness of 0.125 to 0.499 inch (3.20 to 12.67 mm), inclusive (See 8.4).

1.2 Application

This product has been used for aircraft applications where it offers a combination of high strength and low density, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS1990 Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4474A>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, 4th Floor, New York, NY 10036, Tel: 212-642-4900, www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	min	max
Silicon	--	0.12
Iron	--	0.15
Copper	3.7	4.3
Manganese	--	0.25
Magnesium	0.25	0.8
Zinc	--	0.25
Titanium	--	0.10
Zirconium	0.08	0.16
Silver	0.25	0.6
Lithium	0.8	1.2
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Product shall be supplied in the following condition:

3.2.1 Solution heat treated, cold worked and artificially aged to T8 temper (See AS1990).

3.3 Heat Treatment

Solution heat treatment and aging shall be performed in accordance with AMS2772.

3.4 Properties

The product shall conform to the following requirements determined in accordance with AMS2355 on the mill produced size.

3.4.1 Tensile Properties

Shall be as shown in Table 2.

3.4.1.1 Mechanical property requirements for product outside the range covered by Table 2 shall be agreed upon between purchaser and producer.

Table 2A - Minimum tensile properties, inch/pound units

Nominal Thickness Inches	Specimen Orientation	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.125 to 0.499, incl	Longitudinal	82.0	78.0	6
	Long-Trans.	80.0	76.0	6

Table 2B - Minimum tensile properties, SI units

Nominal Thickness Millimeters	Specimen Orientation	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm %
3.20 to 12.67, incl	Longitudinal	565	538	6
	Long-Trans.	552	524	6

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.4.1), and tolerances (3.6) are acceptance tests, and except for composition, shall be performed on each inspection lot.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The producer of the product shall furnish with each shipment a report stating that the product conforms to the composition requirements and tolerances and showing the numerical results of tests to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS4474A, size, and quantity. The report shall also identify the producer, the product form, and the mill produced size.