

AEROSPACE
MATERIAL
SPECIFICATION

AMS 4507E
Superseding AMS 4507D

Issued 7-1-45
Revised 7-1-83

BRASS SHEET, STRIP, AND PLATE
70Cu - 30Zn (CDA 26000)
Half Hard

UNS C26000

1. SCOPE:

1.1 Form: This specification covers one type of brass in the form of sheet, strip, and plate.

1.2 Application: Primarily for stampings.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2222 - Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate
AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B248 - General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

ASTM E8 - Tension Testing of Metallic Materials

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E478 - Chemical Analysis of Copper Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 4507E

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-C-3993 - Copper and Copper-Base Alloy Mill Products, Packaging of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, \emptyset determined by wet chemical methods in accordance with ASTM E478, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Copper	68.50	71.50
Lead	--	0.07
Iron	--	0.05
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Zinc	remainder	

3.2 Condition: Cold rolled, half hard temper.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Tensile Strength: Shall be 57,000 - 67,000 psi (395 - 460 MPa), determined in accordance with ASTM E8.

3.3.2 Hardness: Should be 56 - 68 HR30T, or equivalent, determined in accordance with ASTM E18, but the product shall not be rejected on the basis of hardness if the tensile strength requirement is met.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to AMS 2222 as applicable to non-refractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all \emptyset samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.3 Sampling: Shall be in accordance with ASTM B248.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4507E, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 4507E, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as in 5.1.1 unless line marking as in 5.1.2 is specified by purchaser.

5.1.1 Each sheet, strip, and plate shall be marked near one end, coils being marked near the outside end, with AMS 4507E, lot number, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternative method, individual pieces or bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

AMS 4507E

5.1.2 When specified by purchaser, each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 4507E, lot number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking, or may be marked at one location on each piece.

5.1.2.1 Flat Strip 6 In. (150 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.2.2 Flat Sheet, Flat Strip Over 6 In. (150 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced not more than 6 in. (150 mm) apart and alternately staggered.

5.1.2.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.2 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.2. When the inside end of the coil is inaccessible, as when the product is wound on cores, the tag or label may be attached to the core.

5.2 Packaging:

5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-C-3993, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Material not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.