

AEROSPACE MATERIAL SPECIFICATION



AMS 4507H

Issued 1945-07
Revised 2001-11
Reaffirmed 2010-05

Superseding AMS 4507G

Copper Alloy (Brass), Sheet, Strip, and Plate
70Cu - 30Zn
Half Hard (H02)

(Composition similar to UNS C26000)

RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

1. SCOPE:

1.1 Form:

This specification covers a copper-zinc alloy (brass) in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for stampings, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2222 Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate

MAM 2222 Tolerances, Metric, Copper and Copper Alloy Sheet, Strip, and Plate

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4507H>**

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

| | |
|-------------|---|
| ASTM B 248 | General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar |
| ASTM B 248M | General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric) |
| ASTM E 8 | Tension Testing of Metallic Materials |
| ASTM E 8M | Tension Testing of Metallic Materials (Metric) |
| ASTM E 18 | Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials |
| ASTM E 478 | Chemical Analysis of Copper Alloys |

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element (3.1.1) | min | max |
|-------------------------------|-----------|------|
| Copper | 68.5 | 71.5 |
| Lead | -- | 0.07 |
| Iron | -- | 0.05 |
| Zinc (3.1.2) | remainder | -- |
| Sum of Named Elements (3.1.3) | 99.7 | |

- 3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.
- 3.1.2 Zinc may be reported as "remainder", or as the difference between the sum of results for all elements and 100%, or as the result of direct analysis.
- 3.1.3 When all the elements the table are analyzed, the sum shall be 99.7% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition:

Cold rolled, half-hard (H02) temper (See 8.2).

3.3 Properties:

The product shall conform to the following requirements:

- 3.3.1 Tensile Strength: Shall be 57 to 67 ksi (393 to 462 MPa), determined in accordance with ASTM E 8 or ASTM E 8M.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to AMS2222 or MAM 2222 as applicable to nonrefractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing:

Shall be in accordance with ASTM B 248 or ASTM B 248M.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests on each lot to determine conformance to all technical requirements. This report shall include the purchase order number, lot number, AMS 4507H, size, and quantity.

4.5 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing two additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

The product shall be identified as in 5.1.1 unless line marking as in 5.1.2 is specified by purchaser.

5.1.1 Each sheet, strip, and plate shall be legibly marked near one end, coils being marked near the outside end, with AMS 4507H, lot number, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternative method, individual pieces or bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

5.1.2 When specified by purchaser, each sheet, strip, and plate shall be legibly marked on one face, in the respective location indicated below, with AMS4507H, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a suitable marking fluid removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking or may be marked at one location on each piece.

5.1.2.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.2.2 Flat Sheet, Flat Strip Over 6 Inches (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.2.3 Coiled Sheet and Strip: Shall be legibly marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.2 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.2. When the product is wound on cores, the tag or label may be attached to the core.

5.2 Packaging:

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.