



AEROSPACE MATERIAL SPECIFICATION

AMS4520™

REV. M

Issued 1940-01
Revised 2021-04

Superseding AMS4520L

Leaded Phosphor Bronze Strip
88.5Cu - 4.0Sn - 4.0Pb - 3.0Zn - 0.26P
Cold Rolled, Half Hard (H02)
(Composition similar to UNS C54400)

RATIONALE

AMS4520M prohibits unauthorized exceptions (3.6); revises title to correct temper designation, revises composition (3.1), properties (3.3), reports (4.4.1), identification (5.1.3), and notes (8.6); and results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a copper alloy in the form of strip.

1.2 Application

This strip has been used typically for rolled, split bushings, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA, www.sae.org).

AMS2222 Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate

ARP1917 Clarification of Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4520M>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B248 General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

ASTM B248M General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

ASTM B601 Temper Designations for Copper and Copper Alloys - Wrought and Cast

ASTM E8/E8M Tension Testing of Metallic Materials

ASTM E18 Rockwell Hardness of Metallic Materials

ASTM E478 Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM E478 or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Tin	3.5	4.5
Lead	3.0	4.0
Zinc	1.5	4.5
Phosphorus	0.01	0.50
Iron	--	0.10
Copper (3.1.2)	remainder	--
Sum of Named Elements (3.1.3)	99.5	--

3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established, and analysis required, for unnamed elements by agreement between the manufacturer or supplier and purchaser.

3.1.2 Copper may be reported as "remainder," or as the difference between the sum of results for all analyzed elements and 100%, or as the result of direct analysis.

3.1.3 When all the elements in the table are analyzed, the sum shall be 99.5% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition

Cold rolled, half hard (H02) temper (see 8.3).

3.3 Properties

Strip shall conform to the following requirements when tested according to ASTM Test Methods E8/E8M. The test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling:

3.3.1 Tensile Strength, Ultimate

Shall be 55.0 to 70.0 ksi (379 to 483 MPa).

3.3.2 Elongation

Shall not be lower than 16% in 2 inches (50.8 mm), determined in accordance with ASTM E8/E8M.

3.4 Quality

Strip, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the strip.

3.5 Tolerances

Shall conform to AMS2222 as applicable to nonrefractory alloys.

3.6 Exceptions

Any exceptions shall be authorized by purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of strip shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the strip conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing

Shall be in accordance with ASTM B248 or ASTM B248M.

4.4 Reports

The producer of strip shall furnish with each shipment a report showing the results of tests to determine conformance to the technical requirements. This report shall include the purchase order number, lot number, AMS4520M, size, and quantity.

4.4.1 When material produced to this specification has exceptions authorized by purchaser taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS4520M(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

4.5 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the strip may be based on the results of testing two additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the strip represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY

5.1 Identification

Each strip shall be identified as in 5.1.1 unless line marking as in 5.1.2 is specified by purchaser.

5.1.1 Each strip shall be legibly marked near one end, coils being marked near the outside end, with AMS4520M, lot number, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternate method, individual pieces or bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

5.1.2 When specified by purchaser, each strip shall be legibly marked on one face, in the respective location indicated below, with AMS4520M, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a suitable marking fluid removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the strip or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking or may be marked at one location on each piece.

5.1.2.1 Flat Strip 6 Inches (152 mm) and Under in Width

Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.2.2 Flat Strip Over 6 Inches (152 mm) in Width

Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.2.3 Coiled Strip

Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.2 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.2. When the strip is wound on cores, the tag or label may be attached to the core.

5.1.3 When technical exceptions are taken (see 4.4.1), the material shall be marked with AMS4520M(EXC).

5.2 Packaging

Strip shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the strip to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A producer shall include this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Strip not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES

8.1 Revision Indicator

A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revisions. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.