



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4575C

Superseding AMS 4575B

Issued 11-1-49
Revised 10-15-79

UNS N04400

NICKEL-COPPER ALLOY TUBING, BRAZED, CORROSION RESISTANT
67Ni - 31Cu
Annealed

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant nickel-copper alloy in the form of copper-furnace-brazed tubing.

1.2 Application: Primarily for fluid lines, such as primer and fuel lines, requiring corrosion resistance with relatively-high strength.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2263 - Tolerances, Nickel, Nickel-Base, and Cobalt-Base Alloy Tubing

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E76 - Chemical Analysis of Nickel-Copper Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practice recommended, are advisory only. Their use by anyone engaged in industry or trade or that is controlled by governmental agencies is entirely voluntary. There is no agreement to adhere to a standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3. TECHNICAL REQUIREMENTS:

3.1 **Composition:** Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E76, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Nickel + Cobalt	63.0	--
Copper	28.0	34.0
Iron	--	2.5
Manganese	--	2.0
Cobalt (3.1.1)	--	1.0
Silicon	--	0.5
Carbon	--	0.3
Sulfur	--	0.024

3.1.1 Determination not required for routine acceptance.

3.1.2 **Check Analysis:** Composition variations shall meet the requirements of AMS 2269.

3.2 **Condition:** Cold drawn after brazing and annealed.

3.3 **Properties:** Tubing shall conform to the following requirements:

3.3.1 **Tensile Properties:** Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, Max	85,000 psi (586 MPa)
Elongation in 2 in. (50 mm) or 4D, min	32%

3.3.2 **Flareability:** Tubing shall withstand flaring without formation of cracks or other visible defects by being forced, at room temperature, axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg included angle to produce a flare having a permanent expanded OD not less than 1.25 times the original nominal OD.

3.3.3 **Pressure Test:** Tubing shall show no bulges, leaks, pinholes, cracks, or other defects when subjected to an internal hydrostatic pressure (P), calculated from the following equation:

$$P = \frac{2St}{D}$$

where, P = Test pressure
 S = 17,500 psi (120,070 KPa)
 t = Minimum wall thickness
 D = Nominal OD

3.4 **Quality:** Tubing, as received by purchaser, shall be uniform in quality and condition, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to usage of the tubing.

3.5 **Tolerances:** Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2263.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for flarability (3.3.2) and pressure test (3.3.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

∅ 4.3 Sampling: Shall be in accordance with AMS 2371 and the following:

4.3.1 Specimens for flarability test shall be full tubes or sections cut from tubes. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.

4.4 Reports:

4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile properties of each size from each heat and stating that the tubing conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

∅ 4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows:

5.1.1 Straight Tubes 0.029 In. (0.74 mm) and Over in Wall Thickness and 0.500 In. (12.70 mm) and Over in OD, Minor Axis, or Least Width of Flat Surface: Shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with AMS 4575C, manufacturer's identification, and nominal wall thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the tubing or its performance and shall be sufficiently stable to withstand normal handling.