

Copper Nickel Tin Alloy, Mechanical Tube
77Cu - 15Ni - 8Sn
Solution Annealed and Spinodal Hardened (TX 00)
(Composition similar to UNS C72900)

RATIONALE

AMS4598A corrects an error in the converted metric value for tensile yield strength in forward extruded product (Table 2).

1. SCOPE

1.1 Form

This specification covers a copper-nickel-tin alloy in the form of mechanical tube (See 8.8).

1.2 Application

These products have been used typically for parts requiring high strength, wear resistance, and corrosion resistance at moderate temperatures, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2750 Pyrometry

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4598A>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

- ASTM B 251 General Requirements for Wrought Seamless Copper and Copper-Alloy Tube
- ASTM B 251M General Requirements for Wrought Seamless Copper and Copper-Alloy Tube (Metric)
- ASTM E 8/E 8M Tension Testing of Metallic Materials
- ASTM E 18 Rockwell Hardness of Metallic Materials
- ASTM E 478 Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to the purchaser.

TABLE 1 - COMPOSITION

Element (3.1.1)	min	max
Nickel (+ Cobalt)	14.5	15.5
Tin	7.5	8.5
Iron	--	0.50
Zinc	--	0.50
Manganese	--	0.30
Columbium	--	0.10
Magnesium	--	0.15
Lead	--	0.02
Copper (3.1.2)	remainder	
Copper + sum of Named Elements (3.1.3)	99.5	

- 3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.
- 3.1.2 Copper may be reported as "remainder", or as the difference between the sum of results for all elements and 100%, or as the result of direct analysis.
- 3.1.3 When all the elements in the table are analyzed, the sum shall be 99.5% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition

The product shall be supplied in the following condition:

Vertically continuously cast, extruded, and, if necessary, cold finished; solution annealed and spinodal hardened to the TX 00 temper (See 8.2).

3.3 Heat Treatment

Product shall be heat treated as follows; pyrometry shall be in accordance with AMS2750.

3.3.1 Solution Annealing

Heat within the range 1450 to 1600 °F (788 to 870 °C), hold at heat for 45 to 360 minutes and water quench in room temperature water.

3.3.2 Spinodal Hardening

Heat to 600 to 800 °F (315 to 425 °C), hold at heat for a total time at temperature greater than 1 hour and less than 10 hours, depending on section thickness to meet the property requirements of 3.4, then air cool or quench (TX 00 temper, See 8.2).

3.4 Properties

The product shall conform to the following requirements:

3.4.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E 8/E 8M.

TABLE 2 - MINIMUM LONGITUDINAL TENSILE PROPERTIES

Nominal Outside Diameter* (tube)	Ultimate Tensile Strength	Yield Strength (at 0.2% offset)	Elongation in 4D
1.100 (28 mm) to 7.250 inches (184 mm), incl (A)	131 ksi (903 MPa)	104 ksi (717 MPa)	8%
7.250 (184 mm) to 13.6 inches (330 mm) (B)	130 ksi (896 MPa)	108 ksi (745 MPa)	5%

*Wall thickness is dependent on outside diameter and averages approximately 15% of OD in extrusions
(A) Forward extruded, (B) Back extruded

3.4.2 Hardness

Tubes shall have a minimum hardness of 30 HRC, or equivalent (See 8.5) determined in accordance with ASTM E 18.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound and free of foreign materials and from imperfections detrimental to the usage of the product.

3.5.1 Soundness

When specified, the product shall be ultrasonically inspected to a specification and acceptance criterion agreed to by the purchaser and supplier (See 8.7).

3.6 Tolerances

3.6.1 Diameter tolerances shall be in accordance with Table 3.

TABLE 3 - HOT WORKED TUBE DIAMETER TOLERANCES

Specified Outside or Inside Diameter, inches (mm)	Tolerance, Plus and Minus, inch (mm)
Over 0.5 (1.27) to 1 (25.4), incl	0.020 (0.51)
Over 1 (25.4) to 2 (50.8), incl	0.030 (0.76)
Over 2 (50.8) to 3 (76.2), incl	0.040 (1.02)
Over 3 (76.2) to 4 (102), incl	0.050 (1.27)
Over 4 (102) to 8 (203), incl	0.060 (1.52)
Over 8 (203)	0.060 (1.52)

3.6.2 Straightness as measured by maximum depth of arc along any longitudinal surface or edge shall not exceed 1/4 inch (6.35 mm) (for product length less than 10 feet (3.05 m)) or 1/2 inch (12.7 mm) (for product 10 feet (3.05 m) or longer).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each melt or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with ASTM B 251/B 251M and the following; a lot shall be all products with the same form, from the same heat, processed at one time through all steps of manufacture.

4.3.1 One or more chemical analysis samples from each heat shall be analyzed in accordance with 3.1.

4.3.2 One or more longitudinal tensile specimens from each lot shall be tested in accordance with 3.4.1.

4.3.3 One or more hardness specimens from each lot shall be tested in accordance with 3.4.2.

4.3.4 Testing for soundness shall be in accordance with 3.5.1 with sampling at a frequency agreed upon by the purchaser and supplier, but not less than one tube length per lot.

4.4 Reports

The vendor of tubes shall furnish with each shipment a report showing the results of the tests for the composition of each heat and for tensile properties and hardness of each lot and stating that the product conforms to the other technical requirements. The report shall include the purchaser order number, heat and lot numbers, AMS4598A, size or part number, and quantity.