

AEROSPACE
MATERIAL
SPECIFICATION

AMS 4611E
Superseding AMS 4611D

Issued 12-1-42
Revised 1-1-83

UNS C46400

BRASS BARS AND RODS, NAVAL
60.5Cu - 38.7Zn - 0.8Sn
Half Hard

1. SCOPE:

1.1 Form: This specification covers one type of brass in the form of bars and rods.

1.2 Application: Primarily for automatic screw machine parts. These products have better corrosion resistance than AMS 4610 but are less readily machinable.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2221 - Tolerances, Copper and Copper Alloy Bars and Rods
AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B154 - Mercurous Nitrate Test for Copper and Copper Alloys
ASTM B249 - General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, and Shapes
ASTM E8 - Tension Testing of Metallic Materials
ASTM E478 - Chemical Analysis of Copper Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-C-3993 - Copper and Copper-Base Alloy Mill Products, Packaging of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM 478, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Copper	59.0	- 62.0
Tin	0.50	- 1.0
Lead	--	0.20
Iron	--	0.10
Other Elements, total	--	0.10
Zinc	remainder	

3.2 Condition: Cold finished, half-hard temper.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8 and 4.3.2.1.

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D &, min
Up to 0.500, incl	60,000	27,000	22 (See 3.3.1.1.1)
Over 0.500 to 1.000, incl	60,000	27,000	25
Over 1.000 to 2.500, incl	58,000	26,000	25
Over 2.500 to 3.500, incl	54,000	25,000	27
Over 3.500	54,000	22,000	30

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D &, min
Up to 12.50, incl	415	185	22 (See 3.3.1.1.1)
Over 12.50 to 25.00, incl	415	185	25
Over 25.00 to 62.50, incl	400	186	25
Over 62.50 to 87.50, incl	370	170	27
Over 87.50	370	150	30

3.3.1.1 In no case shall the gage length be less than 1 in. (25 mm).

Ø

3.3.2 Embrittlement: Specimens as in 4.3.3.1 shall withstand, without cracking, immersion in mercurous nitrate solution in accordance with ASTM B154, Procedure A.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to AMS 2221 as applicable to nonrefractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with ASTM B249 and the following:

4.3.1 Composition: One sample from each lot.

4.3.2 Tensile Properties: One sample from each lot.

4.3.2.1 Tensile tests shall be performed on full-section specimens when practicable. When machined specimens are required, the axis of the specimen shall coincide with the central axis of the piece except that for bars and rods over 1.50 in. (37.5 mm) in nominal diameter or distance between parallel sides, the axis shall be midway between center and surface of the piece. The longitudinal axis of the tensile specimen shall be parallel to the direction of rolling or drawing.

4.3.3 Embrittlement: As agreed upon by purchaser and vendor.

4.3.3.1 Specimens for embrittlement test shall be full cross-section of the product and shall have length of approximately 6 in. (150 mm) or twice the nominal diameter or least distance between parallel sides, whichever is greater.