

AEROSPACE MATERIAL SPECIFICATION



AMS4634B

Issued 1993-01
Reaffirmed 2006-04
Revised 2009-03

Superseding AMS4634A

Aluminum Bronze Bars, Rods, and Forgings
90.5Cu - 7.5Al - 1.9Si
Stress Relieved

(Composition similar to UNS C64200)

RATIONALE

AMS4634B results from a 5 Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum bronze alloy in the form of bars, rods, forgings, and forging stock.

1.2 Application

These products have been used typically for parts requiring strength and wear resistance at moderate temperatures, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2808 Identification, Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2009 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4634B>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 154 Mercurous Nitrate Test for Copper and Copper Alloys

ASTM B 249/249M General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes, and Forgings

ASTM B 858M Determination of Susceptibility to Stress Corrosion Cracking in Copper Alloys Using an Ammonia Vapor Test

ASTM E 8/8M Tension Testing of Metallic Materials

ASTM E 10 Brinell Hardness of Metallic Materials

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 478 Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element (3.1.1)	min	max
Aluminum	6.3	7.6
Silicon	1.5	2.2
Iron	--	0.30
Nickel (incl Cobalt)	--	0.25
Manganese	--	0.10
Tin	--	0.20
Zinc	--	0.50
Lead	--	0.05
Copper (incl Silver)		(See 3.1.2)
Sum of Named Elements (3.1.3)	99.5	--

3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.

3.1.2 Copper may be reported as "remainder", or as the difference between the sum of results for all elements and 100%, or as the result of direct analysis.

3.1.3 When all named elements in Table 1 are analyzed, the sum shall be 99.5% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars and Rods

Hot rolled or drawn, or extruded, cold finished if necessary, and stress relieved or stress relief annealed to meet the requirements of 3.3.1.1. (HR50) (See 8.2).

3.2.2 Forgings

Stress relieved.

3.2.3 Forging Stock

As ordered by the forging manufacturer.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Bars, Rods, and Forgings

3.3.1.1 Tensile Properties

3.3.1.1.1 Bars and Rods

Shall be as specified in Table 2, determined in accordance with ASTM E 8/8M.

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Diameter or Distance Between Parallel Sides, Inches	Tensile Strength ksi	Yield Strength	
		at 0.5% Extension Under Load ksi	Elongation in 4D %
Up to 0.500, incl	90.0	45.0	9
Over 0.500 to 1.000, incl	85.0	45.0	12
Over 1.000 to 2.000, incl	80.0	42.0	12
Over 2.000 to 3.000, incl	75.0	35.0	15

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Diameter or Distance Between Parallel Sides, Millimeters	Tensile Strength MPa	Yield Strength	
		at 0.5% Extension Under Load MPa	Elongation in 4D %
Up to 12.70, incl	621	310	9
Over 12.70 to 25.40, incl	586	310	12
Over 25.40 to 50.80, incl	552	290	12
Over 50.80 to 76.20, incl	517	241	15

3.3.1.1.2 Forgings

Shall be as agreed upon by purchaser and vendor.

3.3.1.2 Hardness

Shall be as follows:

3.3.1.2.1 Surface

Not lower than 130 HB/10/1000, or equivalent, (See 8.3) determined in accordance with ASTM E 10; on rounds; a flat, as necessary for accuracy, may be made.

3.3.1.2.2 Internal

Not lower than 80 HRB, or equivalent, (See 8.3) determined in accordance with ASTM E 18 at mid-radius or quarter thickness.

3.3.1.3 Embrittlement

Specimens as in 4.3.1.2 and 4.3.2.1 shall withstand, without cracking, immersion in mercurous nitrate solution in accordance with ASTM B 154, Procedure A, or the Ammonia Vapor Test in accordance with ASTM B 858M.

3.3.2 Forging Stock

Shall be as agreed upon by purchaser and vendor.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Bars and rods shall conform to ASTM B 249/249M as applicable.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1.1), hardness (3.3.1.2), and tolerances (3.5) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests

Embrittlement (3.3.1.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.