



AEROSPACE MATERIAL SPECIFICATION

AMS4634

REV. C

Issued 1993-01
Revised 2015-02

Superseding AMS4634B

Aluminum Bronze Bars, Rods, and Forgings
90.5Cu - 7.5Al - 1.9Si
Stress Relieved
(Composition similar to UNS C64200)

RATIONALE

AMS4634C revises Composition (3.1.2), Properties (3.3.1.1.1), and Reports (4.4) and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum bronze alloy in the form of bars, rods, forgings, and forging stock.

1.1.1 This specification covers products up to 3.000 inches (76.20 mm) in diameter or distance between parallel sides, and forging stock of any size (See 8.5).

1.2 Application

These products have been used typically for parts requiring strength and wear resistance at moderate temperatures, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2808 Identification, Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4634C>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B154	Mercurous Nitrate Test for Copper and Copper Alloys
ASTM B249/B249M	General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes, and Forgings
ASTM B858	Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E10	Brinell Hardness of Metallic Materials
ASTM E18	Rockwell Hardness of Metallic Materials
ASTM E478	Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element (3.1.1)	min	max
Aluminum	6.3	7.6
Silicon	1.5	2.2
Iron	--	0.30
Nickel (incl Cobalt)	--	0.25
Manganese	--	0.10
Tin	--	0.20
Zinc	--	0.50
Lead	--	0.05
Copper (incl Silver)		(See 3.1.2)
Sum of Named Elements (3.1.3)	99.5	--

- 3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.
- 3.1.2 Copper may be reported as "remainder", or as the difference between the sum of results for all analyzed elements and 100%, or as the result of direct analysis.
- 3.1.3 When all named elements in Table 1 are analyzed, the sum shall be 99.5% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars and Rods

Hot rolled or drawn, or extruded, cold finished if necessary, and stress relieved or stress relief annealed to meet the requirements of 3.3.1.1. (HR50) (See 8.2).

3.2.2 Forgings

Stress relieved.

3.2.3 Forging Stock

As ordered by the forging manufacturer.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Bars, Rods, and Forgings

3.3.1.1 Tensile Properties

3.3.1.1.1 Bars and Rods

Shall be as specified in Table 2, determined in accordance with ASTM E8/E8M. Mechanical property requirements for outside of the range covered by Table 2 shall be agreed upon between purchaser and producer.

Table 2A - Minimum tensile properties, inch/pound units

Nominal Diameter or Distance Between Parallel Sides, Inches	Tensile Strength ksi	Yield Strength at 0.5% Extension Under Load ksi	Elongation in 4D %
Up to 0.500, incl	90.0	45.0	9
Over 0.500 to 1.000, incl	85.0	45.0	12
Over 1.000 to 2.000, incl	80.0	42.0	12
Over 2.000 to 3.000, incl	75.0	35.0	15

Table 2B - Minimum tensile properties, SI units

Nominal Diameter or Distance Between Parallel Sides, Millimeters	Tensile Strength MPa	Yield Strength at 0.5% Extension Under Load MPa	Elongation in 4D %
Up to 12.70, incl	621	310	9
Over 12.70 to 25.40, incl	586	310	12
Over 25.40 to 50.80, incl	552	290	12
Over 50.80 to 76.20, incl	517	241	15

3.3.1.1.2 Forgings

Shall be as agreed upon by purchaser and vendor.

3.3.1.2 Hardness

Shall be as follows:

3.3.1.2.1 Surface

Not lower than 130 HB/10/1000, or equivalent, (See 8.3) determined in accordance with ASTM E10; on rounds; a flat, as necessary for accuracy, may be made.

3.3.1.2.2 Internal

Not lower than 80 HRB, or equivalent, (See 8.3) determined in accordance with ASTM E18 at mid-radius or quarter thickness.

3.3.1.3 Embrittlement

Specimens as in 4.3.1.2 and 4.3.2.1 shall withstand, without cracking, immersion in mercurous nitrate solution in accordance with ASTM B154, Procedure A, or the Ammonia Vapor Test in accordance with ASTM B858.

3.3.2 Forging Stock

Shall be as agreed upon by purchaser and vendor.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Bars and rods shall conform to ASTM B249/B249M as applicable.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1.1), hardness (3.3.1.2), and tolerances (3.5) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests

Embrittlement (3.3.1.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with the following:

4.3.1 Bars and Rods

ASTM B249/B249M and the following:

4.3.1.1 Specimens for tensile testing of bars and rods over 1.500 inches (38.10 mm) in nominal diameter or distance between parallel sides shall have their axes located approximately midway between center and surface.