



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4675™</b>	<b>REV. E</b>
	Issued 1963-07 Reaffirmed 2003-05 Revised 2017-01 Superseding AMS4675D	
Nickel-Copper Alloy, Corrosion-Resistant, Bars and Forgings 67Ni - 30Cu (Composition similar to UNS N04400)		

### RATIONALE

AMS4675E revises Chemical Analysis Standards (3.1), Properties (3.3.1.3), and Reports (4.4), and is a Five-Year Review and update of this specification.

#### 1. SCOPE

##### 1.1 Form

This specification covers a corrosion-resistant nickel-copper alloy in the form of bars 0.093 to 4.000 inches (2.35 to 100.00 mm) in diameter or distance between parallel sides, and forgings and forging stock of any size (see 8.5).

##### 1.2 Application

These products have been used typically for fittings, such as cones, nipples, and unions, in fluid line assemblies using AMS4574 or AMS4575 tubing, but usage is not limited to such applications.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

- AMS2261 Tolerances Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
- AMS2269 Chemical Check Analysis Limits Nickel, Nickel Alloys, and Cobalt Alloys
- AMS2371 Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steels and Alloys Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this Technical Report, please visit**  
<http://standards.sae.org/AMS4675E>

AMS2374	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2806	Identification Bars, Wire, Mechanical Tubing, and Extrusions Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification Forgings
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM E8/E8M Tension Testing of Metallic Materials

ASTM E18 Rockwell Hardness of Metallic Materials

ASTM E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness Rockwell Hardness

ASTM E1473 Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E1473, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

**Table 1. Composition**

Element	Min	Max
Carbon	--	0.30
Manganese	--	2.00
Silicon	--	0.50
Copper	28.0	34.00
Iron	--	2.50
Nickel	remainder	

#### 3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

### 3.2 Condition

The product shall be supplied in the following condition:

#### 3.2.1 Bars

Cold drawn and stress relieved by heating to a temperature within the range 1000 to 1100 °F (538 to 593 °C), holding at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) for 1 hour  $\pm$  0.25 hour, and cooling at a rate equivalent to cooling in air.

3.2.1.1 Bars shall not be cut from plate (also see 4.4.2).

## 3.2.2 Forgings

As forged.

## 3.2.3 Forging Stock

As ordered by the forging manufacturer.

## 3.3 Properties

The product shall conform to the following requirements:

## 3.3.1 Tensile Properties

Shall be as follows, determined in accordance with ASTM E8/E8M:

## 3.3.1.1 Round Bars

Shall be as shown in Table 2.

**Table 2**

**Table 2A - Minimum tensile properties, inch/pound units**

Nominal Diameter Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %
0.093 to 0.500, excl	84	50	10
0.500 to 3.500, incl	87	60	22
Over 3.500 to 4.000, incl	84	55	25

**Table 2B - Minimum tensile properties, SI units**

Nominal Diameter Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D %
2.35 to 12.50, excl	579	345	10
12.50 to 87.50, incl	600	414	22
Over 87.50 to 100.00, incl	579	379	25

## 3.3.1.2 Hexagonal, Square, and Rectangular Bars

Shall be as shown in Table 3.

**Table 3**

**Table 3A - Minimum tensile properties, inch/pound units**

Nominal Distance Between Parallel Sides Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %
0.093 to 0.500, incl	84	50	10
0.500 and over	84	50	22

**Table 3B - Minimum Tensile properties, SI units**

Nominal Distance Between Parallel Sides Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D %
2.35 to 12.50, excl	579	345	10
12.50 and over	579	345	22

3.3.1.3 Mechanical property requirements for product outside the range covered by Tables 2 and 3 shall be agreed upon between purchaser and producer.

### 3.3.2 Hardness

#### 3.3.2.1 Bars

Should be not lower than the values shown, or equivalent (see 8.2), determined in accordance with ASTM E18. Product shall not be rejected on the basis of hardness if the tensile properties of Table 2 or Table 3 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness.

Minimum Hardness, HRB

Rounds 84

Hexagons, Squares, and Rectangles 80.

#### 3.3.2.2 Forgings

Shall have hardness of 78 to 96 HRB, or equivalent (see 8.2), determined in accordance with ASTM E18.

### 3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

### 3.5 Tolerances

3.5.1 Bars shall conform to all applicable requirements of AMS2261.

3.5.2 Tolerances for forgings and forging stock shall be as acceptable to purchaser.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.