

BRASS WIRE
65Cu - 35Zn
Annealed

UNS C27000

1. SCOPE:

1.1 Form: This specification covers one type of brass in the form of wire.

1.2 Application: Primarily for woven wire screening.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2224 - Tolerances, Copper and Copper Alloy Wire
AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B250 - General Requirements for Wrought Copper-Alloy Wire
ASTM E112 - Estimating the Average Grain Size of Metals
ASTM E478 - Chemical Analysis of Copper Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 4712C

2.3.2 Military Specifications:

MIL-C-3993 - Copper and Copper-Base Alloy Mill Products, Packaging of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight,
Ø determined by wet chemical methods in accordance with ASTM E478, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Copper	63.00	68.50
Lead	--	0.10
Iron	--	0.07
Other Elements, each	--	0.05
Other Elements, total	--	0.25
Zinc		remainder

3.2 Condition: Cold-drawn or cold-rolled, and annealed.

3.3 Properties: Wire shall conform to the following requirements:

3.3.1 Grain Size: Average grain size shall be 0.035 - 0.070 mm, determined in accordance with ASTM E112 on a longitudinal section.

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the wire.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to AMS 2224 as applicable to nonrefractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples
Ø for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.3 Sampling: Shall be in accordance with ASTM B250.

4.4 Reports:

- 4.4.1 The vendor of wire shall furnish with each shipment three copies of a report showing the results of tests on each lot to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4712C, nominal size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 4712C, contractor or other direct supplier of wire, part number, and quantity. When wire for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of wire to determine conformance to the requirements of this specification and shall include in the report either a statement that the wire conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the wire may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the wire represented and no additional testing shall be permitted. Reports of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Wire shall be supplied on spools or in coils except when straight lengths are ordered.

5.2 Identification:

5.2.1 Spools and Coils: Shall be marked with a durable tag or label showing the manufacturer's identification, purchase order number, AMS 4712C, nominal size, and quantity; boxes or drums shall be marked with the same information.

5.2.2 Straight Lengths: Shall have attached to each bundle or enclosed in each box a durable tag or label marked with the information of 5.2.1; when boxed, the box shall be marked with the same information.

5.3 Packaging:

5.3.1 Spools and Coils: Coils shall be individually wrapped with waterproof paper or packed in waterproof drums. Spools, when ordered, shall be boxed.

5.3.2 Straight Lengths: Shall be bundled or boxed.