

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4713A

Issued 7-1-45

Revised 3-1-51

BRASS WIRE
65Cu-35Zn
Eighth Hard

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for cold headed parts such as pins and rivets.

3. COMPOSITION:

Copper	63.0 - 68.5
Lead	0.1 max
Iron	0.05 max
Zinc	remainder

4. CONDITION: Cold drawn or rolled, eighth hard temper.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	50,000 - 65,000
-----------------------	-----------------

6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2224 as applicable. Diameter, thickness and width tolerances shall be as specified below:

7.1 Rounds, Hexagons and Octagons: Table II, Non-refractory.

7.2 Squares: Table III, Non-refractory.

7.3 Rectangles, Thickness: Table III, Non-refractory.

7.4 Rectangles, Width: Table IV, Non-refractory.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of wire shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the requirements of this specification or stating that the chemical composition and tensile properties of the wire conform to the requirements specified. This report shall include the purchase order number material specification number, size, and quantity.

on 7C of the SAE Technical Board rules provides that: "All technical reports, including stand- approved and practices recommended, are advisory only. Their by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."