

Issued	1970-11
Revised	2007-07
Reaffirmed	2012-10
Superseding AMS4731B	

Nickel-Copper Alloy Wire and Ribbon, Corrosion-Resistant
67Ni - 31Cu
Annealed

(Composition similar to UNS N04400)

RATIONALE

AMS4731C has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant nickel-copper alloy in the form of wire and ribbon.

1.2 Application

This product is used typically for parts where essentially nonmagnetic properties are required, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
AMS 2371 Quality Assurance Sampling of Corrosion and Heat-Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 8 Tension Testing of Metallic Materials
ASTM E 76 Chemical Analysis of Nickel-Copper Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4731C>

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the following percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 76 or by spectrographic or other analytical methods approved by purchaser:

TABLE 1 - COMPOSITION

Element	min	max
Nickel	63.0	--
Copper	28.0	34.0
Iron	--	2.5
Manganese	--	2.0
Aluminum	--	0.50
Silicon	--	0.50
Carbon	--	0.20
Phosphorus	--	0.02
Zinc	--	0.02
Sulfur	--	0.015
Lead	--	0.006
Tin	--	0.006

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition

Cold drawn or cold rolled, annealed, and, unless annealing is performed in an atmosphere yielding a bright finish, descaled.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Tensile Strength

Shall be not higher than 85 ksi (585 MPa), determined in accordance with ASTM E 8.

3.4 Quality

The product shall be uniform in quality, condition, temper, and cross section. Surfaces shall, determined at up to 30X magnification, be free from scale, corrosion, cracks, seams, scratches, slivers, dirt, grease, oil, streaks, stains, pit marks, burns, dents, blisters, laps, grooves, inclusions, and other imperfections detrimental to usage of the product.

3.5 Sizes and Tolerances

The product shall be supplied in the sizes and to the tolerances specified in 3.5.1 and 3.5.2.

3.5.1 Round Wire (Cold Drawn)

Shall be as shown in Table 2.

TABLE 2A - DIAMETRAL TOLERANCES, INCH/POUND UNITS

Nominal Diameter Inch	Tolerance, Inch plus and minus
0.0040	0.0002
0.0060	0.0002
0.0080	0.0003
0.0120	0.0003
0.0160	0.0004
0.0200	0.0005
0.0250	0.0005
0.0320	0.0006
0.0400	0.0006

TABLE 2B - DIAMETRAL TOLERANCES, SI UNITS

Nominal Diameter Millimeters	Tolerance, Millimeters plus and minus
0.100	0.005
0.150	0.005
0.200	0.008
0.300	0.008
0.400	0.010
0.500	0.012
0.625	0.012
0.800	0.015
1.000	0.015

3.5.2 Ribbon (Cold Rolled)

3.5.2.1 Thickness

Shall be as shown in Table 3.

TABLE 3A - THICKNESS TOLERANCES, INCH/POUND UNITS

Nominal Thickness (T) Inch	Tolerance, Inch plus and minus
0.002	0.050T
0.003	0.050T
0.004	0.050T
0.005	0.050T
0.006	0.050T
0.008	0.050T
0.010	0.050T
0.012	0.001
0.016	0.0015
0.020	0.0015
0.025	0.0015
0.032	0.0015
0.040	0.0015
0.051	0.0015

TABLE 3B - THICKNESS TOLERANCES, SI UNITS

Nominal Thickness (T) Millimeters	Tolerance, Millimeters plus and minus
0.05	1.27T
0.08	1.27T
0.10	1.27T
0.12	1.27T
0.15	1.27T
0.20	1.27T
0.25	1.27T
0.30	0.03
0.40	0.038
0.50	0.038
0.62	0.038
0.80	0.038
1.00	0.038
1.28	0.038

3.5.2.2 Width

Shall be as shown in Table 4.

TABLE 4A - WIDTH TOLERANCES, INCH/POUND UNITS

Nominal Width Inch	Tolerance, Inch plus and minus
0.015	0.0025
0.031	0.0025
0.046	0.0025
0.062	0.0025
0.093	0.004
0.125	0.005
0.187	0.005
0.250	0.005
0.375	0.005
0.500	0.005
0.625	0.005
0.750	0.007
1.000	0.007

TABLE 4B - WIDTH TOLERANCES, SI UNITS

Nominal Width Millimeters	Tolerance, Millimeters plus and minus
0.38	0.062
0.78	0.062
1.15	0.062
1.55	0.062
2.32	0.10
3.12	0.012
4.75	0.012
6.25	0.012
9.50	0.012
12.50	0.012
15.60	0.012
18.75	0.018
25.00	0.018