



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

**AMS 4773B**  
Superseding AMS 4773A

Issued 1-15-59  
Revised 7-15-78

UNS P07600

BRAZING FILLER METAL, SILVER  
60Ag - 30Cu - 10Sn  
1115° - 1325°F (600° - 720°C) Solidus-Liquidus Range

## 1. SCOPE:

- 1.1 Form: This specification covers a silver alloy in the form of wire, rod, sheet, strip, pig, powder, shot, and chips.
- 1.2 Application: Primarily for joining ferrous metals, particularly austenitic steels and alloys, where moderate joint strength up to 600°F (315°C) for short-time service or 400°F (205°C) for long-time service is required, and for joining nonferrous metals except those having base of aluminum or magnesium. This filler metal is particularly suitable for brazing in hydrogen or inert atmosphere.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2222 - Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate  
AMS 2224 - Tolerances, Copper and Copper Alloy Wire  
AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B214 - Sieve Analysis of Granular Metal Powders  
ASTM B293 - Subsieve Analysis of Granular Metal Powders by Air Classification  
ASTM E56 - Chemical Analysis of Silver Brazing Alloys

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

## 3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E56, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Silver	59.0	61.0
Copper	29.0	31.0
Tin	9.5	10.5
Phosphorus	--	0.025
Other Elements, total (3.1.1)	--	0.15

∅ 3.1.1 Determination not required for routine acceptance.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Wire: Cold drawn or cold rolled, as ordered, in annealed temper, and cleaned.

3.2.2 Rod: Cold drawn, cold rolled, or extruded, as ordered, in hard temper, and cleaned.

3.2.3 Sheet and Strip: Cold rolled, hard.

3.2.4 Pig, Powder, Shot, and Chips: As fabricated.

3.3 Properties: Filler metal shall conform to the following requirements:

∅ 3.3.1 Color: Shall be yellow-white.

3.3.2 Flatness: When unrolled, strip shall lie flat with no undue tendency to recoil.

3.4 Quality: The product shall be uniform in color, quality, and condition and free from foreign materials and from imperfections detrimental to its working qualities. Wire rod, sheet, and strip shall be clean, sound, bright, and free from slivers, splitting, ragged edges, damaged ends, and other injurious imperfections. Pig, powder, shot, and chips shall have a metallic luster.

3.5 Sizes and Tolerances: The product shall be supplied in the following standard sizes and to the tolerances shown, unless otherwise specified:

3.5.1 Wire and Rod:

3.5.1.1 Nominal Diameters:

∅	Inch	(Millimetres)	Inch	(Millimetres)	Inch	(Millimetres)
	0.005	(0.13)	0.031	(0.79)	0.125	(3.18)
	0.007	(0.18)	0.040	(1.02)	0.175	(4.44)
	0.010	(0.25)	0.047	(1.19)	0.188	(4.78)
	0.015	(0.38)	0.062	(1.57)	0.225	(5.72)
	0.025	(0.64)	0.094	(2.39)	0.250	(6.35)

3.5.1.2 Diameter Tolerances for Drawn Wire and Rod: AMS 2224 as applicable to refractory alloys.

3.5.1.3 Diameter Tolerance for Rolled or Extruded Wire and Rod:

TABLE I

$\emptyset$	Nominal Diameter or Distance Between Parallel Sides Inch	Tolerances, Inch Plus and Minus	
		Rounds	Squares
		0.031 to 0.062, incl	0.005
Over 0.062 to 0.125, incl	0.006	--	
Over 0.125 to 0.188, incl	0.007	0.009	
Over 0.188 to 0.250, incl	0.008	0.010	

TABLE I (SI)

$\emptyset$	Nominal Diameter or Distance Between Parallel Sides Millimetres	Tolerances, Millimetre Plus and Minus	
		Rounds	Squares
		0.79 to 1.57, incl	0.13
Over 1.57 to 3.18, incl	0.15	--	
Over 3.18 to 4.78, incl	0.18	0.23	
Over 4.78 to 6.35, incl	0.20	0.25	

3.5.2 Sheet and Strip:

3.5.2.1 Nominal Thickness:

Inch	(Millimetre)	Inch	(Millimetre)
0.001	(0.03)	0.006	(0.15)
0.0015	(0.038)	0.008	(0.20)
0.002	(0.05)	0.010	(0.25)
0.003	(0.08)	0.014	(0.36)
0.004	(0.10)	0.020	(0.51)
0.005	(0.13)	0.030	(0.76)

3.5.2.2 Tolerances: Thicknesses under 0.002 in. (0.05 mm) shall have a tolerance of  $\pm 0.0002$  in. ( $\pm 0.005$  mm); thicknesses 0.002 in. (0.05 mm) and over shall have tolerances conforming to AMS 2222 as applicable to refractory alloys. Width of individual rolls shall not vary more than  $\pm 0.010$  in. ( $\pm 0.25$  mm) from nominal width ordered. The length in a roll is not limited except that no roll shall weigh more than 75 lb (34 kg).

3.5.3 Powder:

3.5.3.1 Nominal Sizes: -60, -100, -200 and -325.

3.5.3.2 Tolerances: Nominal sizes shown in 3.5.3.1 shall be supplied in accordance with the following tolerances on particle size distribution, determined in accordance with ASTM B214:

Nominal Size	Not Less Than 95% Through U. S. Sieve Series Number	Not More Than 10% Through U. S. Sieve Series Number
-60	60	200
-100	100	325
-200	200	400
-325	325	As in 3.5.3.2.1

$\emptyset$  3.5.3.2.1 Not more than 10% finer than a 10 micron particle size, determined in accordance with ASTM B293.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot of product.
- 4.3 Sampling: Shall be in accordance with the following; a lot shall be all product other than powder produced from a single furnace charge and presented for vendor's inspection at one time; a lot of powder shall be that product produced from a uniform blend of powder produced from one or more furnace charges and presented for vendor's inspection at one time:
- Ø 4.3.1 Composition: One sample from each lot.
- Ø 4.3.2 Properties: One sample from each lot.
- Ø 4.3.3 Other Technical Requirements: As agreed upon by purchaser and vendor.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the composition requirements and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, lot number, material specification number and its revision letter, form, size, and quantity from each lot.
- 4.4.2 When parts made of this filler metal or assemblies requiring use of this filler metal are supplied, the part or assembly manufacturer shall inspect each lot of filler metal to determine conformance to the technical requirements of this specification and shall furnish with each shipment three copies of a report stating that the filler metal conforms. This report shall include the purchase order number, material specification number and its revision letter, part or assembly number, and quantity.
- 4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

- 5.1.1 The product shall be identified as agreed upon by purchaser and vendor.
- 5.1.2 Each exterior container or package shall be permanently and legibly marked to show not less than the following information:

BRAZING FILLER METAL

AMS 4773B

LOT NUMBER \_\_\_\_\_

MANUFACTURER'S IDENTIFICATION \_\_\_\_\_

NOMINAL DIMENSIONS \_\_\_\_\_

WEIGHT \_\_\_\_\_

5.2 Packaging: