

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 4779D

Issued 30 JUN 1960
Revised 1 APR 1992

Superseding AMS 4779C

Submitted for recognition as an American National Standard

NICKEL ALLOY BRAZING FILLER METAL
94Ni - 3.5Si - 1.8B
1800 to 1950 °F (982 to 1066 °C) Solidus-Liquidus Range
UNS N99640

1. SCOPE:

1.1 Form:

This specification covers a nickel alloy in the form of wire, rod, strip, foil, and powder and a viscous mixture (paste) of the powder in a suitable binder.

1.2 Application:

Primarily for joining corrosion and heat resistant steels and alloys requiring corrosion and oxidation resistant joints with good strength at elevated temperatures. Also may be used as a corrosion and oxidation resistant hard coating. Flows well in most reducing and neutral atmospheres.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The applicable issue of referenced publications shall be the issue in effect on the date of the purchase order.

2.1 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 214 Sieve Analysis of Granular Metal Powders

ASTM D 638 Tensile Properties of Plastics

ASTM D 638M Tensile Properties of Plastics (Metric)

ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.2 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	—	0.06
Silicon	3.00	4.00
Phosphorus	—	0.02
Sulfur	—	0.02
Boron	1.50	2.20
Iron	—	1.50
Cobalt (3.1.1)	—	0.10
Titanium	—	0.05
Aluminum	—	0.05
Selenium (3.1.1)	—	0.005 (50 ppm)
Zirconium	—	0.05
Nickel	remainder	

3.1.1 Determination not required for routine acceptance.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Wire and Strip: Powder bonded in a suitable plastic.

3.2.2 Rod: As cast, with fins and projections removed.

3.2.3 Foil and Powder: As fabricated.

3.2.4 Paste: Shall consist of 84 to 90% by weight powder in a suitable binder (R) and, unless otherwise ordered, shall not contain flux.

3.3 Properties:

Filler metal shall conform to the following requirements:

3.3.1 Wire and Strip:

3.3.1.1 Burn-Off of Plastic: The plastic used for bonding powder to form wire and strip shall burn off, leaving no adherent residue, when the product is heated to a temperature not higher than 1800 °F (980 °C).
(R)

3.3.1.2 Tensile Strength: Shall be not lower than 360 psi (2.5 MPa), determined in accordance with ASTM D 638 or ASTM D 638M, Speed B.

3.3.1.3 Metallic Content: The ratio of volume of powder to volume of plastic binder shall be the largest possible consistent with the requirements of 3.3.1.1 and 3.3.1.2.

3.3.2 Rod, Foil, and Powder: When specified, properties shall be as agreed upon by purchaser and vendor.
(R)

3.3.3 Paste:

3.3.3.1 Paste shall have a shelf life of not less than six months; not more than thorough mixing shall be required to restore paste for use during that time.

3.3.3.2 Paste without flux shall leave no adherent residue when heated in a protective atmosphere to a temperature higher than 1000 °F (538 °C).
(R)

3.3.4 When used as a hard coating, alloy shall melt quickly and shall flow freely under neutral oxy-acetylene flame, without bubbling or boiling, to produce an adherent deposit free from porosity due to blow-holes, gas cavities, or slag inclusions.

3.3.4.1 Alloy, deposited as in 3.3.4, shall have hardness not lower than 20 HRC, or equivalent, determined in accordance with ASTM E 18.

3.4 Quality:

The product, as received by purchaser, shall be uniform in color, quality, and condition and free from foreign materials and from imperfections detrimental to its working qualities. Rod and powder shall have a metallic luster. Wire, strip, and foil shall be clean, sound, smooth, and free from ragged edges, splitting, damaged ends, and other imperfections detrimental to usage of the product.

3.5 Sizes and Tolerances:

The product shall be supplied in the following standard sizes and to the tolerances shown:

3.5.1 Wire:

3.5.1.1 Nominal Diameters:

TABLE 2 - Standard Diameter Sizes

Inch	Millimeters
0.031	0.79
0.062	1.57
0.125	3.18
0.188	4.78

3.5.1.2 Diameter Tolerances: ± 0.004 inch (± 0.10 mm).

3.5.2 Rod:

3.5.2.1 Nominal Diameters: Shall be as ordered.

3.5.2.2 Diameter Tolerances:
(R)

TABLE 3 Diameter Tolerance

Diameter Inch	Diameter Millimeters	Tolerance, % of Diameter
0.031	0.79	± 20
0.062	1.57	± 15
0.125	3.18	± 10
0.188	4.78	± 10

3.5.2.3 Concentricity: When long lengths are supplied as welded composites of cast lengths, the diameters of the adjacent sections shall be concentric within ± 0.031 inch (± 0.79 mm).

3.5.3 Strip and Foil: When specified, properties shall be as agreed upon by
(R) purchaser and vendor.

3.5.4 Powder:

3.5.4.1 Mesh Designations: 60, 100, 140, 200, and 325.
(R)

3.5.4.2 Powder shall be supplied in accordance with the limits on particle size
(R) distribution shown in Table 4, unless some other distribution is specified. Tests shall be in accordance with ASTM B 214.

TABLE 4 - Particle Size Distribution

Mesh Designation	U.S. Standard Sieve
60	Through a No. 40 sieve - 100% Through a No. 60 sieve - 95% minimum Through a No. 325 sieve - 10% maximum
100	Through a No. 60 sieve - 100% Through a No. 100 sieve - 95% minimum Through a No. 325 sieve - 15% maximum
140C	On a No. 100 sieve - 0.5% maximum On a No. 140 sieve - 10% maximum Through a No. 325 sieve - 20% maximum
140F	On a No. 100 sieve - 0.5% maximum On a No. 140 sieve - 10% maximum Through a No. 325 sieve - 55% maximum
200	On a No. 140 sieve - 0.5% maximum On a No. 200 sieve - 10% maximum Through a No. 325 sieve - 65% maximum
325	On a No. 200 sieve - 0.5% maximum On a No. 325 sieve - 10% maximum Through a No. 325 sieve - 90% minimum

3.5.4.2.1 When a mesh designation is not specified, 140F mesh shall be supplied.
(R)

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: (R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for all technical requirements, other than shelf life of paste (3.3.3.1), are acceptance tests and shall be performed on each lot.
(R)

4.2.2 Periodic Tests: Tests for shelf life of paste (3.3.3.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
(R)

4.3 Sampling and Testing:
(R)

Shall be in accordance with the following:

4.3.1 Composition: One sample shall be taken from each furnace charge.
(R)

4.3.2 Properties Except Shelf Life of Paste: One sample from each lot.
(R)

4.3.3 A lot shall be all product, other than powder or paste, which has been tested and found to conform to Table 1, in the same temper and size, and presented for vendor's inspection at one time.

4.3.4 A lot of powder shall be a uniform blend of powder produced from one or more furnace charges, each meeting the requirements of Table 1, and presented for vendor's inspection at one time.

4.3.5 A lot of paste shall be that paste produced from a single lot of powder, combined with binder from the same manufacturing batch, and presented for vendor's inspection at one time.

4.4 Reports:
(R)

The vendor of the product shall furnish with each shipment a report showing the results of tests on each lot to determine conformance to the composition requirements and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, lot number or numbers, AMS 4779D, form, size, and quantity.

4.5 Resampling and Retesting:
(R)

Not applicable.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 The product shall be identified as agreed upon by purchaser and vendor.

5.1.2 Each exterior container or package shall be permanently and legibly marked with not less than the following information:

NICKEL ALLOY BRAZING FILLER METAL

AMS 4779D

LOT NUMBER _____

MANUFACTURER'S IDENTIFICATION _____

NOMINAL DIMENSIONS _____

WEIGHT _____

5.1.2.1 Each container and package of paste shall also be marked with the date of
(R) manufacture.