

BRAZING FILLER METAL, HIGH TEMPERATURE  
82Au - 18Ni  
1740°F (950°C) Solidus-Liquidus Temperature UNS P00820

1. SCOPE:

- 1.1 Form: This specification covers a gold-nickel alloy in the form of wire, rod, sheet, strip, foil, pig, powder, shot, and chips and a viscous mixture (paste) of powder in a suitable binder.
- 1.2 Application: Primarily for joining corrosion and heat resistant steels and alloys requiring corrosion and oxidation resistant joints with good strength up to 1300°F (705°C). This filler metal is normally used for brazing without flux, using a protective atmosphere.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2222 - Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate  
MAM 2222 - Tolerances, Metric, Copper and Copper Alloy Sheet, Strip, and Plate  
AMS 2224 - Tolerances, Copper and Copper Alloy Wire  
MAM 2224 - Tolerances, Metric, Copper and Copper Alloy Wire  
AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B214 - Sieve Analysis of Granular Metal Powders

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

## 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

## 2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

## 3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Gold	81.50	82.50
Nickel	17.50	18.50
Other Elements, total (3.1.2)	--	0.15

3.1.1 Determination not required for routine acceptance.

3.1.2 The requirements of 3.1 apply to paste after removal of the binder.  
Ø

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Wire: Cold drawn or cold rolled, as ordered, and annealed and pickled clean or bright annealed.

3.2.2 Rod: Cold drawn, cold rolled, or extruded, as ordered, and annealed and pickled clean or bright annealed.

3.2.3 Sheet, Strip, and Foil: Cold rolled, hard.  
Ø

3.2.4 Pig, Powder, Shot, and Chips: As fabricated.

3.2.5 Paste: Shall consist of 84 - 90% by volume powder in a suitable binder and, unless otherwise agreed upon by purchaser and vendor, shall not contain flux.  
Ø

3.3 Properties: Filler metal shall conform to the following requirements:

3.3.1 Color: Shall be as follows:

3.3.1.1 Wire, Rod, Sheet, Strip, and Pig: Gold to yellow-white.

3.3.1.2 Powder, Shot, and Chips: Nickel gray.

3.3.2 Flatness: When unrolled, strip and foil shall lie flat with no undue  
 ∅ tendency to recoil.

3.3.3 Paste:

3.3.3.1 Paste shall have a shelf life of not less than six months from date of  
 ∅ manufacture; not more than thorough mixing shall be required to restore  
 paste for use during that time.

3.3.3.2 Paste shall leave no undesirable residue when heated in a protective  
 ∅ atmosphere to 1000°F (540°C) or higher.

3.4 Quality: The product, as received by purchaser, shall be uniform in color,  
 ∅ quality, and condition and free from foreign materials and from  
 imperfections detrimental to its working qualities. Wire, rod, sheet,  
 strip, and foil shall be clean, sound, bright, and free from slivers,  
 splitting, ragged edges, damaged ends, and other injurious imperfections.  
 Pig, powder, shot, and chips shall have a metallic luster.

3.5 Sizes and Tolerances: The product shall be supplied in the following  
 standard sizes and to the tolerances shown, unless otherwise specified:

3.5.1 Wire and Rod:

3.5.1.1 Nominal Diameters:

<u>Inch</u>		<u>Millimetres</u>	
0.005	0.062	0.12	1.55
0.007	0.094	0.18	2.35
0.010	0.125	0.25	3.12
0.015	0.175	0.38	4.40
0.025	0.188	0.62	4.70
0.031	0.225	0.78	5.60
0.040	0.250	1.00	6.25
0.047		1.18	

3.5.1.2 Diameter Tolerances for Drawn Wire and Rod: AMS 2224 or MAM 2224 as  
 applicable to refractory alloys.

### 3.5.1.3 Diameter Tolerance for Rolled or Extruded Wire and Rod:

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inch	Tolerances, Inch	
	Plus and Minus	
	Rounds	Squares
0.031 to 0.062, incl	0.005	--
Over 0.062 to 0.125, incl	0.006	--
Over 0.125 to 0.188, incl	0.007	0.009
Over 0.188 to 0.250, incl	0.008	0.010

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Tolerances, Millimetre	
	Plus and Minus	
	Rounds	Squares
0.78 to 1.55, incl	0.12	--
Over 1.55 to 3.12, incl	0.15	--
Over 3.12 to 4.75, incl	0.18	0.22
Over 4.75 to 6.25, incl	0.20	0.25

### 3.5.2 Sheet, Strip, and Foil:

#### 3.5.2.1 Nominal Thicknesses:

<u>Inch</u>		<u>Millimetre</u>	
0.001	0.006	0.02	0.15
0.0015	0.008	0.038	0.20
0.002	0.010	0.05	0.25
0.003	0.014	0.08	0.35
0.004	0.020	0.10	0.50
0.005	0.030	0.12	0.75

#### 3.5.2.2 Tolerances:

3.5.2.2.1 Thickness: Nominal thicknesses under 0.002 in. (0.05 mm) shall have a tolerance of  $\pm 0.0002$  in. ( $\pm 5 \mu\text{m}$ ); nominal thicknesses 0.002 in. (0.05 mm) and over shall have tolerances conforming to AMS 2222 as applicable to refractory alloys.

3.5.2.2.2 Width of Individual Rolls: Nominal widths under 6 in. (150 mm) shall vary not more than  $\pm 0.010$  in. ( $\pm 0.25$  mm) from the width ordered. Nominal widths 6 in. (150 mm) and over shall vary not more than  $\pm 0.015$  in. ( $\pm 0.38$  mm) from the width ordered.

3.5.2.2.3 Length in Individual Roll: Shall not be limited except that no roll shall weigh more than 75 lb (35 kg).

3.5.3 Powder:

3.5.3.1 Nominal Sizes: -60, -100, -200, and -325.

3.5.3.2 Tolerances: Nominal sizes shown in 3.5.3.1 shall be supplied in accordance with the following limit on particle size distribution, tested in accordance with ASTM B214:

$\phi$	Nominal Size	Not Less Than 95% Through U.S. Standard or Tyler Sieve Number
	-60	60
	-100	100
	-200	200
	-325	325

3.5.3.2.1 Control of fines shall be as specified by purchaser.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Composition: One sample from each lot.

4.3.2 Properties: One sample from each lot.

4.3.3 Other Technical Requirements: As agreed upon by purchaser and vendor.

# AMS 4787B

4.3.4 A lot shall be all product, other than powder or paste, which has been tested and found to conform to 3.1 and in the same temper and size and presented for vendor's inspection at one time.

4.3.5 A lot of powder shall be a uniform blend of powder produced from one or more furnace charges and presented for vendor's inspection at one time.

4.3.6 A lot of paste shall be that produced from a single lot of powder combined with binder from the same manufacturing batch and presented for vendor's inspection at one time.

## 4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the composition requirements and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 4787B, form, size, and quantity from each lot.

4.4.2 When parts made of this filler metal or assemblies requiring use of this filler metal are supplied, the part or assembly manufacturer shall inspect each lot of filler metal to determine conformance to the technical requirements of this specification and shall furnish with each shipment three copies of a report stating that the filler metal conforms. This report shall include the purchase order number, AMS 4787B, part or assembly number, and quantity.

4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

## 5. PREPARATION FOR DELIVERY:

### 5.1 Identification:

5.1.1 The product shall be identified as agreed upon by purchaser and vendor.