

**AEROSPACE
MATERIAL
SPECIFICATION**



AMS 4816D

Issued	MAR 1955
Revised	APR 1987
Reaffirmed	APR 1992
Noncurrent	OCT 1998
Cancelled	OCT 2006

Superseding AMS 4816C

Bearings, Silver-Clad Steel Strip

RATIONALE

AMS 4816D places this specification in cancelled status.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of October, 2006. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been "CANCELLED".

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of ams4816d

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: custsvc@sae.org
SAE WEB ADDRESS: http://www.sae.org

1. SCOPE:**1.1 Form:**

This specification covers a low-alloy strip clad on one or both faces with silver in the form of bearing stock or finished bearings.

1.2 Application:

Primarily for shims, thrust washers, bushings, and bearings.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2350 Standards and Test Methods

AMS 2370 Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

AMS 2800 Identification, Finished Parts

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 378 Spectrograph Analysis of Silver by the Powder Technique

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

3.1.1 Basis Steel: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.11	0.17
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.040
Sulfur	--	0.040
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.15	0.25

3.1.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.1.2 Cladding: Shall be oxygen-free silver having a minimum fineness of 99.95%, determined by spectrographic methods in accordance with ASTM E378 or by other analytical methods agreed upon by purchaser and vendor.

3.2 Condition:

Shall be a composite material produced by bonding silver sheet to one or both faces of steel strip by a controlled combination of temperature and pressure and subsequently cold rolled to the specified thickness.

3.3 Properties:

Bearings shall conform to the following requirements, determined in accordance with ASTM A 370:

3.3.1 Hardness: The basis steel shall have hardness of 26 - 38 HRC, or equivalent.

3.3.2 Bending: Bearings, after being annealed in a suitable protective atmosphere, shall withstand, without cracking, free bending through an angle of 180 deg around a diameter equal to the nominal thickness of the bearing with axis of bend parallel to the direction of rolling and with the clad surface on the outside of the bend.

3.4 Quality:

Bearings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the bearings.

- 3.4.1 Cladding shall be firmly and continuously bonded to the steel backing, determined by a procedure agreed upon by purchaser and vendor.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of bearings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bearings conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling:

Shall be in accordance with the following; a lot shall be all bearings of one size and configuration made from a single heat of basis steel and a single heat of cladding processed in one continuous run and presented for vendor's inspection at one time:

- 4.3.1 Basis Steel: AMS 2370.

- 4.3.2 Cladding: Two samples from each heat of material melted at the same time.

- 4.3.3 Bearings or Bearing Stock: Three samples from each lot.

4.4 Reports:

- 4.4.1 The vendor of bearings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for hardness and bending of each lot. This report shall include the purchase order number, lot number, AMS 4816B, part number, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4816B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.