

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS4870B

Issued 5-1-44

Revised 6-1-51

ALUMINUM BRONZE CASTINGS, CENTRIFUGAL AND CHILL
85Cu - 11.2Al - 3.6Fe
As Cast

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for high strength.

3. COMPOSITION:

Copper	83.5	min
Aluminum	10.5	12.0
Iron	3.0	- 4.25
Manganese	0.50	max
Nickel	0.50	max
Total Named Elements	99.7	min

4. CONDITION: As cast.

5. TECHNICAL REQUIREMENTS:

5.1 Casting: A melt shall be the metal withdrawn from a batch furnace charge of 2000 pounds or less as melted for pouring castings.

5.2 Tensile Test coupons: Shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. Coupons shall be of such size that a standard (0.5-inch diameter at the reduced parallel section) tensile test specimen may be machined from each coupon, and shall be cast in permanent molds. Metal for the coupons shall be part of the melt which is used for the castings. The temperature of the metal during pouring of the coupons shall be not lower than the temperature of the metal during pouring of the castings.

5.3 Tensile Properties:

5.3.1 Tensile test specimens cut from the coupons shall conform to the following requirements:

Tensile Strength, psi	90,000	min
Yield Strength at 0.2% offset or at 0.0088 inch. in 2 in. extension under load, psi	36,000	min
Elongation, % in 4D	6	min

5.3.2 If castings are cut for examination, tensile properties of specimens cut from sections of castings 1 in. and under in thickness shall conform to the requirements of 5.3.1; specimens cut from sections of castings over 1 in. in thickness shall conform to the following requirements:

Tensile Strength, psi	72,000	min
Yield Strength at 0.2% offset or at 0.0077 inch in 2 in. extension under load, psi	28,000	min
Elongation, % in 4D	6	min

SAE Form 7C of the SAE Technical Board provides that: "All technical reports, including standards, approved and practices recommended are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committee will not investigate or consider suits which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."