

Titanium Alloy, Sheet and Strip  
79Ti - 15Mo - 3.0Al - 2.8Cb - 0.20Si

(Composition Similar to UNS R58210)

## RATIONALE

AMS 4897B results from a Five Year Review and update of this specification.

### 1. SCOPE

#### 1.1 Form

This specification covers a titanium alloy in the form of sheet and strip.

#### 1.2 Application

These products have been used typically for parts to be formed in the solution heat treated condition and subsequently precipitation heat treated to obtain high strength-to-weight ratio or stability up to 1100 °F (593 °C), but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS 2242	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS 2642	Structural Examination of Titanium Alloys, Etch-Anodize Inspection Procedure
AMS 2750	Pyrometry
AMS 2809	Identification, Titanium and Titanium Alloy Wrought Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
**SAE WEB ADDRESS:** <http://www.sae.org>

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 21	Elevated Temperature Tension Tests of Metallic Materials
ASTM E 112	Determining Average Grain Size
ASTM E 290	Bend Testing Material for Ductility
ASTM E 1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique
ASTM E 1447	Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
ASTM E 1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys
ASTM E 2371	Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E 1941, hydrogen in accordance with ASTM E 1447, oxygen and nitrogen in accordance with ASTM E 1409, and other elements in accordance with ASTM E 2371. Other analytical methods may be used if acceptable to the purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Molybdenum	14.0	16.0
Aluminum	2.5	3.5
Columbium (Niobium)	2.4	3.2
Silicon	0.15	0.25
Oxygen	0.11	0.15
Carbon	--	0.05
Iron	--	0.40
Nitrogen	--	0.05 (500 ppm)
Hydrogen (3.1.2)	--	0.015 (150 ppm)
Other Elements, each (3.1.1)	--	0.10
Other Elements, total (3.1.1)	--	0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Sample size when using ASTM E 1447 for hydrogen analysis may be as large as 0.35 gram.

3.1.3 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2249.

### 3.2 Melting Practice

Alloy shall be multiple melted. Melting cycle(s) prior to the final melting cycle shall be made using vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice(s). The final melting cycle shall be made under vacuum using vacuum arc remelting (VAR) practice with no alloy additions permitted.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

### 3.3 Condition

Rolled, solution heat treated, descaled, and leveled, having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish (See 8.2).

### 3.4 Solution Heat Treatment

Product shall be solution heat treated by heating to a temperature within the range 1500 to 1650 °F (816 to 899 °C), holding at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) degrees for 3 to 30 minutes, and cooling at a rate that will produce product meeting the requirements of 3.5 (See 8.3). Pyrometry shall be in accordance with AMS 2750.

### 3.5 Properties

The product shall conform to the following requirements:

#### 3.5.1 As Solution Heat Treated

##### 3.5.1.1 Tensile Properties

Shall be as shown in Table 2 for product 0.125 inch (3.18 mm) and under in nominal thickness, determined in accordance with ASTM E 8 with the rate of strain maintained at 0.003 to 0.007 inch/inch/minute (0.003 to 0.007 mm/mm/minute) through the yield strength and then increased so as to produce failure in approximately one additional minute. When a dispute occurs between purchaser and vendor over the yield strength values, a referee test shall be performed on a machine having a strain rate pacer using a rate of 0.005 inch/inch/minute (0.005 mm/mm/minute) through the yield strength and a minimum cross head speed of 0.10 inch per minute (0.04 mm/s) above the yield strength.

TABLE 2 - ROOM-TEMPERATURE TENSILE PROPERTIES

Property	Value
Tensile Strength	120 to 145 ksi (827 to 1000 MPa)
Yield Strength at 0.2% Offset	115 to 140 ksi (793 to 965 MPa)
Elongation in 2 Inches (50.8 mm), min	8%

##### 3.5.1.2 Bending

Product 0.125 inch (3.18 mm) and under in nominal thickness, shall have a test sample prepared nominally 0.750 inch (19.06 mm) in width, with its axis of bending parallel to the direction of rolling. The sample shall be bend tested in conformance with the guided bend test defined in ASTM E 290 through an angle of 105 degrees. The test fixture supports shall have a contact radius 0.010 minimum, and the plunger shall have a radius equal to the bend factor shown in Table 3 times the nominal thickness. Examination of the bent sample shall show no evidence of cracking when examined at 15 to 25X magnification.

TABLE 3 - BENDING PARAMETERS

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.070, incl	Up to 1.78, incl	3
Over 0.070 to 0.125, incl	Over 1.78 to 3.18, incl	3.5

##### 3.5.1.3 Surface Contamination

The product shall be free of any oxygen-rich layer, such as alpha case, or other surface contamination, determined by the bend test of 3.5.1.2, by microscopic examination at not lower than 400X magnification, or by other method acceptable to purchaser.

### 3.5.1.4 Microstructure

Shall be greater than 80% recrystallized beta grains (see 8.4.2), determined by optical examination at not lower than 100X magnification after decoration aging (See 8.4.3) a representative specimen at 900 °F (482 °C) for one to two hours. Silicides are an intrinsic feature of this product and, therefore, shall not be cause for rejection. Specimens shall be polished and etched as in AMS 2642 or by other suitable polishing and etching techniques.

### 3.5.1.5 Average Grain Size

Shall be as shown in Table 4, determined in accordance with ASTM E 112.

TABLE 4 - AVERAGE GRAIN SIZE

Nominal Thickness Inch	Nominal Thickness Millimeters	ASTM Grain Size Number
Up to 0.100, incl	Up to 2.54, incl	6
Over 0.100 to 0.125, incl	Over 2.54 to 3.18, incl	4

### 3.5.2 Response to Heat Treatment

Product 0.125 inch (3.18 mm) and under in nominal thickness shall meet the requirements of Table 5, Table 6, Table 7, and Table 8, after precipitation heat treatment as in 3.5.2.1 or 3.5.2.2 as applicable, determined with the rate of strain maintained at 0.003 to 0.007 inch/inch/minute (0.003 to 0.007 mm/mm/minute) through the yield strength and then increased so as to produce failure in approximately one additional minute. When a dispute occurs between purchaser and vendor over the yield strength values, a referee test shall be performed on a machine having a strain rate pacer, using a rate of 0.005 inch/inch/minute (0.005 mm/mm/minute) through the yield strength and a minimum cross head speed of 0.10 inch per minute (0.04 mm/s) above the yield strength.

3.5.2.1 Product shall conform to requirements shown in Table 5 and Table 6 after being heated to 1100 °F ± 10 (593 °C ± 6), held at heat for 8 hours ± 0.5, and cooled in air.

#### 3.5.2.1.1 At Room Temperature

Shall be as shown in Table 5, determined in accordance with ASTM E 8.

TABLE 5A - MINIMUM ROOM TEMPERATURE TENSILE PROPERTIES, INCH/POUND UNITS

Grain Direction	Ultimate Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation %
Longitudinal	144	136	5
Transverse	147	138	5

TABLE 5B - MINIMUM ROOM TEMPERATURE TENSILE PROPERTIES, SI UNITS

Grain Direction	Ultimate Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation %
Longitudinal	993	938	5
Transverse	1014	951	5

## 3.5.2.1.2 At 900 °F (482 °C)

Shall be as shown in Table 6, determined in accordance with ASTM E 21 on specimens heated to 900 °F ± 5 (482 °C ± 3), held at heat for 20 to 30 minutes before testing, and tested at 900 °F ± 5 (482 °C ± 3).

TABLE 6 - MINIMUM TENSILE PROPERTIES AT 900 °F (482 °C)

Property	Value
Tensile Strength	95 ksi (655 MPa)
Yield Strength at 0.2% Offset	75 ksi (517 MPa)
Elongation in 2 Inches (50.8 mm)	15%

3.5.2.2 Product shall conform to requirements shown in Table 7 and Table 8 after being heated to 1275 °F ± 10 (691 °C ± 6), held at heat for 8 hours ± 0.5, cooled in air, reheated to 1200 °F ± 10 (649 °C ± 6), held at heat for 8 hours ± 0.5, and cooled in air.

## 3.5.2.2.1 At Room Temperature

Shall be as shown in Table 7, determined in accordance with ASTM E 8.

TABLE 7A - MINIMUM ROOM TEMPERATURE TENSILE PROPERTIES, INCH/POUND UNITS

Grain Direction	Ultimate Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches %
Longitudinal	125	115	6
Transverse	125	115	5

TABLE 7B - MINIMUM ROOM TEMPERATURE TENSILE PROPERTIES, SI UNITS

Grain Direction	Ultimate Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm %
Longitudinal	862	793	6
Transverse	862	793	5

## 3.5.2.2.2 At 1100 °F (593 °C)

Shall be as shown in Table 8, determined in accordance with ASTM E 21 on specimens heated to 1100 °F ± 5 (593 °C ± 3), held at heat for 20 to 30 minutes before testing, and tested at 1100 °F ± 5 (593 °C ± 3). Properties shown apply to both the longitudinal and transverse grain orientation.

TABLE 8 - MINIMUM TENSILE PROPERTIES AT 1100 °F (593 °C)

Property	Value
Tensile Strength	60 ksi (414 MPa)
Yield Strength at 0.2% Offset	49.0 ksi (338 MPa)
Elongation in 2 Inches (50.8 mm)	17%

## 3.6 Quality

3.6.1 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from "oil cans" (See 8.4.1) of depth in excess of the flatness tolerances, ripples, and foreign materials and from imperfections detrimental to usage of the product.

## 3.7 Tolerances

Shall conform to all applicable requirements of AMS 2242.

#### 4. QUALITY ASSURANCE PROVISIONS

##### 4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

##### 4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

##### 4.3 Sampling and Testing

Shall be in accordance with the following; a lot shall be all product of the same nominal size from the same heat processed at the same time and in the same heat treatment batch.

###### 4.3.1 Composition

One sample from each heat, except that for hydrogen determinations one sample from each lot obtained after thermal and chemical processing is completed.

###### 4.3.2 Tensile Properties, Bending, Grain Size, Surface Contamination, and Microstructure

One or more samples from each lot for each requirement.

4.3.2.1 Specimens for tensile tests of widths 9 inches (229 mm) and over shall be taken and tested in both the longitudinal and transverse direction; for widths under 9 inches (229 mm), specimens shall be taken in the longitudinal direction.

#### 4.4 Reports

##### 4.4.1 Raw Material

The vendor shall provide a copy of the original material manufacturer's report (material certification) including: producer name, product form, mill produced size, and country where the metal was melted (i.e., final melt in the case of metal processed by multiple melting operations). The vendor of the product shall furnish with each shipment a report showing the results of tests for composition of each heat and for hydrogen content, room temperature tensile properties, bending, average grain size, surface contamination, and room and elevated temperature tensile properties after aging of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 4897B, product form, size, and quantity.

##### 4.4.2 Fabricated Parts

A copy of the original manufacturer's report (material certification) shall be provided by the vendor to the purchaser when the purchase order specifies AMS 4897.

##### 4.5 Resampling and Retesting

If any specimen used in the above tests fails to meet specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet specified requirements shall be cause for rejection of the product represented. Results of all tests shall be reported.