



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4898™</b>	<b>REV. E</b>
	Issued 1996-09 Revised 2018-08	
Superseding AMS4898D		
Titanium Alloy, Sheet 6Al - 2Sn - 2Zr - 2Mo - 2Cr - 0.15Si Annealed (Composition similar to UNS R56222)		

### RATIONALE

AMS4898E results from a Five-Year Review and update of this specification that adds ASTM E539 and ASTM E2994 (3.1), check analysis (3.1.2), provision for continuous heat treating (3.3.1.2), AS6279 (3.7), and prohibits unauthorized exceptions (3.8) and revises the report paragraph (4.4.2) and identification (5.1).

#### 1. SCOPE

##### 1.1 Form

This specification covers a titanium alloy in the form of sheet in nominal thicknesses 0.016 through 0.1874 inch (0.41 through 4.760 mm).

##### 1.2 Application

This sheet has been used typically for parts requiring high strength, toughness, and fatigue strength up to 750 °F (399 °C), but usage is not limited to such applications. The product can be superplastically formed above 1500 °F (816 °C) and it can be aged after air cooling from the solution treatment or super-plastic forming temperature to increase the strength.

1.2.1 Certain processing procedures and service conditions may cause this sheet to become subject to stress-corrosion cracking; ARP982 recommends practices to minimize such conditions.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2018 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this Technical Report, please visit**  
<http://standards.sae.org/AMS4898E>

## 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org)

AMS2242	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS2368	Sampling and Testing of Wrought Titanium Raw Material, Except Forgings and Forging Stock
AMS2750	Pyrometry
AMS2809	Identification, Titanium and Titanium Alloy Wrought Products
ARP982	Minimizing Stress-Corrosion Cracking in Wrought Titanium Alloy Products
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications
AS4194	Sheet and Strip Surface Finish Nomenclature
AS6279	Standard Practice for Production, Distribution, and Procurement of Metal Stock

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org)

ASTM A480/480M	General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E290	Bend Testing Material for Ductility
ASTM E539	Analysis of Titanium Alloys by X-Ray Fluorescence Spectrometry
ASTM E1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
ASTM E1447	Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
ASTM E1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
ASTM E2371	Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Atomic Emission Plasma Spectrometry
ASTM E2994	Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E1941, hydrogen in accordance with ASTM E1447, oxygen and nitrogen in accordance with ASTM E1409, and other elements in accordance with ASTM E539, ASTM E2371, or ASTM E2994. Other analytical methods may be used if acceptable to the purchaser.

**Table 1 - Composition**

Element	Min	Max
Aluminum	5.25	6.25
Tin	1.75	2.25
Zirconium	1.75	2.25
Molybdenum	1.75	2.25
Chromium	1.75	2.25
Silicon	0.10	0.20
Iron	--	0.15
Oxygen	--	0.15
Carbon	--	0.08
Nitrogen	--	0.05 (500 ppm)
Hydrogen	--	0.015 (150 ppm)
Other Elements, each (3.1.1)		0.10
Other Elements, total (3.1.1)		0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet applicable requirements of AMS2249.

3.2 Melting Practice

Alloy shall be multiple melted. The first melt shall be made by vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice. The subsequent melt or melts shall be made using vacuum arc remelting (VAR) practice. Alloy additions are not permitted in the final vacuum arc remelting (VAR) melt.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

Hot rolled, annealed, ground, and pickled. Surface appearance shall be comparable to a commercial corrosion-resistant steel No. 2D finish (see 8.4).

3.3.1 Annealing

The product shall be annealed as follows, pyrometry shall be in accordance with AMS2750.

3.3.1.1 Heat to a temperature within the range 1300 to 1650 °F (704 to 899 °C), hold at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) for a time commensurate with product thickness and the heating equipment and procedure used, and cool to room temperature at a rate equivalent to an air cool or faster.

3.3.1.2 Continuous Anneal of Sheet and Strip

When continuous annealing is used, process parameters (e.g., furnace temperature set points, heat input, travel rate, etc.) for continuous heat treating lines shall be established by the material producer and validated by testing of product to requirements of 3.4.

3.4 Properties

The product shall conform to the following requirements, determined in accordance with AMS2368, except tensile testing shall be determined in accordance with 3.4.1.1 and bending shall be determined in accordance with 3.4.1.2.

## 3.4.1 As Annealed

## 3.4.1.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E8/E8M with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of  $\pm 0.002$  in/in/min (0.002 mm/mm/min) through the 0.2% offset yield strain. Tensile property requirements apply in both the longitudinal and transverse directions.

**Table 2****Table 2A - Minimum tensile properties, inch/pound units**

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.016 to 0.025, incl	155	150	5
Over 0.025 to 0.032, incl	155	150	6
Over 0.032 to 0.080, incl	155	150	7
Over 0.080 to 0.1874, incl	155	150	8

**Table 2B - Minimum tensile properties, SI units**

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.41 to 0.64, incl	1069	1034	5
Over 0.64 to 0.81, incl	1069	1034	6
Over 0.81 to 2.03, incl	1069	1034	7
Over 2.03 to 4.760, incl	1069	1034	8

## 3.4.1.2 Bending

Product 0.016 to 0.1874 inch (0.41 to 4.76 mm) and under in nominal thickness, shall have a test sample prepared nominally 0.750 inch (19.06 mm) in width, with its axis of bending parallel to the direction of rolling. The sample shall be bend tested in conformance with the guided bend test defined in ASTM E290 through an angle of 105 degrees. The test fixture supports shall have a contact radius 0.010 minimum, and the plunger shall have a radius equal to the bend factor shown in Table 3 times the nominal thickness. Examination of the bent sample shall not show evidence of cracking when examined at 15 to 25X magnification.

**Table 3 - Bending parameters**

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.016 to 0.070, incl	0.41 to 1.78, incl	4.5
Over 0.070 to 0.1874, incl	Over 1.78 to 4.760, incl	5

## 3.4.1.3 Average Grain Size

Sheet 0.016 to 0.125 inch (0.41 to 3.18 mm) and under in nominal thickness, shall have an average grain size of ASTM No. 10 or finer (see 8.5).

## 3.4.1.4 Microstructure

Shall be that structure resulting from processing within the alpha-beta phase field. Microstructure shall conform to 3.4.1.4.1 or 3.4.1.4.2.

## 3.4.1.4.1 Equiaxed and/or elongated primary alpha in a transformed beta matrix with no continuous network of alpha at prior beta grain boundaries.

3.4.1.4.2 Essentially complete field of equiaxed and/or elongated alpha with or without intergranular beta and with no continuous network of alpha at prior beta grain boundaries.

#### 3.4.1.5 Surface Contamination

Sheet shall be free of any oxygen-rich layer, such as alpha case, or other surface contamination.

#### 3.4.2 Response to Heat Treatment

When specified by purchaser, specimens from sheet, 0.016 to 0.1874 inch (0.41 to 4.760 mm), inclusive, in nominal thickness, shall meet the requirements shown in Table 4 after being solution heat treated by heating to a temperature within the range 1600 to 1700 °F (871 to 927 °C), holding at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) for 15 to 60 minutes, cooling to room temperature at a rate equivalent to an air cool or faster, followed by aging within the range of 900 to 1000 °F (482 to 538 °C), holding at the selected temperature within  $\pm 15$  °F ( $\pm 8$  °C) for 8 to 12 hours (see 8.2 and 8.3), and cooling to room temperature.

**Table 4 - Minimum tensile properties**

Property	Value
Tensile Strength	180 ksi (1241 MPa)
Yield Strength at 0.2% Offset	160 ksi (1103 MPa)
Elongation in 2 Inches (50.8 mm)	5% (3.4.2.1)

3.4.2.1 Elongation requirement applies only to sheet 0.032 inch (0.81 mm) and over in nominal thickness.

#### 3.5 Quality

Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from "oil canning" (see 8.6.1) of depth in excess of one-half of the flatness tolerances, ripples, foreign materials, and from imperfections detrimental to usage of the sheet.

#### 3.6 Tolerances

Shall conform to all applicable requirements of AMS2242 except the variation in flatness, unless otherwise specified, shall not exceed  $\frac{1}{2}$  of the standard flatness tolerance.

3.7 Production, distribution, and procurement of metal stock shall comply with AS6279. This requirement becomes effective January 1, 2020.

3.8 Any exceptions shall be authorized by purchaser and reported as in 4.4.2.

### 4. QUALITY ASSURANCE PROVISIONS

#### 4.1 Responsibility for Inspection

The producer of sheet shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

#### 4.2 Classification of Tests

##### 4.2.1 Acceptance Tests

Composition (3.1), surface appearance (3.3), tensile properties as annealed (3.4.1.1), bending (3.4.1.2), average grain size (3.4.1.3), microstructure (3.4.1.4), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.