



AEROSPACE MATERIAL SPECIFICATION	AMS4903™	REV. E
	Issued 2003-04 Revised 2024-12	
	Superseding AMS4903D	
Titanium Alloy Sheet, Strip, and Plate, 6Al - 4V, Solution Heat Treated (Composition similar to UNS R56400)		

RATIONALE

AMS4903E results from a Five-Year Review and update of this specification with changes to update standard language related to unauthorized exceptions (see 3.5.3 and 8.4), relocate Definitions (see 2.3) and information regarding statistical analysis of properties (see 3.5.4), add standard note regarding alpha case (see 8.3), and update Applicable Documents (see Section 2), need for specific property values and reporting (see 3.5.1.1.2 and 3.5.2.1.1), and Ordering Information (see 8.6).

1. SCOPE

1.1 Form

This specification covers a titanium alloy in the form of sheet, strip, and plate up through 2.000 inches (50.80 mm), inclusive (see 8.6)

1.2 Application

This material has been used typically for parts to be formed or machined in the solution heat-treated condition and subsequently precipitation heat treated requiring high strength-to-weight ratio and stability up to 550 °F (288 °C) in the precipitation heat-treated condition, but usage is not limited to such applications.

1.3 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP982 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4903E/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2242	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium and Titanium Alloy Sheet, Strip, and Plate
AMS2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS2368	Sampling and Testing of Wrought Titanium Raw Material Except Forgings and Forging Stock
AMS2631	Ultrasonic Inspection, Titanium and Titanium Alloy Bar, Billet, and Plate
AMS2750	Pyrometry
AMS2809	Identification, Titanium and Titanium Alloy Wrought Products
ARP982	Minimizing Stress-Corrosion Cracking in Wrought Titanium Alloy Products
AS1814	Terminology for Titanium Microstructures
AS4194	Sheet and Strip Surface Finish Nomenclature
AS6279	Standard Practice for Production, Distribution, and Procurement of Metal Stock
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A480/480M	General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E290	Bend Testing of Material for Ductility
ASTM E384	Microindentation Hardness of Materials
ASTM E539	Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry
ASTM E1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion
ASTM E1447	Determination of Hydrogen in Reactive Metals and Reactive Metal Alloys by Inert Gas Fusion with Detection by Thermal Conductivity or Infrared Spectrometry
ASTM E1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis
ASTM E2371	Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)
ASTM E2994	Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry (Performance-Based Method)

2.3 Definitions

Terms used in AMS are defined in AS7766.

2.3.1 Terminology relating to titanium microstructures is presented in AS1814.

2.3.2 Commercial corrosion-resistant steel finishes are defined in ASTM A480/A480M and AS4194.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E1941, hydrogen in accordance with ASTM E1447, oxygen and nitrogen in accordance with ASTM E1409, and other elements in accordance with ASTM E539, ASTM E2371, or ASTM E2994. Other analytical methods may be used if acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Aluminum	5.50	6.75
Vanadium	3.50	4.50
Iron	--	0.30
Oxygen	--	0.20
Carbon	--	0.08
Nitrogen	--	0.05 (500 ppm)
Hydrogen	--	0.015 (150 ppm)
Yttrium (see 3.1.1)	--	0.005 (50 ppm)
Other Elements, each (see 3.1.1)	--	0.10
Other Elements, total (see 3.1.1)	--	0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the requirements of AMS2249.

3.2 Melting Practice

Alloy shall be multiple melted. The first melt shall be made by vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice. The subsequent melt or melts shall be made using vacuum arc remelting (VAR) practice. Alloy additions are not permitted in the final melt cycle.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Sheet and Strip

Hot rolled, with or without subsequent cold reduction, solution heat treated, descaled, and leveled, having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish (see 2.3.2).

3.3.2 Plate

Hot rolled, solution treated, and flattened, having a surface appearance comparable to a commercial corrosion-resistant steel No. 1 finish (see 2.3.2). Plate product shall be produced using standard industry practices designed strictly for the production of plate stock to the procured thickness. Bar, billet, forgings, or forging stock shall not be substituted for plate.

3.4 Solution Heat Treatment

The product shall be solution heat treated by heating to a temperature within the range 1650 to 1775 °F (899 to 968 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with product thickness and the heating equipment and procedure used, and cooling at a rate that will produce product meeting the requirements of 3.5. When vacuum furnace equipment is used, inert gas cooling may be applied. Pyrometry shall be in accordance with AMS2750.

3.5 Properties

The product shall conform to the following requirements:

3.5.1 As Solution Heat Treated

3.5.1.1 Tensile Properties

Shall be as specified in Table 2, determined in accordance with ASTM E8/E8M with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through the 0.2% offset yield strain.

Table 2A - Tensile properties, inch/pound units (see 3.5.4)

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %, min
Up to 0.032, excl	(see 3.5.1.1.1)	150 (max)	6 (see 3.5.1.1.2)
0.032 to 0.1875, excl	(see 3.5.1.1.1)	150 (max)	8

Table 2B - Tensile properties, SI units (see 3.5.4)

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %, min
Up to 0.81, excl	(see 3.5.1.1.1)	1034 (max)	6 (see 3.5.1.1.2)
0.81 to 4.76, excl	(see 3.5.1.1.1)	1034 (max)	8

3.5.1.1.1 Spread between tensile strength and yield strength shall be 15 ksi (103 MPa) minimum.

3.5.1.1.2 For thickness under 0.025 inch (0.64 mm), elongation values shall be as agreed upon between the purchaser and the producer and reported per 4.4.2.

3.5.1.2 Bending

Product under 0.1875 inch (4.76 mm) in nominal thickness shall have a test sample prepared nominally 0.750 inch (19.06 mm) in width with its axis of bending parallel to the direction of rolling. The sample shall be bend tested in conformance with the guided bend test defined in ASTM E290 through an angle of 105 degrees. The test fixture supports shall have a contact radius 0.010 inch (0.25 mm) minimum, and the plunger shall have a diameter equal to the bend factor shown in Table 3 times the nominal thickness. Examination of the bent sample shall not show evidence of cracking when examined at 15X to 25X magnification.

Table 3 - Bend factor

Nominal Thickness Inches	Nominal Thickness Millimeters	Bend Factor
Up to 0.070, incl	Up to 1.78, incl	9
Over 0.070 to 0.1875, excl	Over 1.78 to 4.762, excl	10

3.5.1.3 Microstructure

Shall be that structure resulting from processing within the alpha-beta phase field. Microstructure shall conform to 3.5.1.3.1 or 3.5.1.3.2 (see 2.3.1).

3.5.1.3.1 Equiaxed and/or elongated primary alpha in a transformed beta matrix with no continuous network of alpha at prior beta grain boundaries.

3.5.1.3.2 Primary alpha in a matrix of equiaxed alpha prime.

3.5.1.3.3 A microstructure showing a continuous network of alpha in prior beta grain boundaries is not acceptable.

3.5.1.4 Surface Contamination

The product shall be free of any oxygen-rich layer, such as alpha case (see 8.3), or other surface contamination, determined as in 3.5.1.4.1, 3.5.1.4.2, or 3.5.1.4.3 or other method acceptable to the purchaser (see 8.6).

3.5.1.4.1 The bend test of 3.5.1.2.

3.5.1.4.2 Microscopic examination at 400X minimum.

3.5.1.4.3 Hardness difference; a surface hardness more than 40 points higher than the subsurface hardness, determined in accordance with ASTM E384 on the Knoop scale using a 200-gram load, being evidence of unacceptable surface contamination.

3.5.2 Response to Heat Treatment

The product shall conform to the following requirements after being precipitation heat treated at 900 to 1275 °F ± 15 °F (482 to 691 °C ± 8 °C), holding at heat for 2 to 8 hours, and cooling in air. Precipitation heat treatment shall precede final machining of specimens. Pyrometry shall be in accordance with AMS2750.

3.5.2.1 Tensile Properties

Shall be as shown in Table 4, determined in accordance with ASTM E8/E8M, with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ±0.002 in/in/min (±0.002 mm/mm/min) through the 0.2% offset yield strain.

Table 4A - Minimum tensile properties, inch/pound units (see 3.5.4)

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.032, excl	160	145	3 (see 3.5.2.1.1)
0.032 to 0.049, excl	160	145	4
0.049 to 0.1875, excl	160	145	5
0.1875 to 0.750, excl	160	145	8
0.750 to 1.000, excl	150	140	6
1.000 to 2.000, incl	145	135	6

Table 4B - Minimum tensile properties, SI units (see 3.5.4)

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 0.81, excl	1103	1000	3 (see 3.5.2.1.1)
0.81 to 1.24, excl	1103	1000	4
1.24 to 4.76, excl	1103	1000	5
4.76 to 19.05, excl	1103	1000	8
19.05 to 25.40, excl	1034	965	6
25.40 to 50.80, incl	1000	931	6

3.5.2.1.1 For thickness under 0.025 inch (0.635 mm), elongation values shall be as agreed upon between the purchaser and the producer and reported per 4.4.2.

3.5.3 Mechanical property requirements for product outside the size range covered by 1.1 shall be agreed upon between the purchaser and producer and reported per 4.4.2 (see 8.6).

3.5.4 These mechanical properties have been taken from MIL-T-9046 and have not been substantiated by AMS statistical procedures.

3.6 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from "oil cans" of depth in excess of the flatness tolerances, ripples, foreign materials, and imperfections detrimental to usage of the product.

3.6.1 Ultrasonic Inspection

Plate 0.500 inch (12.70 mm) and over in nominal thickness shall meet Class A1 requirements of AMS2631.

3.7 Tolerances

In accordance with AMS2242.

3.8 Production, distribution, and procurement of metal stock shall comply with AS6279.

3.9 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.2.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1 Ultrasonic inspection of each plate when required by 3.6.1.