



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4932</b>	<b>REV. C</b>
	Issued 1990-04 Revised 2011-02 Reaffirmed 2015-03  Superseding AMS4932B	
Titanium Alloy Sheet 6Al - 4V Driver Sheet  (Composition similar to UNS R56400)		

### RATIONALE

AMS4932C has been reaffirmed to comply with the SAE five-year review policy.

#### 1. SCOPE

##### 1.1 Form

This specification covers a titanium alloy in the form of sheet.

##### 1.2 Application

This material has been used typically for driver sheet used as a consumable manufacturing aid in superplastic forming of titanium alloy sheet or plate components at 1600 to 1700 °F (871 to 927 °C), but usage is not limited to such applications.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
**SAE WEB ADDRESS:** <http://www.sae.org>

**SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS4932C>**

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM E 8 / E 8M	Tension Testing of Metallic Materials
ASTM E 539	X-Ray Emission Spectrometric Analysis of 6Al-4V Titanium Alloy
ASTM E 1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique
ASTM E 1447	Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
ASTM E 1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys
ASTM E 2371	Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E 1941, hydrogen in accordance with ASTM E 1447, oxygen and nitrogen in accordance with ASTM E 1409, and other elements in accordance with ASTM E 539 or ASTM E 2371. Other analytical methods may be used if acceptable to the purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Aluminum	5.50	6.75
Vanadium	3.50	4.50
Iron	--	0.30
Oxygen	--	0.20
Carbon	--	0.08
Nitrogen	--	0.05 (500 ppm)
Hydrogen (3.1.2)	--	0.02 (200 ppm)
Other Elements, total (3.1.1)	--	0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Sample size when using ASTM E 1447 for hydrogen determination may be as large as 0.35 gram.

3.1.3 Check Analysis

Composition variations shall meet the applicable requirements of AMS2249.

### 3.2 Melting Practice

Alloy shall be multiple melted. Melting cycle(s) prior to the final melting cycle shall be made using vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice(s). The final melting cycle shall be made under vacuum using vacuum arc remelting (VAR) practice with no alloy additions permitted.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be inert gas at a pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

### 3.3 Condition

Hot rolled, flattened, descaled, and, if required, pickled. Sheet may be supplied annealed or as-rolled, at vendor's option.

### 3.4 Properties

Shall conform to the following requirements:

#### 3.4.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E 8 / E 8M with the rate of strain set at 0.005 inch/inch/minute (0.005 mm/mm/minute) and maintained within a tolerance of  $\pm 0.002$  inch/inch/minute (0.002 mm/mm/minute) through the 0.2% offset yield strain.

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	134 ksi (924 MPa)
Yield Strength at 0.2% Offset	126 ksi (869 MPa)
Elongation in 2 Inches (50.8 mm)	5%

3.4.1.1 Tensile properties shall be determined in the transverse direction.

3.4.1.2 Sheet shall not be rejected on the basis of tensile properties if all other technical requirements are met.

#### 3.4.2 Microstructure

Shall be the structure resulting from processing within the alpha-beta phase field. Microstructure shall conform to 3.4.2.1 or 3.4.2.2.

3.4.2.1 Equiaxed and/or elongated primary alpha in a transformed beta matrix with no continuous network of alpha at prior beta grain boundaries.

3.4.2.2 Essentially complete field of equiaxed and/or elongated alpha with or without intergranular beta and no continuous network of alpha at prior grain boundaries.

#### 3.4.3 Surface Contamination

Sheet shall be free of any oxygen-rich layer (See 8.2), such as alpha case, or other surface contamination, determined by microscopic examination at 400X or other method acceptable to purchaser.

### 3.5 Quality

Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.6 Tolerances

Shall conform to the following:

#### 3.6.1 Length and Width

-0, +1/4 inch (-0, +6.4 mm).

#### 3.6.2 Thickness

-0, +0.013 inch (-0, +0.33 mm).

#### 3.6.3 Flatness

Shall not deviate more than 3% for sheet 36 inches (914 mm) and under in width, and not more than 5% for sheet over 36 inches (914 mm) in width.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

Composition (3.1), surface contamination (3.4.3), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

#### 4.2.2 Periodic Tests

Tensile properties (3.4.1) and microstructure (3.4.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling and Testing

Shall be in accordance with the following; a lot shall be all sheet from the same heat processed at the same time; a heat shall be the vacuum arc remelted ingots produced from alloy originally melted as a single furnace charge.

#### 4.3.1 For Acceptance Tests

##### 4.3.1.1 Composition

One sample from each heat, except that for hydrogen one sample from each lot obtained after thermal and chemical processing is completed.

##### 4.3.1.2 Surface Contamination and Tolerances

One sample from each lot.