

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 4952D

Issued JUL 1988
Revised OCT 2007

Superseding AMS 4952C

Titanium Alloy, Welding Wire
6Al - 2Sn - 4Zr - 2Mo

(Composition similar to UNS R54620)

RATIONALE

AMS 4952D results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a titanium alloy in the form of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-metal-arc and gas-tungsten-arc welding, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2249	Chemical Check Analysis Limits, Titanium and Titanium Alloys
AMS 2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS 2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS 2816	Identification, Welding Wire, Tab Marking Method
AMS 2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 1409	Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique
ASTM E 1447	Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method
ASTM E 1941	Determination of Carbon in Refractory and Reactive Metals and Their Alloys
ASTM E 2371	Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E 1941, hydrogen in accordance with ASTM E 1447, oxygen and nitrogen in accordance with ASTM E 1409, and other elements in accordance with ASTM E 2371. Other analytical methods may be used if acceptable to the purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Aluminum	5.50	6.50
Zirconium	3.60	4.40
Molybdenum	1.80	2.20
Tin	1.80	2.20
Oxygen (3.1.1.1), (3.1.3)	--	0.15
Silicon	--	0.10
Iron	--	0.10
Copper	--	0.10
Carbon (3.1.1.1)	--	0.04
Nitrogen (3.1.1.1)	--	0.0400 (400 ppm)
Hydrogen (3.1.1.1), (3.1.3)	--	0.0125 (125 ppm)
Yttrium (3.1.1.2)	--	0.0050 50 ppm)
Boron (3.1.1)	--	0.0030 30 ppm)
Other Elements, each (3.1.1.2)	--	0.10
Other Elements, total (3.1.1.2)	--	0.40
Titanium	remainder	

3.1.1 Except for carbon, oxygen, nitrogen, and hydrogen, chemical analysis of initial bar or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure conformance to composition requirements.

3.1.1.1 Carbon, oxygen, nitrogen, and hydrogen shall be determined on each lot of finished wire.

3.1.1.2 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2249.

3.1.3 When ASTM E 1409 or ASTM E 1447 is used, sample sizes larger than those recommended may be used.

3.2 Melting Practice

Alloy shall be multiple melted. Melting cycle(s) prior to the final melting cycle shall be made using vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practices. The final melting cycle shall be made under vacuum using vacuum arc remelting (VAR) practice with no alloy additions permitted.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

Cold drawn, bright finish, in a temper and with a surface finish that will provide proper feeding of the wire in machine-welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process that does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not treat the wire surface are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 In-process annealing, if required between cold rolling or drawing operations, shall be performed in a vacuum or in protective atmosphere to avoid surface oxidation and adsorption of other extraneous elements.

3.4.3 Butt welding is permissible provided both ends to be joined are either alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed within the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with the uniform, uninterrupted feeding of the wire in machine welding equipment.

3.4.4 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4.5 Residual elements and dissolved gasses picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld material, shall be removed.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire

Shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast

Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form a loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.5.2.2 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.6 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances

Wire shall be supplied in the standard sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter

Shall be as shown in Table 2.

TABLE 2A - SIZES AND DIAMETER TOLERANCES, INCH/POUND UNITS

Form	Nominal Diameter Inch	Tolerance	Tolerance
		Inch Plus	Inch Minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE 2B - SIZES AND DIAMETER TOLERANCES, SI UNITS

Form	Nominal Diameter Millimeters	Tolerance	Tolerance
		Millimeter Plus	Millimeter Minus
Cut Lengths	0.76, 1.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.7.2 Length

Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall vary not more than +0, -0.5 inch (+0, -13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1) and sizes and tolerances (3.7) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Weldability (3.5.1), cast (3.5.2.1), helix (3.5.2.2), and alloy verification (5.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.