

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4953

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 3-1-58
Revised

TITANIUM ALLOY WIRE
5Al - 2.5Sn

SUPERSEDED

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for inert gas shielded arc welding.
3. COMPOSITION: The product shall conform to the following:

		Check Analysis	
		Under	Over
Aluminum	4.00 - 6.00	0.40	0.40
Tin	2.00 - 3.00	0.15	0.15
Iron	0.50 max	--	0.15
Manganese	0.20 max	--	--
Oxygen, if determined	0.175 max	--	--
Carbon	0.10 max	--	0.04
Nitrogen	0.07 max	--	0.02
Hydrogen	0.015 max	--	0.002
Titanium	remainder		

4. CONDITION: Annealed and descaled.
5. TECHNICAL REQUIREMENTS:
 - 5.1 Tensile Properties:

Tensile Strength, psi	115,000 - 150,000
-----------------------	-------------------
 - 5.2 Weldability: Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds.
6. QUALITY: Material shall be multiple melted under vacuum using consumable electrode practice, unless otherwise permitted, and shall be uniform in quality and condition, clean, sound and free from foreign materials and from internal and external imperfections detrimental to its use for welding purposes.
7. TOLERANCES:
 - 7.1 Unless otherwise specified, straight lengths shall not vary more than $\pm 1/4$ in. from the length ordered.
 - 7.2 Unless otherwise specified, diameter of the wire shall not vary more than ± 0.002 in. from the size ordered.

Section 7C of the SAE Technical Board rules provides that: "All technical reports use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to conform to or be guided by any technical report in formulating and approving patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."