

Titanium Alloy Welding Wire
5Al - 2.5Sn

(Composition similar to UNS R54520)

RATIONALE

AMS 4953E results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a titanium alloy in the form of welding wire.

1.2 Application

This wire has been used typically for gas-metal-arc and gas-tungsten-arc welding, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

| | |
|----------|--|
| AMS 2249 | Chemical Check Analysis Limits, Titanium and Titanium Alloys |
| AMS 2813 | Packaging and Marking of Packages of Welding Wire, Standard Method |
| AMS 2814 | Packaging and Marking of Packages of Welding Wire, Premium Quality |
| AMS 2816 | Identification, Welding Wire, Tab Marking Method |
| AMS 2819 | Identification, Welding Wire, Direct Color Code System |
| ARP1876 | Weldability Test for Weld Filler Metal Wire |
| ARP4926 | Alloy Verification and Chemical Composition of Welding Wire |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

| | |
|-------------|--|
| ASTM E 1409 | Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique |
| ASTM E 1447 | Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method |
| ASTM E 1941 | Determination of Carbon in Refractory and Reactive Metals and Their Alloys |
| ASTM E 2371 | Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry |

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E 1941, hydrogen in accordance with ASTM E 1447, oxygen and nitrogen in accordance with ASTM E 1409, and other elements in accordance with ASTM E 2371. Other analytical methods may be used if acceptable to the purchaser.

TABLE 1 - COMPOSITION

| Element | min | max |
|---------------------------------|-----------|-----------------|
| Aluminum | 4.50 | 5.75 |
| Tin | 2.00 | 3.00 |
| Iron | -- | 0.50 |
| Oxygen (3.1.1.1) | -- | 0.175 |
| Carbon (3.1.1.1) | -- | 0.08 |
| Nitrogen (3.1.1.1) | -- | 0.05 |
| Hydrogen (3.1.1.1) | -- | 0.015 (150 ppm) |
| Yttrium (3.1.1.2) | -- | 0.005 (50 ppm) |
| Other Elements, each (3.1.1.2) | -- | 0.10 |
| Other Elements, total (3.1.1.2) | -- | 0.40 |
| Titanium | remainder | |

3.1.1 Except for carbon, oxygen, nitrogen, and hydrogen, chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.

3.1.1.1 Carbon, oxygen, nitrogen, and hydrogen shall also be determined on each lot of finished wire.

3.1.1.2 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2249.

3.1.3 Sample size when using ASTM E 1447 for hydrogen may be as large as 0.35 gram.

3.2 Melting Practice

Alloy should be multiple melted. Melting cycle(s) prior to the final melting cycle shall be made using vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice(s). The final melting cycle shall be made under vacuum using vacuum arc remelting (VAR) practice with no alloy additions permitted.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be inert gas at a pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

Cold drawn, bright finish, in a temper that will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process that does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not tear the wire surface are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 In-process annealing, if required between rolling or drawing operations, shall be performed in a vacuum or in a protective atmosphere to avoid surface oxidation and adsorption of other extraneous elements.

3.4.3 Butt welding is permissible provided both ends to be joined are either alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed within the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with the uniform, uninterrupted feeding of the wire in machine welding equipment.

3.4.4 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting, nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4.5 Residual elements and dissolved gasses picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire

Shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast

Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop, with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter,

3.5.2.2 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.6 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter

Shall be as shown in Table 2.

TABLE 2A - SIZES AND DIAMETER TOLERANCES, INCH/POUND UNITS

| Form | Nominal Diameter, Inch | Tolerance | |
|-------------|----------------------------|-----------|------------|
| | | Inch Plus | Inch Minus |
| Cut Lengths | 0.030, 0.045, 0.062, 0.078 | 0.002 | 0.002 |
| Cut Lengths | 0.094, 0.125, 0.156, 0.188 | 0.003 | 0.003 |
| Spools | 0.007, 0.010, 0.015 | 0.0005 | 0.0005 |
| Spools | 0.020, 0.030, 0.035, 0.045 | 0.001 | 0.002 |
| Spools | 0.062, 0.078, 0.094 | 0.002 | 0.002 |

TABLE 2B - SIZES AND DIAMETER TOLERANCES, SI UNITS

| Form | Nominal Diameter, Millimeters | Tolerance | |
|-------------|-------------------------------|-----------------|------------------|
| | | Millimeter Plus | Millimeter Minus |
| Cut Lengths | 0.76, 1.14, 1.57, 1.98 | 0.05 | 0.05 |
| Cut Lengths | 2.39, 3.18, 3.96, 4.78 | 0.08 | 0.08 |
| Spools | 0.18, 0.25, 0.38 | 0.013 | 0.013 |
| Spools | 0.51, 0.76, 0.89, 1.14 | 0.03 | 0.05 |
| Spools | 1.57, 1.98, 2.39 | 0.05 | 0.05 |

3.7.2 Length

Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (+0, -13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), alloy verification (5.2), and sizes and tolerances (3.7) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Weldability (3.5.1), cast (3.5.2.1) and helix (3.5.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.