



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4981A

Superseding AMS 4981

Issued 11-15-72

Revised 4-1-81

UNS R56260

TITANIUM ALLOY BARS AND FORGINGS
6.0Al - 2.0Sn - 4.0Zr - 6.0Mo
Solution and Precipitation Heat Treated

1. SCOPE:

1.1 Form: This specification covers a titanium alloy in the form of bars, wire, forgings, and forging stock.

1.2 Application: Primarily for parts requiring high strength up to 1000°F (540°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2249 - Chemical Check Analysis Limits, Titanium and Titanium Alloys

AMS 2350 - Standards and Test Methods

AMS 2375 - Control of Forgings Requiring First Article Approval

AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E21 - Elevated Temperature Tension Tests of Metallic Materials

ASTM E120 - Chemical Analysis of Titanium and Titanium Alloys

ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials

ASTM E292 - Conducting Time-for-Rupture Notch Tension Tests of Materials

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E120, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Aluminum	5.50	6.50
Zirconium	3.50	4.50
Tin	1.75	2.25
Molybdenum	5.50	6.50
Iron	--	0.15
Oxygen	--	0.15
Carbon	--	0.04
Nitrogen	--	0.04 (400 ppm)
Hydrogen (3.1.1)	--	0.0125 (125 ppm)
Yttrium	--	0.005 (50 ppm)
Residual Elements, each (3.1.2)	--	0.10
Residual Elements, total (3.1.2)	--	0.40
Titanium		remainder

3.1.1 Hydrogen content of forgings may be as high as 0.0150 (150 ppm).

3.1.2 Determination not required for routine acceptance.

3.1.3 Check Analysis: Composition variations shall meet the requirements of AMS 2249.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars: Hot finished, solution and precipitation heat treated, and descaled.

3.2.2 Wire: Cold drawn, solution and precipitation heat treated, and descaled.

3.2.3 Forgings: Solution and precipitation heat treated and descaled.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Heat Treatment: Bars and forgings with section thickness 0.50 in. (12.5 mm) and over shall be solution heat treated by heating in a suitable atmosphere to 1500° - 1675°F (815° - 915°C), holding at the selected temperature within ± 25°F (± 15°C) for not less than 1 hr, and cooling, at a rate equivalent to air cool or faster, and precipitation heat treated by heating to 1100°F ± 15 (595°C ± 8), holding at heat for 4 - 8 hr, and cooling in air. Heat treatment for section thicknesses under 0.50 in. (12.5 mm) shall be as agreed upon by purchaser and vendor.

3.3.1 Water-quenching from the solution heat treatment temperature is prohibited.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Bars, Wire, and Forgings:

3.4.1.1 Tensile Properties:

3.4.1.1.1 At Room Temperature: Shall be as specified in Table I, determined in accordance with ASTM E8 with the rate of strain maintained at 0.003 - 0.007 in. per in. per min. (0.003 - 0.007 (mm/mm)/min.) through the yield strength and then increased so as to produce failure in approximately one additional minute. When a dispute occurs between purchaser and vendor over the yield strength values, a referee test shall be performed on a machine having a strain rate pacer, using a rate of 0.005 in. per in. per min. (0.005 (mm/mm)/min.) through the yield strength and a minimum cross head speed of 0.10 in. (2.5 mm) per min. above the yield strength.

TABLE I

Form	Nominal Diameter or Distance Between Parallel Sides Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D		Reduction of area	
				%, min		%, min	
				L	T	L	T
Forgings	Up to 3.000, incl	170,000	160,000	10	8	20	15
Bars and Wire	Up to 2.500, incl	170,000	160,000	10	8	20	15
Bars	Over 2.500 to 3.000, incl	165,000	155,000	8	6	15	12
Bars and Forgings	Over 3.000 to 4.000, incl	160,000	150,000	8	6	15	12

TABLE I(SI)

Form	Nominal Diameter or Distance Between Parallel Sides Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D		Reduction of area	
				%, min		%, min	
				L	T	L	T
Forgings	Up to 75.00, incl	1172	1103	10	8	20	15
Bars and Wire	Up to 62.50, incl	1172	1103	10	8	20	15
Bars	Over 62.50 to 75.00, incl	1138	1069	8	6	15	12
Bars and Forgings	Over 75.00 to 100.00, incl	1103	1034	8	6	15	12

3.4.1.1.2 At 800°F (427°C): The product shall meet the requirements of Table II, determined in accordance with ASTM E21; specimens shall be heated to 800°F ± 5 (427°C ± 3), held at heat for 20 - 30 min. before testing, and tested at 800°F ± 5 (427°C ± 3) using strain rates as specified in 3.4.1.1.1.

TABLE II

Form	Nominal Diameter or Distance Between Parallel Sides Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min	Reduction of area %, min

TABLE II (SI)

Form	Nominal Diameter or Distance Between Parallel Sides Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D %, min	Reduction of area %, min

- 3.4.1.1.3 Tensile properties for bars over 4.000 in. (100.00 mm) in nominal diameter or distance between parallel sides and for forgings having any section with thickness over 4.000 in. (100.00 mm) at time of heat treatment shall be as agreed upon by purchaser and vendor.
- 3.4.1.1.4 Yield strength and reduction of area requirements do not apply to wire under 0.125 in. (3.18 mm) in nominal diameter.
- Ø 3.4.1.1.5 Tensile tests in the longitudinal direction of product over 2-1/2 in. (65 mm) in nominal diameter or section thickness are not required if tests are made in the transverse direction.
- 3.4.1.2 Hardness: Shall be 33 - 45 HRC or equivalent, determined in accordance with ASTM E18.
- 3.4.1.3 Room-Temperature Notched Stress-Rupture: The product shall meet the following requirements; tests shall be conducted in accordance with ASTM E292:
- 3.4.1.3.1 A test specimen machined to the dimensions shown in Fig. 1 and Table III, maintained at room temperature while a load sufficient to produce an initial axial stress of 190,000 psi (1310 MPa) is applied continuously shall not rupture in less than 5 hours. The initial stress may be less than 190,000 psi (1310 MPa) and increased to 190,000 psi (1310 MPa), based on the initial diameter at root of notch, in increments of 10,000 psi (69 MPa) at intervals of not less than 5 hours.
- 3.4.1.4 Creep Test at 800°F (427°C): The product shall meet the following requirements; tests shall be conducted in accordance with ASTM E139:
- 3.4.1.4.1 A smooth tensile test specimen shall be maintained at 800°F ± 5 (427°C ± 3) under continuously applied axial stress of 95,000 psi (655 MPa). Time to 0.2% plastic deformation shall be not less than 35 hours. If plastic deformation is less than 0.2% after 35 hr, the test may be discontinued; the amount of plastic deformation in 35 hr shall be reported. Gauge dimensions of specimen and technique used to measure creep shall be as agreed upon by purchaser and vendor.
- Ø 3.4.1.5 Microstructure: Shall be essentially that resulting from alpha-beta processing. The specific alpha plus beta microstructure shall not be cause for rejection unless standards have been agreed upon by purchaser and vendor. Microstructure of forgings shall be cause for rejection if any area of the forging exhibits an all-transformed beta microstructure.
- Ø 3.4.1.6 Surface Contamination: The product shall be free of any oxygen-enriched layer, such as alpha case, or other surface contamination, determined by microscopic examination.
- Ø 3.4.1.6.1 When permitted by purchaser, forgings to be machined all over may have an oxygen-rich layer provided such layer is removable within the machining allowance on the forgings.
- 3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the coupon shall conform to the requirements of 3.4.1.1.1 and 3.4.1.2. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1.1 and 3.4.1.2, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.5 Quality:
- Ø 3.5.1 Alloy shall be produced by multiple melting using consumable electrode practice. The final melting cycle shall be under vacuum.
- Ø 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.6 Tolerances: Unless otherwise specified, tolerances for bars and wire shall conform to all applicable requirements of AMS 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of the product.

4.2.1.2 Room-temperature tensile properties (3.4.1.1.1), hardness (3.4.1.2), microstructure (3.4.1.5), and surface contamination (3.4.1.6) of each lot of bars, wire, and forgings.

4.2.1.3 Tolerances (3.6) of bars and wire.

4.2.2 Periodic Tests: Tests to determine conformance to the following requirements are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Tensile properties at 800°F (427°C) (3.4.1.1.2), room-temperature notched stress-rupture properties (3.4.1.3), and creep properties at 800°F (427°C) (3.4.1.4) of bars, wire, and forgings.

4.2.2.2 Ability of forging stock to develop required properties (3.4.2).

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed on the first-article shipment of a forging to a purchaser, when a change in material or processing requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring agency, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following; a lot shall be all product of the same nominal size from the same heat processed at the same time:

4.3.1 For Acceptance Tests:

4.3.1.1 Composition: One sample from each heat except that for hydrogen determinations one sample from each lot obtained after thermal and chemical processing is completed.

4.3.1.2 Tensile Properties: At least one sample from bars and wire from each lot. The number, location, and orientation of samples from each lot of forgings shall be as agreed upon by purchaser and vendor.

4.3.1.3 Other Requirements: As agreed upon by purchaser and vendor.

4.3.2 For Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the hydrogen and tensile property requirements and, when performed, to the periodic test requirements, and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 4981A, specific solution heat treatment temperature used, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 4981A, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars and Wire:

5.1.1.1 Each straight bar over 0.500 in. (12.5 mm) in nominal diameter or least width of flat surface shall be marked in a row of characters recurring at intervals not greater than 3 ft (900 mm) with AMS 4981A, heat number, and manufacturer's identification. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid whose residue shall contain not more than traces of halogen-bearing compounds, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

5.1.1.2 Straight bars and wire 0.500 in. (12.5 mm) and under in nominal diameter or least width of flat surface shall be securely bundled and identified by a durable tag marked with the purchase order number, AMS 4981A, heat number, nominal size, and manufacturer's identification and attached to each bundle or shall be boxed and the box marked with the same information.

5.1.1.3 Coiled bars and wire shall be securely bundled and identified by a durable tag marked with the purchase order number, AMS 4981A, heat number, nominal size, and manufacturer's identification and attached to each coil or shall be boxed and the box marked with the same information.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Forging Stock: As agreed upon by purchaser and vendor.

5.2 Packaging:

- 5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Material not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.
8. NOTES:
- 8.1 Marginal Indicia: The phi (\emptyset) symbol is used to indicate technical changes from the previous issue of this specification.
- 8.2 For direct U.S. Military procurement, purchase documents should specify not less than the following:
- Title, number, and date of this specification
 - Form and size or part number of product desired
 - Quantity of product desired
 - Microstructure standards for acceptance (See 3.4.1.5)
 - Applicable level of packaging (See 5.2.2).

SAENORM.COM : Click to view the full PDF of AMS 4981A