

Steel, Welding Wire  
1.05Cr - 0.55Ni - 1.0Mo - 0.08V (0.26 - 0.32C)  
Vacuum Melted, Environment-Controlled Packaging  
(Composition similar to UNS K22925)

#### RATIONALE

AMS5027F results from a Five Year Review and update of this specification.

#### 1. SCOPE

##### 1.1 Form

This specification covers a low-alloy steel in the form of welding wire.

##### 1.2 Application

This wire has been used typically as filler metal for gas-tungsten-arc welding of heat-treatable steels of similar composition where the weld area is required to have strength comparable to that of the base metal, but usage is not limited to such applications.

##### 1.3 Classification

Wire shall be classified as follows:

- Type 1 - Bare Wire
- Type 2 - Copper Coated

1.3.1 Type 1 shall be supplied unless Type 2 is specified.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS5027F>**

## 2.1 SAE Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org)

AMS2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org)

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

## 3. TECHNICAL REQUIREMENTS

### 3.1 Wire Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon (3.1.1.1)	0.26	0.32
Manganese	0.60	0.90
Silicon	0.10	0.30
Phosphorus	--	0.010
Sulfur	--	0.010
Chromium	0.90	1.20
Nickel	0.40	0.70
Molybdenum	0.90	1.10
Vanadium	0.05	0.10
Copper (3.1.1.2)	--	0.35
Hydrogen (3.1.1.1)	--	0.0010 (10 ppm)
Oxygen (3.1.1.1)	--	0.0100 (100 ppm)
Nitrogen (3.1.1.1)	--	0.0050 (50 ppm)

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements.

3.1.1.1 Carbon, oxygen, nitrogen, and hydrogen shall also be periodically determined on finished wire.

3.1.1.2 For Type 2 (copper coated) wire, copper shall also be periodically determined on finished wire (See 4.2.2).

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259. No variation over maximum is permissible for oxygen, nitrogen, and hydrogen.

3.2 Melting Practice

Steel shall be vacuum induction melted or vacuum arc remelted, but remelting is not required.

3.3 Condition

Cold worked, bright finish, in a temper and with a surface finish that will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from bar descaled by a process that does not affect the composition of the wire. Surface irregularities inherent with a forming process that do not tear the wire surface are acceptable provided the wire conforms to the tolerance of 3.7

3.4.2 In process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or in protective atmosphere to avoid surface oxidation and adsorption of other extraneous materials.

3.4.3 Butt welding is permissible provided both ends to be joined are either alloy verified using a method or methods capable of distinguishing the alloy from all other alloys processed in the facility or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.4.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipments or the properties of the weld metal shall be removed by cleaning processes that will neither result in pitting nor cause gas adsorption by the wire or deposition of substances harmful to welding operations.

3.4.5 When Type 2 copper-coated wire is specified, the copper coating shall be clean, bright, and uniform in appearance. A maximum of four discontinuities in any 36-inch (914-mm) length is acceptable provided the exposed wire is clean and bright. The maximum allowable discontinuity size shall be 0.25 inch (6.35 mm) in length. The thickness of the copper coating shall not exceed 0.0005 inch (0.0127 mm) on the diameter.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchase and vendor. The referee method of ARP1876 may be used to resolve weldability disputes.

### 3.5.2 Spooled Wire

Shall conform to 3.5.2.1, 3.5.2.2 and 3.5.2.3.

#### 3.5.2.1 Winding

Filler metal in coils and on spools shall be wound so that kinks, waves, sharp bends, overlapping, or wedging are not encountered, leaving the filler metal free to unwind without restriction. The outside end of the electrode (the end where welding is to begin) shall be identified so it can be located readily and shall be fastened to avoid unwinding. The winding shall be level winding.

#### 3.5.2.2 Cast

Wire, wound on standard diameter spools as shown in Table 2 shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle (cast) within the limits shown in Table 2..

#### 3.5.2.3 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than shown in Table 2.

TABLE 2A - CAST AND HELIX REQUIREMENTS - INCH-POUND UNITS

Spool Diameter Inches	Wire Diameter Inches	Cast Diameter Inches		Helix Inches
		min	max	max
4	All	4	9	0.5
All other	≤0.030	12	n/a	1
	>0.030	15	n/a	1

TABLE 2B - CAST AND HELIX REQUIREMENTS - SI UNITS

Spool Diameter Millimeters	Wire Diameter Millimeters	Cast Millimeters		Helix Millimeters
		min	max	max
102	All	100	230	13
All other	≤0.8	305	n/a	25
	>0.8	380	n/a	25

### 3.6 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

### 3.7 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

#### 3.7.1 Diameter shall be as shown in Table 3.

TABLE 3A - SIZES AND DIAMETER TOLERANCES, INCH/POUND UNITS

Form	Standard Sizes Nominal Diameter Inch	Tolerance Inch plus and minus
Cut Lengths	0.030, 0.045	0.001
Cut Lengths	0.052, 0.062, 0.078, 0.094, 0.125, 0.156, 0.188	0.002
Spools	0.007, 0.010, 0.015	0.0005
Spools	0.020, 0.030, 0.035, 0.045	0.001
Spools	0.063, 0.078, 0.094	0.002

TABLE 3B - SIZES AND DIAMETER TOLERANCES, SI UNITS

Form	Standard Sizes Nominal Diameter Millimeters	Tolerance Millimeter plus and minus
Cut Lengths	0.76, 1.14	0.025
Cut Lengths	1.32, 1.57, 1.98, 2.39, 3.18, 3.96, 4.78	0.05
Spools	0.18, 0.25, 0.38	0.013
Spools	0.51, 0.76, 0.89, 1.14	0.025
Spools	1.57, 1.98, 2.39	0.05

### 3.7.2 Length

Cut lengths shall be furnished in 18, 27, or 36-inch (457, 686, or 914-mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (+0, -13 mm) from the length ordered.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

Composition (3.1.1), sizes and tolerances (3.7), and alloy verification (5.2) are acceptance tests and shall be performed on each heat or lot as applicable.

#### 4.2.2 Periodic Tests

Determination of carbon, hydrogen, oxygen, nitrogen on finished wire (3.1.1.1), determination of copper (if Type 2) on finished wire (3.1.1.2), weldability (3.5.1), cast (3.5.2.2), and helix (3.5.2.3) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling and Testing

Shall be in accordance with AMS2370 and as specified herein: