



AEROSPACE MATERIAL SPECIFICATION	AMS5029™	REV. F
	Issued 1969-05 Reaffirmed 2013-10 Revised 2024-09	
Superseding AMS5029E		
Steel, Welding Wire 0.78Cr - 1.8Ni - 0.35Mo - 0.20V (0.33 - 0.38C)(4335 Mod) Vacuum Melted, Environment Controlled Packaging (Composition similar to UNS K33517)		

RATIONALE

AMS5029F is the result of a Five-Year Review and update of the specification. The revision updates composition testing and reporting (see 3.1 and 3.1.3), adds producer country of origin to reports (see 4.4.1), and updates exception requirements (see 8.6).

1. SCOPE

1.1 Form

This specification covers a low-alloy steel in the form of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-tungsten-arc welding of basis metal of similar composition and quality requiring heat-treatment response in the weld joint approximating strength of the basis metal, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2024 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5029F/>

AMS2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A751 Chemical Analysis of Steel Products

ASTM D2650 Chemical Composition of Gases by Mass Spectrometry

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Composition shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751 or by other analytical methods acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Carbon (see 3.1.2)	0.33	0.38
Manganese	0.60	0.90
Silicon	--	0.25
Phosphorus	--	0.008
Sulfur	--	0.008
Chromium	0.65	0.90
Nickel	1.65	2.00
Molybdenum	0.30	0.40
Vanadium	0.17	0.23
Oxygen (see 3.1.2)	--	0.0025 (25 ppm)
Nitrogen (see 3.1.2)	--	0.0050 (50 ppm)
Hydrogen (see 3.1.2 and 3.1.2.1)	--	0.0010 (10 ppm)

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing, other than those analyses required to be done on the finished wire, is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to requirements.

3.1.2 Carbon, oxygen, nitrogen, and hydrogen shall be determined on finished wire (see 8.2).

3.1.2.1 The hydrogen content of the wire shall be determined at final diameter in accordance with ASTM D2650.

3.1.3 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.4 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259, except that no variation is permitted for oxygen, nitrogen, or hydrogen (see 8.2).

3.2 Melting Practice

Steel shall be multiple melted using vacuum consumable electrode practice in the remelt cycle or shall be vacuum induction melted.

3.3 Condition

Wire shall be cold worked, bright finish, and in a temper that will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process that does not affect the composition of the wire.

3.4.2 In-process annealing, if required, between cold rolling or drawing operations shall be performed in vacuum or in protective atmosphere to avoid surface oxidation and absorption of other extraneous elements.

3.4.3 Butt welding is permissible provided both ends to be joined are either alloy verified using a method or methods capable of distinguishing the alloy from all others processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.4.4 Drawing compounds, oxides, dirt, and oil shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4.5 Residual elements and dissolved gases picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal shall be removed.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire

Spooled wire shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast

Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.5.2.2 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.6 Quality

Wire, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances

Unless otherwise specified, wire shall be supplied in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter

Diameter shall be shown in Table 2.

Table 2A - Sizes and diameter tolerances, inch/pound units

Form	Nominal Diameter Inch	Tolerance, Inch Plus and Minus
Cut Lengths	0.030, 0.045	0.001
Cut Lengths	0.052, 0.062, 0.078, 0.094, 0.125, 0.156	0.002
Spools	0.007, 0.010, 0.015, 0.020	0.0005
Spools	0.030, 0.035, 0.045	0.001
Spools	0.062, 0.078, 0.094	0.002

Table 2B - Sizes and diameter tolerances, SI units

Form	Nominal Diameter Millimeters	Tolerance, Millimeters Plus and Minus
Cut Lengths	0.75, 1.15	0.025
Cut Lengths	1.32, 1.57, 1.98, 2.35, 3.10, 4.00	0.05
Spools	0.20, 0.25, 0.40, 0.50	0.013
Spools	0.75, 0.90, 1.15	0.025
Spools	1.55, 2.00, 2.35	0.05

3.7.2 Length

Cut lengths shall be furnished in 18-, 27-, or 36-inch (457-, 686-, or 914-mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (+0, -13 mm) from the length ordered.

3.8 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.2