

STEEL SHEET AND STRIP  
0.15 Carbon, maximum  
Deep Forming Grade

UNS G10100

1. SCOPE:

- 1.1 Form: This specification covers a carbon steel in the form of sheet and strip.
- 1.2 Application: Primarily for deep drawn and formed parts requiring a steel of high ductility.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2232 - Tolerances, Carbon Steel Sheet, Strip, and Plate
- MAM 2232 - Tolerances, Metric, Carbon Steel Sheet, Strip, and Plate
- AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any particular infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	--	0.15
Manganese	0.30 -	0.60
Phosphorus	--	0.035
Sulfur	--	0.040

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: Cold rolled.

3.3 Properties: The product shall conform to the following requirements; hardness and bend tests shall be performed in accordance with ASTM A370:

3.3.1 Hardness: Shall be not higher than specified in the following table, or equivalent:

<u>Nominal Thickness</u>		<u>Maximum Hardness</u>
<u>Inch</u>	<u>Millimetres</u>	
0.009 to 0.014, incl	0.23 to 0.36, incl	99 HV (1 kg Load)
Over 0.014 to 0.027, incl	Over 0.36 to 0.69, incl	79 HR15T
Over 0.027 to 0.059, incl	Over 0.69 to 1.50, incl	53 HR30T
Over 0.059 to 0.089, incl	Over 1.50 to 2.26, incl	88 HRF
Over 0.089	Over 2.26	55 HRB

3.3.2 Bending: The product shall withstand, without cracking or producing an "orange peel" surface, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2232 or MAM 2232.

#### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with AMS 2370.
- 4.4 Reports: The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 5040J, size, and quantity.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.

#### 5. PREPARATION FOR DELIVERY:

- 5.1 Identification: The product shall be identified as in 5.1.1 unless purchaser permits a method from 5.1.2.
- 5.1.1 Each sheet and strip shall be marked on one face, in the respective location indicated below, with AMS 5040J, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked.
- 5.1.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).
- 5.1.1.2 Flat Sheet and Flat Strip Over 6 Inches (152 mm) in Width: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.
- 5.1.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.1. When the product is wound on cores, the tag or label may be attached to the core.