



AEROSPACE MATERIAL SPECIFICATION	AMS5050™	REV. M
	Issued 1939-12 Reaffirmed 2015-12 Revised 2025-03 Superseding AMS5050L	
Steel Tubing, Seamless 0.15 Carbon Maximum (SAE 1010) Annealed (Composition similar to UNS G10100)		

RATIONALE

AMS5050M is the result of a Five-Year Review and update of the specification. The revision updates the title to include the SAE designation for the alloy, adds size limit (see 1.1), updates composition reporting (see 3.1.1), revises tensile test methods (see 3.3.1), and clarifies quality requirements (see 3.4).

1. SCOPE

1.1 Form

This specification covers a low-carbon steel in the form of seamless tubing up to 5.50 inches (139.7 mm), nominal OD, inclusive.

1.2 Application

This tubing has been used typically for oil lines and other parts requiring high-quality tubing suitable for severe forming and for welding or brazing, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2253 Tolerances, Carbon and Alloy Steel Tubing

AMS2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2025 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5050M/>

- AMS2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
- AMS2807 Identification, Carbon and Low-Alloy Steels, Corrosion- and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
- AS7766 Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A370 Mechanical Testing of Steel Products

ASTM A751 Chemical Analysis of Steel Products

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Composition shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751, or by other analytical methods acceptable to the purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.15
Manganese	0.30	0.60
Phosphorus	--	0.040
Sulfur	--	0.050

3.1.1 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Condition

Tubing shall be cold drawn and annealed.

3.2.1 Fabrication

Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to the last annealing. A light polish to improve surface appearance may be employed after annealing.

3.3 Properties

Tubing shall conform to the following requirements:

3.3.1 Tensile Properties

Tensile properties shall be as shown in Table 2, determined in accordance with ASTM A370.

Table 2 - Minimum tensile properties

Nominal OD Inches	Nominal OD Millimeters	Elongation in 2 Inches (50 mm)	Elongation in 2 Inches (50 mm)
		% Full Tube	% Strip
Up to 0.50, incl	Up to 12.7, incl	32	--
Over 0.50 to 5.50, incl	Over 12.7 to 139.7, incl	35	25

3.3.2 Flarability

Specimens as in 4.3.1 shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than shown in Table 3. After flaring, the inside surface of the tubing shall be smooth and shall show no evidence of conditions that might prevent the assembly of pressure-tight joints.

Table 3 - Minimum OD increase, percent

Nominal Wall Thickness Percent of OD	OD Increase Percent
Up to 7, incl	35
Over 7	45

3.4 Quality

Tubing, as received by the purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high-quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. OD surface imperfections such as handling marks, straightening marks, light mandrel and die marks, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

3.5 Tolerances

Tolerances shall conform to AMS2253.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.2.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

All technical requirements of this specification are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Sampling and testing shall be in accordance with AMS2370 and the following:

4.3.1 Specimens for flarability (see 3.3.2) tests shall be full tubes or sections cut from a tube. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs but not rounded. One or more specimens from each lot shall be tested.

4.4 Reports

4.4.1 The producer of the product shall furnish with each shipment a report showing the results of chemical composition for each heat and test results for tensile properties and flarability of each lot. The report shall state that the product conforms to the other technical requirements and shall include the purchase order number, heat and lot numbers, AMS5050M, size, and quantity.

4.4.2 When material produced to this specification is beyond the sizes allowed in the scope or tables, or other exceptions are taken to the technical requirements listed in Section 3, the report shall contain a statement "This material is certified as AMS5050M(EXC) because of the following exceptions:" and the specific exceptions shall be listed (see 5.2).

4.5 Resampling and Retesting

Resampling and retesting shall be in accordance with AMS2370.

5. PREPARATION FOR DELIVERY

5.1 Sizes

Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m), but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

5.2 Identification

Identification shall be in accordance with AMS2807. When technical exceptions are taken (see 4.4.2), the material shall be identified with AMS5050M(EXC).

5.3 Protective Treatment

Tubing shall be protected from corrosion prior to shipment.

5.4 Packaging

Tubing shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the tubing to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A producer shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Tubing not conforming to this specification, or to modifications authorized by the purchaser, will be subject to rejection.