



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5053D

Superseding AMS 5053C

Issued 6-1-42

Revised 6-15-75

STEEL TUBING, WELDED Low Carbon Annealed

1. SCOPE:

- 1.1 Type: This specification covers a low-carbon steel in the form of welded tubing.
- 1.2 Application: Primarily for parts requiring superior-quality welded tubing suitable for severe forming and for welding or brazing.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pennsylvania 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
- AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products
Except Forgings and Forging Stock

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

- ASTM E8 - Tension Testing of Metallic Materials
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.13
Manganese	--	0.60
Phosphorus	--	0.04
Sulfur	--	0.05

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standards or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: Normalized or annealed.

3.2.1 Fabrication:

3.2.1.1 Tubing shall be produced by electrical-resistance, shielded-metal arc, or gas welding the edges of \emptyset formed sheet or strip.

3.2.1.2 Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to the last annealing. A light polish to improve surface appearance may be employed after annealing.

3.3 Properties: Tubing shall conform to the following requirements; tensile testing shall be performed in \emptyset accordance with ASTM E8:

3.3.1 Tensile Properties: Shall be as follows:

Nominal OD		Elongation	
Inches	(Millimetres)	in 2 in. (50.8 mm), %	min
		Full Tube	Strip
Up to 0.50, incl	(Up to 12.7, incl)	32	---
Over 0.50 to 5.50, incl	(Over 12.7 to 139.7, incl)	35	25

3.3.2 Crushing Test: Test specimens shall withstand, without failure of the weld, crushing lengthwise under a gradually applied load until the cross-sectional dimension is increased in one zone by 20%, or until one complete fold is formed, or until the specimen is reduced in length to 2/3 of the original length.

3.3.3 Flarability: Tubing shall flare without formation of cracks or other visible defects. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg (1.29 rad) included angle to produce a flare having the following permanent percentage \emptyset OD increase. After flaring, the inside surface of the tubing shall be smooth and shall show no evidence of a bead that might prevent the assembly of pressure tight joints.

Nominal Wall Thickness	OD Increase
% of OD	%, min
Up to 7, incl	35
Over 7	45

3.4 Quality: Tubing shall be uniform in quality and condition and shall have a workmanlike finish conforming to the best practice for high-quality tubing. It shall be clean and free from heavy scale or oxide, burrs, \emptyset seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness. The removal of surface imperfections is not required.

3.4.1 Nondestructive Test: Each length of tubing shall be subjected to a nondestructive test by the tube manufacturer for the detection of injurious imperfections. The method of testing shall be capable of detecting all imperfections, interior and exterior, having a length greater than 1/16 in. (1.6 mm) and a total depth equivalent to half the nominal wall thickness of the tube.

3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, tubing will be acceptable in mill \emptyset lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2253.

3.6.1 The outside surface shall be free from welding flash and the maximum height of the inside flash shall not exceed 0.007 in. (0.18 mm).

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance or routine control tests.

4.3 Sampling: Shall be in accordance with AMS 2370 and the following:

4.3.1 At least one sample for crushing tests shall be selected from each 1000 ft (305 m) or less from each lot of tubing in the shipment. Test specimens shall have a length equal to approximately 1-1/2 times the nominal OD.

4.3.2 Specimens for flarability test may be cut from any portion of the tube or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs but not rounded.

4.4 Reports:

4.4.1 The vendor of the tubing shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and a statement that the tubing conforms to the other technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows:

5.1.1 Straight Tubes 0.029 In. (0.74 mm) and Over in Wall Thickness and 0.500 In. (12.70 mm) and Over in OD, Minor Axis, or Least Width of Flat Surface: Shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with AMS 5053D, manufacturer's identification, and nominal wall thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.