



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS 5060E

Superseding AMS 5060D

Issued 3-13-40

Revised 1-15-81

UNS G10150

STEEL BARS, FORGINGS, AND TUBING  
0.13 - 0.18C (SAE 1015)

### 1. SCOPE:

- 1.1 Form: This specification covers a low-carbon steel in the form of bars, forgings, mechanical tubing, and forging stock.
- 1.2 Application: Primarily for steel-backed bearings and carburized parts requiring a low maximum hardness of uncarburized surfaces after quenching the steel in water from a temperature above the transformation range of the steel.

### 2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publication: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

- AMS 2231 - Tolerances, Carbon Steel Bars
- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
- AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
- AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

#### 2.3.2 Military Standards:

- MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and prepared by SAE, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

### 3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.13	0.18
Manganese	0.30	0.60
Silicon	0.10	0.35
Phosphorus	--	0.040
Sulfur	--	0.050

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.
- 3.2 Condition: The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM A370:
- 3.2.1 Bars: Hot finished having hardness not higher than 229 HB or equivalent except that bars ordered cold finished may have hardness as high as 241 HB or equivalent.
- 3.2.2 Forgings: As ordered.
- 3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 241 HB or equivalent.
- 3.2.4 Forging Stock: As ordered by the forging manufacturer.
- 3.3 Properties: The product shall conform to the following requirements:
- 3.3.1 Response to Heat Treatment: Specimens with sections not over 0.250 in. (6.35 mm) in nominal thickness shall have surface hardness not higher than 30 HRC, determined in accordance with ASTM A370, after being quenched in water from a temperature above the transformation range.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of the following:
- 3.6.1 Bars: AMS 2231.
- 3.6.2 Mechanical Tubing: AMS 2253.

### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests of the product to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars and Mechanical Tubing: AMS 2370.

4.3.2 Forgings and Forging Stock: AMS 2372.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and stating that the product conforms to the response to heat treatment requirements of this specification. This report shall include the purchase order number, AMS 5060E, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5060E, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with the following:

4.5.1 Bars and Mechanical Tubing: AMS 2370.

4.5.2 Forgings and Forging Stock: AMS 2372.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars and Mechanical Tubing: In accordance with AMS 2806.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Forging Stock: As agreed upon by purchaser and vendor.

5.2 Protective Treatment: Bars and tubing ordered cold drawn, cold rolled, ground, turned, or polished shall be coated with a suitable corrosion-preventive compound prior to shipment.

5.3 Packaging:

5.3.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.3.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.3.1 will be acceptable if it meets the requirements of Level C.