

AEROSPACE MATERIAL SPECIFICATION

Issued SEP 1948
Reaffirmed SEP 2000
Revised MAR 2004
Superseding AMS 5061E

Steel, Low Carbon, Bars and Wire
0.08 to 0.20 C

(Composition similar to UNS K00802)

1. SCOPE:

1.1 Form:

This specification covers a low-carbon steel in the form of bars and wire 0.750 inch (19.05 mm) and under in nominal diameter or distance between parallel sides.

1.2 Application:

These products have been used typically for the manufacture of cold-headed threaded parts, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2231	Tolerances, Carbon Steel Bars
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.
Copyright 2004 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A 370 Mechanical Testing of Steel Products
 ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.08	0.20
Manganese	0.40	0.80
Phosphorus	--	0.040
Sulfur	--	0.050

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

Cold drawn.

3.3 Properties:

The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	70 ksi (483 MPa)
Elongation in 4D	10%

3.3.2 Hardness: Shall be 80 to 100 HRB, or equivalent (See 8.2). However, the product should not be rejected on the basis of hardness if the tensile properties of Table 2 are acceptable, determined on specimens taken from the same sample with nonconforming hardness or from another sample with similar nonconforming hardness.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2231.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2370.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition of each heat and for tensile properties and hardness of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5061F, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars and wire will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

5.2 Identification:

Shall be in accordance with AMS 2806.

5.3 Protective Treatment:

The product shall be protected from corrosion prior to shipment.

5.4 Packaging:

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

8.1 A change bar (|) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of a specification. An (R) symbol to the left of the document title indicates a complete revision of the specification, including technical revision. Change bars and (R) are not used in original publications, nor in specifications that contain editorial changes only.

8.2 Hardness conversion tables for metals are presented in ASTM E 140.

8.3 Terms used in AMS are clarified in ARP1917.

8.4 Dimensions and properties in inch/pound units are primary; dimensions and properties in SI units are shown as the approximate equivalents of the primary units and are presented only for information.

8.5 Purchase documents should specify not less than the following:

AMS 5061F
Form and size of product desired
Quantity of product desired.