



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5075C

Superseding AMS 5075B

Issued 3-1-42
Revised 12-15-74

STEEL TUBING, SEAMLESS 0.22 - 0.28C (SAE 1025)

1. SCOPE:

1.1 **Form:** This specification covers a carbon steel in the form of seamless tubing.

1.2 **Application:** Primarily for parts requiring a material of moderate ductility.

2. **APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 **SAE Publications:** Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pennsylvania 15096.

2.1.1 **Aerospace Material Specifications:**

- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
- AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

2.2 **ASTM Publications:** Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

- ASTM E8 - Tension Testing of Metallic Materials
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 **Government Publications:** Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 **Federal Standards:**

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

3.1 **Composition:** Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	0.22	0.28
Manganese	0.30	0.60
Silicon	0.10	0.35
Phosphorous	--	0.040
Sulfur	--	0.050

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.
- 3.2 Condition: Cold drawn, and stress relieved if necessary, having a uniform fine grain in all areas of the tubing.
- 3.3 Properties: Tubing shall conform to the following requirements; tensile testing shall be performed in accordance with ASTM E8:

3.3.1 Tensile Properties As Received: Shall be as follows:

Tensile Strength, min	55,000 psi (379 MPa)
Yield Strength at 0.2% Offset, min	36,000 psi (248 MPa)
Elongation in 2 in. (50.8 mm or 4D), min	22%

- 3.3.1.1 For each 2000 psi (13.8 MPa) in excess of 55,000 psi (379 MPa) tensile strength, a reduction in elongation of 1%, to a minimum elongation of 10%, is permissible.
- 3.3.2 Tensile Properties After Normalizing: The tubing shall be capable of meeting the tensile properties specified in 3.3.1 after being normalized by heating to $1625^{\circ}\text{F} \pm 10$ ($885^{\circ}\text{C} \pm 5.6$) and cooling in still air.
- 3.4 Quality: Tubing shall be uniform in quality and condition and shall have a workmanlike finish conforming to the best practice for high-quality tubing. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, lamination, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness. The removal of surface imperfections is not required.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the tubing conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1) condition (3.2), tensile properties as-received (3.3.1), quality (3.4), and tolerance (3.6) requirements are classified as acceptance or routine control tests.
- 4.2.2 Qualification Tests: Tests to determine conformance to tensile properties after normalizing (3.3.2) are classified as qualification or periodic control tests.
- 4.3 Sampling: Shall be in accordance with AMS 2370.

4.4 Reports:

- 4.4.1 The vendor of the tubing shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each size from each heat to determine conformance to the tensile property requirements. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

∅ 4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows:

5.1.1 Straight Tubes 0.029 In. (0.74 mm) and Over In Wall Thickness and 0.500 In. (12.70 mm) and Over In OD, Minor Axis, or Least Width of Flat Surface: Shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with AMS 5075C, manufacturer's identification, and nominal wall thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.

5.1.2 Straight Tubes Under 0.029 In. (0.74 mm) In Wall Thickness or Under 0.500 In. (12.70 mm) In OD, Minor Axis, or Least Width of Flat Surface: Shall be securely bundled and identified by a durable tag marked with the information of 5.1.1 and the nominal OD and attached to each bundle or shall be boxed and the box marked with the same information.

5.1.3 Coiled Tubing: Shall be securely bundled and identified by a durable tag marked with the purchase order number, AMS 5075C, nominal OD and wall thickness, and manufacturer's identification and attached to each coil or shall be boxed and the box marked with the same information.

5.2 Protective Treatment: Tubing shall be coated with a suitable corrosion-preventive compound prior to shipment.

5.3 Packaging: Tubing shall be prepared for shipment in accordance with commercial practice to assure carrier acceptance and safe transportation to the point of delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Tubing not conforming to this specification or to authorized modifications will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi (∅) symbol is used to indicate technical changes from the previous issue of this specification.