

SAE-AMS5085

ADOPTION NOTICE

SAE-AMS5085, "Sheet, Strip and Plate, 0.47 - 0.55C, Annealed," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, Attn: DISC-E, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:
 Army - AR
 Navy - AS
 Air Force - 99
 DLA - IS

Adopting Activity
 DLA - IS

SAENORM.COM : Click to view the full PDF of AMS5085

FSG 95GP

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

G-27-05

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 5085D

Issued 5-1-54
Revised 4-1-87

Superseding AMS 5085C

STEEL SHEET, STRIP, AND PLATE
0.47 - 0.55C (SAE 1050)
Annealed

UNS G10500

1. SCOPE:

- 1.1 Form: This specification covers a carbon steel in the form of sheet, strip, and plate.
- 1.2 Application: Primarily for stamped or formed parts which may subsequently be heat treated.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2232 - Tolerances, Carbon Steel Sheet, Strip, and Plate
MAM 2232 - Tolerances, Metric, Carbon Steel Sheet, Strip, and Plate
AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2350 - Standards and Test Methods
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products
ASTM E112 - Determining Average Grain Size
ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, \emptyset determined by wet chemical methods in accordance with ASTM E350 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.47	0.55
Manganese	0.60	0.90
Silicon	0.10	0.35
Phosphorus	-	0.040
Sulfur	-	0.050

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition: The product shall be supplied in the following condition; hardness shall be not higher than 85 HRB, or equivalent, determined in accordance with ASTM A370:

3.2.1 Sheet and Strip: Cold rolled and bright annealed; or hot rolled, annealed if necessary, and descaled.

3.2.2 Plate: Hot rolled, annealed if necessary, and descaled.

3.3 Properties: The product shall conform to the following requirements; hardness and bend tests shall be performed in accordance with ASTM A370:

3.3.1 Bending: The product shall withstand, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to twice the nominal thickness of the product with axis of bend parallel to the direction of rolling.

3.3.2 Decarburization:

3.3.2.1 Product Under 0.045 in. (1.15 mm) in Nominal Thickness: The method of test and the allowance shall be as agreed upon by purchaser and vendor.

3.3.2.2 Product 0.045 to 0.375 in. (1.15 to 9.50 mm) in Nominal Thickness:

3.3.2.2.1 Specimens: Shall be the full thickness of the product except that specimens from plate 0.250 in. (6.25 mm) and over in nominal thickness shall be slices approximately 0.250 in. (6.25 mm) thick cut parallel to and preserving one original surface of the plate. Recommended specimen size is 1 x 4 in. (25 x 100 mm).

3.3.2.2.2 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably, they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300°F (150°C). During heat treatment, specimens shall be protected by suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization. Protective plating, if used, shall then be removed from specimens of product 0.045 to 0.250 in. (1.15 to 6.25 mm), excl, in nominal thickness and a portion of the specimen shall be ground to a depth of 0.050 in. (1.25 mm) or one-half thickness, whichever is less. Specimens from product 0.250 to 0.375 in. (6.25 to 9.50 mm) excl, in nominal thickness shall be ground to remove 0.020 in. (0.50 mm) of metal from the original surface of the plate and a portion of the specimen shall be further ground to a depth of at least one-third the original thickness of the specimen. At least three Rockwell hardness readings shall be taken on each prepared step and each group of readings averaged.

3.3.2.2.3 Allowance:

3.3.2.2.3.1 Product 0.045 to 0.250 in. (1.15 to 6.25 mm), Excl, in Nominal Thickness: The product shall show no layer of complete decarburization, determined microscopically at a magnification not exceeding 100X. It shall also be free from partial decarburization to the extent that the difference in hardness between the original surface and the portion ground as in 3.3.2.2.2 shall be not greater than 2 units on the Rockwell "A" scale.

3.3.2.2.3.2 Product 0.250 to 0.375 in. (6.25 to 9.50 mm), Excl, in Nominal Thickness: Shall be free from decarburization to the extent that the difference in hardness between the two prepared steps shall be not greater than 3 units on the Rockwell "A" scale.

3.3.2.2.3.3 Product 0.375 in. (9.50 mm) and Over in Nominal Thickness: The total decarburization, determined microscopically at a magnification not exceeding 100X on the as-supplied plate, shall be not greater than shown in Table I:

TABLE I

Nominal Thickness Inches	Depth of Decarburization Inch
0.375 to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035
Over 2.000	As Agreed Upon

TABLE I (SI)

Nominal Thickness Millimetres	Depth of Decarburization Millimetre
9.50 to 12.50, incl	0.38
Over 12.50 to 25.00, incl	0.62
Over 25.00 to 50.00, incl	0.88
Over 50.00	As Agreed Upon

- 3.3.3 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E112.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2232 or MAM 2232.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's test and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with the AMS 2370.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5085D, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5085D, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.