

AMS 5110

ADOPTION NOTICE

AMS 5110, "Carbon Steel, Wire 0.75 -0.88C (SAE 1080) Spring Temper, Cold Drawn" was adopted on 17 January 1995 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Air Force, ASC/ENSI, Building 125, 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:
Army - MR
Navy - AS
Air Force - 11

Adopting Activity:
Air Force - 11
(Proj No. 9505-0292)

Review activities:
AF - 99

AMSC N/A FSC 9505

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AEROSPACE MATERIAL SPECIFICATION

Issued DEC 1939
Revised FEB 1995

Superseding AMS 5110F

Submitted for recognition as an American National Standard

CARBON STEEL, WIRE
0.75 - 0.88C (SAE 1080)
Spring Temper, Cold Drawn

UNS G10800

1. SCOPE:

1.1 Form:

This specification covers a carbon steel in the form of wire supplied as coils of wire or as finished springs.

1.2 Application:

This wire has been used typically for springs and other applications where spring temper is required, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2370 Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.75	0.88
Manganese	0.60	0.90
Silicon	0.10	0.30
Phosphorus	--	0.040
Sulfur	--	0.050

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Wire: Cold drawn.

3.2.2 Finished Springs: Stress relieved.

3.3 Heat Treatment:

Finished springs, after coiling, shall be stress relieved by heating in oil to 550 °F± 10 (288 °C ± 6), holding at heat for not less than one hour, and cooling in air.

3.4 Properties:

The product shall conform to the following requirements:

- 3.4.1 Tensile Properties at Room Temperature: Tensile properties of wire shall be as shown in Table 2, determined in accordance with ASTM A 370.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Diameter Inch	Tensile Strength ksi, min	Tensile Strength ksi, max
Up to 0.062, incl	300	--
Over 0.062 to 0.091, incl	285	335
Over 0.091 to 0.124, incl	265	315
Over 0.124 to 0.149, incl	255	295
Over 0.149 to 0.174, incl	240	280
Over 0.174 to 0.191, incl	225	265
Over 0.191 to 0.250, incl	200	250

TABLE 2B - Tensile Properties, SI

Nominal Diameter Millimeters	Tensile Strength MPa, min	Tensile Strength MPa, max
Up to 1.57, incl	2068	--
Over 1.57 to 2.31, incl	1965	2310
Over 2.31 to 3.15, incl	1827	2172
Over 3.15 to 3.78, incl	1758	2034
Over 3.78 to 4.42, incl	1655	1931
Over 4.42 to 4.85, incl	1551	1827
Over 4.85 to 6.35, incl	1379	1724

3.5 Quality:

Wire, before forming into springs, shall have a bright, smooth, cold-drawn finish and shall be free from imperfections such as seams, pits, nicks, scratches, and other imperfections detrimental to usage of the wire. A dull surface resulting from the use of a phosphate coating during drawing is acceptable.

3.6 Tolerances:

Wire shall be supplied to the tolerances shown in Table 3 and 3.6.1.

TABLE 3A - Diameter Tolerances, Inch/Pound Units

Nominal Diameter Inch	Tolerance, Inch Plus and Minus
Up to 0.026, incl	0.0003
Over 0.026 to 0.063, incl	0.0005
Over 0.063 to 0.150, incl	0.0010
Over 0.150	0.0015

TABLE 3B - Diameter Tolerances, SI Units

Nominal Diameter Millimeters	Tolerance, Millimeters Plus and Minus
Up to 0.66, incl	0.008
Over 0.66 to 1.60, incl	0.013
Over 1.60 to 3.81, incl	0.025
Over 3.81	0.038

3.6.1 Wire shall not be out-of-round by more than one-half the total permissible variation shown in Table 3.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing: (R)

Shall be in accordance with AMS 2370.

4.4 Reports:

The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties of each lot. This report shall include the purchase order number, lot number, AMS 5110G, size, and quantity.