

ALLOY STRIP

UNS N09902

49Fe - 5.3Cr - 42Ni - 2.5Ti - 0.55Al

Solution Heat Treated, Cold Rolled, 50% Reduction

1. SCOPE:

1.1 Form: This specification covers an iron-nickel alloy in the form of strip.

1.2 Application: Primarily for diaphragms, leaf springs, and helical springs, requiring a precipitation-hardenable alloy with a coefficient of modulus of elasticity of -20 to $+20 \times 10^{-6}$ per degree Fahrenheit from -50° to $+150^{\circ}$ F (-36 to $+36 \times 10^{-6}$ per degree Celsius from -46° to $+66^{\circ}$ C) after suitable heat treatment.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging, and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 5225C

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E112 - Estimating the Average Grain Size of Metals

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage.

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.06
Manganese	--	0.80
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	4.90 -	5.75
Nickel + Cobalt	41.00 -	43.50
Titanium	2.20 -	2.75
Aluminum	0.30 -	0.80
Chromium + (Titanium - 4 x Carbon)	7.10 -	8.10
Cobalt (3.1.1)	--	1.00
Iron		remainder

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: Solution heat treated by heating to $1750^{\circ}\text{F} + 25$ ($955^{\circ}\text{C} + 15$), holding at heat for 15 - 30 min., and cooling as required and cold rolled with approximately 50% reduction in thickness.

3.3 Properties: Strip shall conform to the following requirements:

3.3.1 As Solution Heat Treated and Cold Rolled:

3.3.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8; these requirements apply to strip 0.020 to 0.250 in. (0.50 to 6.25 mm), incl, in nominal thickness.

Tensile Strength	125,000 - 140,000 psi (860 - 965 MPa)
Elongation in 2 in. (50 mm), min	3%

3.3.1.1.1 Tensile property requirements for strip under 0.020 in. (0.50 mm) or over 0.250 in. (6.25 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.1.2 Hardness: Should be 24 - 32 HRC or equivalent, determined in accordance with ASTM E18, but strip shall not be rejected on the basis of hardness if the tensile property requirements of 3.3.1.1 are met.

3.3.1.3 Grain Size: Predominantly 5 or finer with occasional grains as large as \emptyset 3 permissible, determined in accordance with ASTM E112.

3.3.2 After Precipitation Heat Treatment: Strip 0.020 to 0.250 in. (0.50 to \emptyset 6.25 mm), incl, in nominal thickness shall conform to the following requirements after being precipitation heat treated by heating to $1300^{\circ}\text{F} + 15$ ($705^{\circ}\text{C} + 8$), holding at heat for 180 min. \pm 5, and cooling in air; properties of strip under 0.020 in. (0.50 mm) or over 0.250 in. (6.25 mm) in nominal thickness shall be as agreed upon by purchaser and vendor:

3.3.2.1 Tensile Properties: Shall be as follows, determined in accordance with \emptyset ASTM E8:

Tensile Strength, min	190,000 psi (1310 MPa)
Yield Strength at 0.2% Offset, Min	165,000 psi (1140 MPa)
Elongation in 2 in. (50 mm), min	5%

3.3.2.2 Hardness: Should be 39 - 46 HRC or equivalent, determined in accordance with ASTM E18, but strip shall not be rejected on the basis of hardness if the tensile property requirements of 3.3.2.1 are met.

3.4 Quality: Strip, as received by purchaser, shall be uniform in quality and \emptyset condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the strip.

AMS 5225C

3.5 Tolerances: Unless otherwise specified, the following tolerances shall apply:

3.5.1 Thickness:

TABLE I

Nominal Thickness (T) Inches	Thickness Tolerance, Inch Plus and Minus	
	Width Ranges, Inches	
	Up to 4.00, incl	Over 4.00 to 5.00, incl
Up to 0.015, incl	0.0005	0.0006
Over 0.015 to 0.025, incl	0.00075	0.0008
Over 0.025 to 0.040, incl	0.001	0.001
Over 0.040	0.025T	0.025T

TABLE I (SI)

Nominal Thickness (T) Millimetres	Thickness Tolerance, Millimetre Plus and Minus	
	Width Ranges, Millimetres	
	Up to 100.0, incl	Over 100 to 125.0, incl
Up to 0.38, incl	0.012	0.015
Over 0.38 to 0.62, incl	0.019	0.020
Over 0.62 to 1.00, incl	0.025	0.25
Over 1.00	0.025T	0.025T

3.5.1.1 When premium tolerances for thickness are specified, strip shall conform to Table II.

TABLE II

Nominal Thickness (T) Inches	Thickness Tolerance, Inch Plus and Minus	
	Width Ranges, Inches	
	Up to 4.00, incl	Over 4.00 to 5.00, incl
Up to 0.005, incl	0.0002	0.0003
Over 0.005 to 0.010, incl	0.0003	0.0004
Over 0.010 to 0.015, incl	0.0004	0.0005
Over 0.015 to 0.025, incl	0.0005	0.0005
Over 0.025	0.02T	0.02T

TABLE II (SI)

Nominal Thickness (T) Millimetres	Thickness Tolerance, Millimetre Plus and Minus	
	Width Ranges, Millimetres	
	Up to 100.0, incl	Over 100.0 to 125.0, incl
Up to 0.12, incl	0.005	0.008
Over 0.12 to 0.25, incl	0.008	0.010
Over 0.25 to 0.38, incl	0.010	0.012
Over 0.38 to 0.62, incl	0.012	0.012
Over 0.62	0.02T	0.02T

3.5.2 Width:

TABLE III

Nominal Width Inches	Width Tolerance, Inch Thickness Ranges, Inch			
	Up to 0.010, incl	Over 0.010 to 0.040, incl	Over 0.040 to 0.075, incl	Over 0.075
		+0.010 -0.000	+0.010 -0.000	+0.015 -0.000
Up to 3.00, incl	+0.010 -0.000	+0.010 -0.000	+0.015 -0.000	+0.015 -0.000
Over 3.00 to 4.00, incl	+0.010 -0.000	+0.012 -0.000	+0.015 -0.000	+0.015 -0.000
Over 4.00 to 5.00, incl	+0.010 -0.000	+0.015 -0.000	+0.015 -0.005	+0.015 -0.015

TABLE III (SI)

Nominal Width Millimetres	Width Tolerance, Millimetre Thickness Range, Millimetres			
	Up to 0.25, incl	Over 0.25 to 1.00, incl	Over 1.00 to 1.90, incl	Over 1.90
		+0.25 -0.00	+0.25 -0.00	+0.38 -0.00
Up to 75.0, incl	+0.25 -0.00	+0.25 -0.00	+0.38 -0.00	+0.38 -0.00
Over 75.0 to 100.0, incl	+0.25 -0.00	+0.30 -0.00	+0.38 -0.00	+0.38 -0.00
Over 100.0 to 125.0, incl	+0.25 -0.00	+0.38 -0.00	+0.38 -0.12	+0.38 -0.38