



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

AMS 5329B

Superseding AMS 5329A

Issued 7-15-63

Revised 5-15-73

STEEL CASTINGS, SAND
0.80Cr - 1.8Ni - 0.35Mo (0.28 - 0.36C) (SAE 4330 Modified)

1. SCOPE:

1.1 Form: This specification covers a low-alloy steel in the form of sand castings.

1.2 Application: Primarily for light-to-medium-section castings which require heat treatment to tensile strengths of 180,000 psi (1241 MPa) and higher.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2360 - Room Temperature Tensile Properties of Castings

AMS 2635 - Radiographic Inspection

AMS 2640 - Magnetic Particle Inspection

AMS 2645 - Fluorescent Penetrant Inspection

AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel,
Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

SAE Technical Board rules provide that: "All technical reports, including standards, approved practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

	min	max
Carbon	0.28	0.36
Manganese	0.60	1.00
Silicon	0.50	0.90
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.65	1.00
Nickel	1.65	2.00
Molybdenum	0.30	0.45
Copper	--	0.35

3.2 Condition: Annealed.

3.3 Castings: A melt shall be the metal poured from a single furnace charge.

3.4 Test Specimens:

3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.4.2 Tensile Test Specimens: Shall be attached to castings, if practicable, or shall be a standard keel blocks conforming to ASTM A370, unless purchaser permits use of cast-to-size specimens. Test specimens shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. Keel blocks shall be cast in molds made of suitable core sand, shall be poured directly after pouring the castings, and shall be kept in the mold until black. Metal for the test specimens shall be part of the melt which is used for the castings.

3.5 Annealing: Castings and representative test specimens shall be annealed by heating to 1550° F ± 25° (843.3° C ± 14°) in an atmosphere neutral to the specified carbon range, holding at heat for not less than 1 hr, and cooling as required.

3.6 Properties: Castings and representative test specimens shall conform to the following requirements as applicable; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.6.1 Castings As Annealed:

3.6.1.1 Hardness: Shall be not higher than 30 HRC or equivalent.

3.6.1.2 Carburization or Decarburization: The carbon content shall be within the limits of 3.1 throughout the casting except that within 0.020 in. (0.51 mm) of the surface or 10% of wall thickness, whichever is smaller, the carbon content may be lower than specified in 3.1.

3.6.2 After Hardening and Tempering: Tensile test specimens, produced in accordance with 3.4.2 and castings, annealed as in 3.5, hardened by heating to 1575° F ± 25° (857.2° C ± 14°), holding at heat for not less than 30 min., and quenching in oil, and double tempered by heating to 750° F ± 15° (398.9° C ± 8.3°), holding at heat for 2 hr ± 15 min., and cooling in air after each tempering operation, shall be capable of meeting the following requirements:

3.6.2.1 Tensile Properties of Test Specimens:

Tensile Strength, min	180,000 psi (1241 MPa)
Yield Strength at 0.2% Offset, min	160,000 psi (1103 MPa)
Elongation in 2 in. (50.8 mm) or 4D, min	5%

3.6.2.2 Properties of Castings:

3.6.2.2.1 Hardness: Shall be 40 - 45 HRC or equivalent.

3.6.2.2.2 Tensile Properties: When specified on the drawing or when agreed upon by purchaser and vendor, tensile test specimens conforming to ASTM A370 shall be machined from castings selected at random from the shipment. Size and location of such specimens and required properties shall be as shown on the drawing or as agreed upon by purchaser and vendor. Required properties may be defined as specified in AMS 2360.

3.7 Quality:

3.7.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.

3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subject to magnetic particle inspection in accordance with AMS 2640 and/or fluorescent penetrant inspection in accordance with AMS 2645.

3.7.4 Radiographic, magnetic particle, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or impregnating without written permission from purchaser.

3.7.6 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding provided the weld repair area has properties comparable to those of the parent metal. Repair welds shall be subjected to the same inspection procedures and acceptance standards required of the casting and the weld repair areas shall be suitably identified to facilitate inspection. The repair welding shall be performed prior to any heat treatment and nondestructive testing specified herein.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory tests as he deems necessary to assure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), hardness of castings as annealed (3.6.1.1), and carbon content (3.6.1.2) requirements are classified as acceptance or routine control tests.

4.2.2 Qualification Tests: Tests to determine conformance to properties after hardening and tempering (3.6.2) are classified as qualification or periodic control tests.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 and/or a casting from each melt.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

- 4.3.3 Three tensile test specimens in accordance with 3.4.2 from each melt, when requested.
- 4.3.4 When properties after hardening and tempering are required from specimens machined from castings, one casting from each melt.

4.4 Approval:

4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived.

4.4.2 Vendor shall establish for production of sample castings of each part number the control factors of processing which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in control factors of processing which could affect quality or properties of the castings, vendor shall submit for reapproval a detailed statement of the revised operations and, when requested, sample castings. No production castings incorporating the revised operations shall be shipped prior to receipt of re-approval.

4.4.2.1 Control factors for producing castings include, but are not limited to the following:

Type of furnace and its capacity
Size of furnace charge
Furnace atmosphere
Fluxing or deoxidation procedure
Pouring temperature (variation of $\pm 50^{\circ}\text{F}$ ($\pm 28^{\circ}\text{C}$) from established limits is permissible)
Solidification rate and subsequent cooling procedures
Cleaning operations
Methods of routine inspection

4.4.2.1.1 Any of the above control factors of processing considered proprietary by the vendor may be assigned a code designation. Each variation in such factors shall be assigned a modified code designation.

4.5 Reports:

4.5.1 The vendor of castings shall furnish with each shipment three copies of a report of results of tests for chemical composition of each melt represented and a statement that the castings conform to the other technical requirements of this specification. When properties of test specimens cut from castings are specified, the report shall include the results of tests to determine conformance to such requirements. This report shall include the purchase order number, melt number, material specification number and its revision letter, part number, and quantity from each melt.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of castings to determine conformance to the requirements of this specification, and shall include in the report a statement that the castings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the castings may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the castings represented and no additional testing shall be permitted. Results of all tests shall be reported.