



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS 5350F

Superseding AMS 5350E

Issued 12-1-47

Revised 4-1-81

UNS J91152

STEEL CASTINGS, INVESTMENT, CORROSION AND MODERATE HEAT RESISTANT  
12.5Cr

### 1. SCOPE:

1.1 Form: This specification covers a corrosion and moderate heat resistant steel in the form of investment castings.

1.2 Application: Primarily for small parts, such as compressor blades and vanes, for use up to 1000°F (540°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2635 - Radiographic Inspection

AMS 2640 - Magnetic Particle Inspection

AMS 2645 - Fluorescent Penetrant Inspection

AMS 2694 - Repair Welding of Aerospace Castings

AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E192 - Reference Radiographs of Investment Steel Castings for Aerospace Applications

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

#### 2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

### 3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.05	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	11.50	13.50
Nickel	--	0.50
Molybdenum	--	0.50
Aluminum	--	0.05
Copper	--	0.50
Tin	--	0.05

- 3.2 Condition: Hardened (air-cooled from the austenitizing temperature) and tempered, having hardness of 90 - 115 HRB or equivalent, determined in accordance with ASTM A370.
- 3.3 Casting: Castings shall be poured either from remelted metal from a master heat or directly from a master heat. In either case, metal for castings shall be qualified as in 3.4.
- 3.3.1 A master heat is refined metal of a single furnace charge or metal blended as in 3.3.2. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings.
- 3.3.2 Unless prohibited by purchaser, metal from two or more master heats may be blended provided that the composition of each master heat to be blended is within the limits of 3.1 and that the total weight of metal blended does not exceed 10,000 lb (4500 kg). Ingot and pig may be blended together, shot may be blended, but shot shall not be blended with ingot or pig. When two or more master heats are blended, the resultant blend shall be considered a master heat.
- 3.4 Master Heat Qualification: Each master heat shall be qualified by evaluation of chemical analysis and tensile test specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.
- 3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.
- 3.4.2 Tensile Test Specimens: Shall be cast from remelted metal from each master heat except when castings are poured directly from a master heat, in which case specimens shall also be poured directly from the master heat. Specimens shall be of standard proportions in accordance with ASTM A370 with 0.250 in. (6.25 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 in. (6.25 mm) diameter. Center gating may be used.

3.5 Properties: Castings and representative tensile test specimens produced in accordance with 3.4.2 shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.5.1 After Rehardening: Castings shall have hardness not lower than 35 HRC after being heated to 1750°F ± 10 (955°C ± 5), held at heat for 60 min. ± 5 per inch (25 mm) of maximum cross-section, and cooled in air.

3.5.2 After Rehardening and Tempering: Castings and separately-cast specimens shall have the following properties after being rehardened by heating to 1750°F ± 10 (955°C ± 5), holding at heat for 60 min. ± 5 per inch (25 mm) of maximum cross-section, and cooling in air and tempered by heating for 60 min. ± 5 at 1350°F ± 15 (730°C ± 8):

3.5.2.1 Tensile Properties:

Tensile Strength, min	95,000 psi (655 MPa)
Yield Strength at 0.2% Offset, min	75,000 psi (517 MPa)
Elongation in 4D, min	8%
Reduction of Area, min	20%

3.5.2.1.1 Specimens cut from castings are not required for routine acceptance; however, properties obtained from such specimens may be basis for acceptance of castings.

3.5.2.2 Hardness: Should be 94 - 100 HRB or equivalent but castings shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.6 Quality:

3.6.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

3.6.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted by purchaser.

3.6.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.6.3 When specified, castings shall be subjected to magnetic particle inspection in accordance with AMS 2640 and/or to fluorescent penetrant inspection in accordance with AMS 2645.

3.6.4 Radiographic, magnetic particle, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E192 may be used to define radiographic acceptance standards.

3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), condition (3.2), and hardness after rehardening (3.5.1) are classified as acceptance tests and shall be performed on each master heat.

4.2.2 Periodic Tests: Except as specified in 4.2.2.1, tests to determine conformance to requirements for tensile properties (3.5.2.1) and hardness (3.5.2.2) after rehardening and tempering are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.2.1 Tensile properties of specimens cut from castings shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a casting to a purchaser, when a change in material or processing requires re-approval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

#### 4.3 Sampling: Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 and/or a casting from each master heat.

4.3.2 Three tensile test specimens in accordance with 3.4.2 from each master heat, when requested.

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.4 One or more castings from each master heat when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile test specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each master heat.

#### 4.4 Approval:

4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived.