

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 5360 A

Issued 9-1-47  
Revised 12-1-51

STEEL CASTINGS, PRECISION INVESTMENT, CORROSION AND HEAT RESISTANT  
17Cr - 13Ni - 2Mo

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for small parts, such as stator vanes and nozzle diaphragm vanes for use at temperatures up to 1600 F. At high temperatures, strength of this steel is slightly higher than, and oxidation resistance is similar to, that of the 18-8 types.
3. COMPOSITION: Castings shall conform to the following:

Carbon	0.15 max
Manganese	2.00 max
Silicon	0.75 max
Phosphorus	0.04 max
Sulfur	0.03 max
Chromium	16.00 - 18.00
Nickel	12.00 - 14.00
Molybdenum	1.50 - 2.25
Copper	0.50 max

4. CASTING: Castings shall be poured either from remelted master heat metal or directly from a master heat. A master heat is previously refined metal of a single furnace charge, except when produced in the form of shot. A master heat in the form of shot shall be the uniformly blended product of one or more furnace charges, with total weight not exceeding 7000 lb. Gates, sprues, risers and rejected castings shall only be used in preparation of a master heat; they shall not be remelted directly, without refining, for pouring of castings.
5. CONDITION: As cast, unless otherwise specified.
6. QUALITY:
  - 6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Unless otherwise specified, metallic shot or grit shall not be used for final cleaning.
  - 6.2 When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.
  - 6.3 Unless otherwise specified, castings shall be produced under radiographic control.
  - 6.4 Inspection standards and procedures shall be as agreed upon by purchaser and vendor.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."