

**AEROSPACE
MATERIAL
SPECIFICATION**

Issued DEC1947
Revised APR 2001
Reaffirmed APR 2006

Superseding AMS 5362J

Steel, Corrosion and Heat Resistant, Investment Castings
19Cr - 12Ni - 1.0(Cb + Ta)
Solution Heat Treated

(Composition similar to UNS J92811)

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of investment castings.

1.2 Application:

These castings have been used typically for structural parts, where welding during fabrication may be required, for use up to 1500 °F (816 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248 Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2360 Room Temperature Tensile Properties of Castings
AMS 2694 Repair Welding of Aerospace Castings
AMS 2804 Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 1417	Liquid Penetrant Examination
ASTM E 1444	Magnetic Particle Examination
ASTM E 1742	Radiographic Examination

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2175	Castings, Classification and Inspection of
QQ-P-35	Passivation Treatments for Corrosion Resistant Steel

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Castings shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser (See 8.2.1 and 8.2.2).

TABLE 1 - Composition

	min	max
Carbon	--	0.12
Manganese	--	2.00
Silicon	--	1.50
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	18.00	19.50
Nickel	10.00	14.00
Columbium	10xC	1.50
Tantalum	--	0.05
Molybdenum	--	0.75
Copper	--	0.75
Iron	remainder	

- 3.1.1 Vendor may test for any element not otherwise listed in Table 1 and include this analysis in the report of 4.5. Limits of acceptability may be specified by purchaser (See 8.2.3).
- 3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.
- 3.2 Melting Practice:
- Castings and specimens shall be poured at casting vendor's facility either from a melt (See 8.2.4) of a master heat, or directly from a master heat (See 8.2.5).
- 3.2.1 Revert (gates, sprues, risers, and rejected castings) may be used only in the preparation of master heats; revert shall not be remelted directly, without refining, for pouring of castings. Melting of revert creates a new master heat.
- 3.2.2 Portions of two or more qualified master heats (See 3.4.2) may be melted together and poured into castings using a procedure authorized by purchaser (See 8.2.6).
- 3.2.3 If modifications, such as alloy additions or replenishments (See 8.2.10), are made by the vendor at remelt, vendor shall have a written procedure acceptable to purchaser which defines the controls, test, and traceability criteria for both castings and separately-cast specimens. Control factors of 4.4.2.2 shall apply.
- 3.3 Condition:
- Solution heat treated.
- 3.4 Test Specimens:
- Specimens shall be either separately-cast, integrally-cast (See 8.2.7), or machined from a casting, and shall conform to 3.2.
- 3.4.1 If specimens are separately-cast, vendor shall have a written procedure acceptable to purchaser. Control factors of 4.4.2.2 shall apply.
- 3.4.2 Each master heat shall be qualified by evaluation of chemical and tensile specimens.
- 3.4.2.1 If alloy additions or replenishments are made at remelt as in 3.2.3, the frequency of sampling and testing used by the vendor for qualification to 3.4.2 shall be acceptable to purchaser.
- 3.4.2.2 Tensile qualification tests of 3.4.2 are not required if these tests are conducted using integrally-cast specimens (4.3.3.2) or specimens machined from a casting (4.3.3.3).
- 3.4.3 Chemical Analysis Specimens: Shall be of any convenient size and shape.
- 3.4.4 Tensile Specimens: Shall be of standard proportions in accordance with ASTM E 8 or ASTM E 8M (See 8.4) with 0.250 inch (6.35 mm) diameter at the reduced parallel gage section.

- 3.4.4.1 Separately-cast and integrally-cast specimens may be either cast to size, or cast oversize and subsequently machined to 0.250 inch (6.35 mm) diameter.
- 3.4.4.2 When integrally-cast specimens or specimens machined from a casting are specified, specimen size and location shall be as agreed upon by purchaser and vendor. (See 8.2.8 and 8.5)

3.5 Heat Treatment:

Castings and representative tensile specimens shall be heat treated in accordance with 3.5.1.

3.5.1 Castings and Specimens:

- 3.5.1.1 Solution Heat Treatment: Heat to 1950 °F ± 50 (1066 °C ± 28), hold at heat for not less than 1 hour per inch (25 mm) of maximum section thickness but in no case less than 30 minutes, and cool at a rate equivalent to a still air cool or faster.
- 3.5.2 Tensile specimens used for master heat qualification may be heat treated separately from castings.

3.6 Properties:

Conformance shall be based upon testing separately-cast specimens unless purchaser specifies integrally-cast specimens or specimens machined from casting. Properties for specimens machined from casting shall be as specified by purchaser (See 8.5).

- 3.6.1 Room Temperature Tensile Properties: Shall be as specified in Table 2; determined in accordance with ASTM E 8 or ASTM E 8M (See 8.4). Properties other than those listed may be defined as specified in AMS 2360.
- 3.6.1.1 Separately-Cast and Integrally-Cast Specimens: Shall be as shown in Table 2.

TABLE 2 - Minimum Room Temperature Tensile Properties

Properties	Value
Tensile Strength	70.0 ksi (483 MPa)
Yield Strength at 0.2% Offset	30.0 ksi (207 MPa)
Elongation in 4D	30%

- 3.6.2 Embrittlement: Specimens cut from castings or representative specimens shall, after sensitizing, pass the intergranular corrosion test performed in accordance with ASTM A 262, Practice E.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings. Castings shall be free of cracks, laps, hot tears, and cold shuts, and free of scale and other process induced surface contamination which would obscure defects.

3.7.1.1 Unless otherwise specified, castings shall be sufficiently cleaned such that, after passivation by purchaser, the castings shall meet the corrosion test requirement of QQ-P-35.

3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of each casting part number until foundry manufacturing controls in accordance with 4.4.2 have been established. Additional radiography shall be conducted in accordance with the frequency of inspection specified by purchaser, or as necessary to ensure continued maintenance of internal quality.

3.7.2.1 Radiographic inspection shall be conducted in accordance with ASTM E 1742 or another method specified by purchaser.

3.7.3 When specified, additional nondestructive testing shall be performed as follows:

3.7.3.1 Fluorescent penetrant inspection in accordance with ASTM E 1417 or another method specified by purchaser.

3.7.3.2 Magnetic particle inspection in accordance with ASTM E 1444 or another method specified by purchaser.

3.7.4 Acceptance standards for radiographic, fluorescent penetrant, magnetic particle, visual, and other inspection methods shall be agreed upon by purchaser and vendor (See 8.2.8). MIL-STD-2175 may be used to specify acceptance standards (casting grade) and frequency of inspection (casting class).

3.7.4.1 When acceptance standards are not specified, Grade C of MIL-STD-2175 as applicable to steel castings shall apply for each applicable method of inspection.

3.7.5 Castings shall not be peened, plugged, impregnated, or welded unless authorized by purchaser.

3.7.5.1 When authorized by purchaser, welding in accordance with AMS 2694 or another welding program acceptable to purchaser may be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.6.1), and the applicable requirements of quality (3.7) are acceptance tests and shall be performed as specified in 4.3.

4.2.2 Periodic Tests: Embrittlement (3.6.2), corrosion resistance (3.7.1.1), and radiographic soundness (3.7.2), are periodic tests and shall be performed at a frequency selected by vendor unless a frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: All technical requirements are preproduction tests and shall be performed on sample castings (4.3.2), when a change in control factors occurs (4.4.2.2), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing:

The minimum testing performed by vendor shall be in accordance with the following:

4.3.1 One chemical analysis specimen or a casting from each master heat shall be tested for conformance with Table 1; if 3.4.2.1 applies, test frequency shall be acceptable to purchaser.

4.3.2 One preproduction casting in accordance with 4.4 shall be tested to the requirements of the casting drawing and to all technical requirements.

4.3.2.1 Dimensional inspection sample quantity shall be as specified by purchaser.

4.3.3 Tensile tests shall be conducted to determine conformance with Table 2. Sampling and test frequency are dependent upon the type and origin of specimen specified by purchaser (See 3.4.4 and 3.6) or selected by vendor (See 4.3.3.4). When 3.4.2.1 applies, test frequency shall be acceptable to purchaser.

4.3.3.1 For separately-cast specimens in the solution heat treated condition of 3.5.1, one specimen from each master heat shall be tested for conformance to 3.6.1.

4.3.3.2 For integrally-cast specimens in the solution heat treated condition of 3.5.1, two specimens from each lot (See 8.2.9) shall be randomly selected and tested for conformance to 3.6.1.

- 4.3.3.3 For specimens machined from casting, one casting shall be randomly selected from each lot and tested after solution heat treatment in conformance with 3.5.1.1 at locations shown on the engineering drawing for conformance with 3.6.1.
- 4.3.3.3.1 When size and location of specimens are not shown, two test specimens shall be tested, one from the thickest section and one from the thinnest section. Once established under 4.4.2.2, test locations may be changed only as agreed upon by purchaser and vendor.
- 4.3.3.4 When acceptable to purchaser, specimens machined from casting may be used in lieu of both separately-cast and integrally-cast specimens, and integrally-cast specimens may be used in lieu of separately-cast specimens. In each case, the resultant properties must conform to requirements of 3.6, or to alternative requirements specified (See 8.2.3) by purchaser.
- 4.3.3.4.1 When specimens are selected for test as in 4.3.3.4 from an origin other than that specified by purchaser, vendor shall include in the report of 4.5 a description of the origin of the specimen that was tested.
- 4.3.3.5 When casting size, section thickness, gating method, or other factors do not permit conformance to 4.3.3.2 or 4.3.3.3, sampling and testing shall be agreed upon by purchaser and vendor.
- 4.3.4 Castings shall be inspected in accordance with 3.7 to the methods, frequency, and acceptance standards specified by purchaser.
- 4.4 Approval:
- 4.4.1 Sample casting(s) from new or reworked master patterns produced under the casting procedure of 4.4.2 shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 For each casting part number, vendor shall establish parameters for process control factors that will consistently produce castings and test specimens meeting the requirements of the casting drawing and this specification. These parameters shall constitute the approved casting procedure and shall be used for production of subsequent castings and test specimens. If necessary to make any change to these parameters, vendor shall submit a statement of the proposed changes for purchaser reapproval. When requested, vendor shall also submit test specimens, sample castings, or both to purchaser for reapproval.
- 4.4.2.1 Production castings produced prior to receipt of purchaser's approval shall be at vendor's risk.

4.4.2.2 Control factors for producing castings and separately-cast specimens include, but are not limited to, the following factors. Supplier's procedures shall identify tolerances, ranges, and/or control limits, as applicable. Control factors for separately-cast specimens must generally represent, but need not be identical to, those factors used for castings (See 3.2.3 and 3.4.1):

Composition of ceramic cores, if used
Arrangement and number of patterns in the mold (including integrally-cast specimens if applicable)
Size, shape, and location of gates and risers
Mold refractory formulation
Grain refinement methods, if applicable
Mold back up material (weight, thickness, or number of dips)
Type of furnace, atmosphere, and charge for melting
Mold preheat and metal pouring temperatures
Fluxing or deoxidation procedure
Replenishment and alloy addition procedures, if applicable
Time that molten metal is in furnace
Solidification and cooling procedures
Cleaning operations (mechanical and chemical)
Heat treatment
Straightening
Final inspection methods
Location and size of integrally cast specimens and specimens machined from a casting, if applicable.

4.4.2.2.1 Any of the control factors for which parameters are considered proprietary by vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.4.2.2.1.1 Unless otherwise agreed upon by purchaser and vendor, purchaser shall be entitled to review proprietary control factor details and coding at vendor's facility.

4.5 Reports:

The vendor of castings shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, master heat identification, heat treat/lot identification, AMS 5362K, part number, quantity, and source of tensile property specimens (See 4.3.3.4.1).