



AEROSPACE MATERIAL SPECIFICATION	AMS5365™	REV. E
	Issued 1947-09 Revised 1982-07 Noncurrent 1995-01 Stabilized 2013-10 Superseding AMS5365D	
Steel Castings, Sand, Corrosion and Heat Resistant 24.5Cr - 20.5Ni Solution Heat Treated (Composition similar to UNS S92411)		

RATIONALE

AMS5365E stabilizes this document because it is deemed to represent technology which is not expected to change in the future.

STABILIZATION NOTICE

AMS5365E has been declared "STABILIZED" by AMS Committee F. This document will no longer be updated and may no longer represent standard industry practice. The last technical update of this document occurred in July 1982. Users of this document should refer any certification issues (e.g. exceptions listed on the certification report) to the cognizant engineering organization for their disposition. CAUTION: In many cases the purchaser is not the cognizant engineering organization (i.e. purchaser may be a sub tier supplier).

SAENORM.COM : Click to view the full PDF of AMS5365E

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2019 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit
<http://standards.sae.org/AMS5365E>

1. SCOPE

1.1 Form

This specification covers a corrosion and heat resistant steel in the form of sand castings.

1.2 Application

Primarily for parts, such as nozzle diaphragm vanes, requiring both corrosion and heat resistance and which may be welded during fabrication. The steel is oxidation resistant up to 2000°F (1095°C) but is useful at the higher temperatures only when stresses are very low. Strength at elevated temperatures is similar to that of the 18Cr - 8Ni types.

2. APPLICABLE DOCUMENTS

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Materials Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

Aerospace Material Specifications

AMS 2350	Standards and Test Methods
AMS 2360	Room Temperature Tensile Properties of Castings
AMS 2635	Radiographic Inspection
AMS 2645	Fluorescent Penetrant Inspection
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

2.2 ASTM Publications

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370	Mechanical Testing of Steel Products
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and other Similar Chromium-Nickel-Iron Alloys
ASTM E446	Reference Radiographs for Steel Castings Up to 2 In. (51 mm) in Thickness

2.3 U.S. Government Publications

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

Federal Standards

Federal Test Method Standard No. 151 - Metals; Test Method

Military Standards

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser.

	min	-	max
Carbon	0.10	-	0.18
Manganese	--	-	2.00
Silicon	0.50	-	1.50
Phosphorus	--	-	0.04
Sulfur	--	-	0.04
Chromium	23.00	-	26.00
Nickel	19.00	-	22.00
Molybdenum	--	-	0.75
Copper	--	-	0.75

3.2 Condition

Solution heat treated.

3.3 Casting

A melt shall be the metal poured from a single furnace charge of 10,000 lb (4500 kg) or less. A lot shall be all castings poured from a single melt in not more than 8 consecutive hours and heat treated together as a batch.

3.4 Test Specimens

3.4.1 Chemical Analysis Specimens

Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimen shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.4.2 Tensile Specimens

Shall be attached to castings, if practicable, or shall be standard keel blocks conforming to ASTM A370, unless purchaser permits use of cast-to-size specimens. Specimens shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. Keel blocks shall be cast in molds made of suitable core sand, shall be poured directly after pouring the castings, and shall be kept in the mold until black. Metal for the specimens shall be part of the melt which is used for the castings.

3.5 Heat Treatment

Castings and separately-cast tensile specimens shall be solution heat treated by heating to a temperature within the range 2025° - 2075°F (1110° - 1135°C), holding at the selected temperature within $\pm 25^\circ\text{F}$ ($\pm 15^\circ\text{C}$) for not less than 30 min., and cooling rapidly to room temperature.

3.6 Properties

Castings and separately-cast tensile specimens shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.6.1 Tensile Properties

3.6.1.1 Separately-Cast, Attached, or Keel Block Specimens

Shall be as follows, determined on specimens produced as in 3.4.2 and heat treated as in 3.5:

Tensile Strength, min	65,000 psi (450 MPa)
Yield Strength at 0.2% Offset, min	28,000 psi (195 MPa)
Elongation in 4D, min	30%

3.6.1.2 Specimens Cut from Castings

Tensile specimens conforming to ASTM A370 shall be machined from castings selected at random from each melt in the shipment. Size, number, and location of such specimens and required properties shall be as shown in the drawing or as agreed upon by purchaser and vendor. Property requirements may be defined as specified in AMS 2360.

3.6.2 Hardness

Should not be higher than 170 HB or equivalent but castings shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.7 Quality

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfection detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.

3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.

3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Except as specified in 4.2.1.1, tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each melt or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings shall be determined only when specified by purchaser or when attached or separately-cast specimens are not available. Tensile properties of attached or separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests

Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling

Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 from each melt and/or a casting from each lot.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.3 Three tensile specimens in accordance with 3.4.2 from each melt, when requested.

4.3.4 One or more castings from each lot when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each lot.

4.4 Approval

4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the control factors of processing which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the control factors of processing, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample test specimens, castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.