

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 5368

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-61
Revised

STEEL CASTINGS, INVESTMENT, CORROSION RESISTANT
15Cr - 4Ni - 2.3Mo - 0.1N
Solution Treated

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for small parts requiring good corrosion resistance and strength at temperatures up to 850 F.

3. COMPOSITION: Castings shall conform to the following:

Carbon	0.08 - 0.15
Manganese	0.40 - 1.10
Silicon	0.75 max
Phosphorus	0.04 max
Sulfur	0.03 max
Chromium	14.5 - 15.5
Nickel	3.5 - 4.5
Molybdenum	2.0 - 2.6
Nitrogen	0.05 - 0.13
Carbon + Nitrogen	0.15 - 0.25

4. CONDITION: Solution heat treated, unless otherwise specified.

5. TECHNICAL REQUIREMENTS:

- 5.1 Casting: Castings shall be poured either from remelted master heat metal or directly from a master heat. A master heat is previously refined metal of a single furnace charge. Gates, sprues, risers, and rejected castings shall not be remelted directly, without refining, for pouring of castings; they may be used in preparation of master heats. When permitted by purchaser, metal in the form of shot from more than one master heat may be uniformly blended together to form a master heat lot; the total weight of metal in a master heat lot shall not exceed 7000 pounds.

- 5.2 Test Specimens:

- 5.2.1 Tensile Test Specimens: Unless otherwise specified, tensile test specimens shall be cast to represent each master heat or master heat lot of metal in castings and, when requested, shall be supplied with the castings. The specimens shall be of standard proportions with 0.25 in. diameter at the reduced parallel section, shall be cast to size in molds made of the same refractory and heated to the same temperature as the molds for castings, and shall be cooled at approximately the same rate as the castings. Center gating may be used but, if specimens are so gated, the gate shall be completely removed before testing. If the metal for castings is given any treatment such as fluxing or cooling and reheating, metal for the specimens shall be so treated.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no assurance that the Board or its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.3 Heat Treatment: Unless otherwise specified, castings shall be solution heat treated by heating to 1900 F + 50, holding at heat for not less than 1 hr per inch of section, and cooling rapidly in air for castings with all sections 1 in. or less in thickness and in water or oil for castings with any section greater than 1 inch.
- 5.4 Hardness: Castings shall have hardness not higher than Rockwell C 39 or equivalent.
- 5.5 Properties After Austenite Conditioning, Subzero-Cooling, and Tempering: Tensile test specimens produced in accordance with 5.2.1 and heat treated in accordance with 5.3 shall be capable of meeting the following requirements after heating to 1725 - 1850 F, holding at heat for not less than 1 hr per inch of cross section, and quenching in water or otherwise cooling as rapidly as possible to room temperature, cooling to not higher than -100 F, holding at this temperature for not less than 3 hr, warming in air to room temperature, heating to 850 F + 25, holding at heat for not less than 3 hr, and cooling in air. If supplied tensile test specimens fail to meet the requirement or are not available, suitable specimens may be prepared from castings for test.

5.5.1 Tensile Properties:

Tensile Strength, psi	200,000 min
Yield Strength at 0.2% Offset or at 0.0072 in. in 1 in. Extension Under Load (E = 29,000,000) psi	150,000 min
Elongation, % in 4D	8 min

- 5.5.2 Hardness: Shall be not lower than Rockwell C 40 or equivalent.

6. QUALITY:

- 6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Unless otherwise specified, metallic shot or grit shall not be used for final cleaning.
- 6.2 When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other imperfections.
- 6.3 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 6.4 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 6.5 Castings shall not be repaired by plugging, welding, or other methods, without written permission from purchaser.