

AEROSPACE MATERIAL SPECIFICATION



AMS 5369D

Issued MAR 1948
Revised JAN 1984
Noncurrent NOV 1994
Reaf. Noncur. NOV 2000

Superseding AMS 5369C

Steel Castings, Sand, Corrosion and Heat Resistant
19.5Cr - 9.5Ni - 1.4Mo - 1.4W - 0.50 (Cb+Ta) - 0.32Ti
Solution and Precipitation Heat Treated

UNS J92843

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of November 1994. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 5369D

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:**1.1 Form:**

This specification covers a corrosion and heat resistant steel in the form of sand castings.

1.2 Application:

Primarily for parts, such as nozzle diaphragm assemblies, requiring high strength up to 1350°F (730°C) and oxidation resistance up to 1600°F (870°C).

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350	Standards and Test Methods
AMS 2635	Radiographic Inspection
AMS 2640	Magnetic Particle Inspection
AMS 2645	Fluorescent Penetrant Inspection
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A262	Detecting Susceptibility to Intergranular Attack in Stainless Steels
ASTM E10	Brinell Hardness of Metallic Materials
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E446	Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.28	0.35
Manganese	0.75	1.50
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	18.00	21.00
Nickel	8.00	11.00
Molybdenum	1.00	1.75
Tungsten	1.00	1.75
Columbium + Tantalum	0.30	0.70
Titanium	0.15	0.50
Copper	--	0.50

3.2 Condition:

Solution and precipitation heat treated free from continuous carbide network.

3.3 Castings:

A melt shall be the metal poured from a single furnace charge of 15,000 lb (6800 kg) or less. A lot shall be all castings of the same part number poured from a single melt in not more than 8 consecutive hours and solution and precipitation heat treated together as a batch.

3.4 Test Specimens:

Chemical analysis specimens shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.5 Heat Treatment:

Castings shall be solution heat treated by heating to $2000^{\circ}\text{F} \pm 50$ ($1095^{\circ}\text{C} \pm 30$), holding at heat for not less than 30 min., and cooling in air and precipitation heat treated by heating to $1600^{\circ}\text{F} \pm 25$ ($870^{\circ}\text{C} \pm 15$), holding at heat for not less than 8 hr, and cooling in air.

3.6 Properties:

Castings shall conform to the following requirements:

- 3.6.1 Hardness: Castings shall have hardness not higher than 229 HB or equivalent, determined in accordance with ASTM E10.
- 3.6.2 Intergranular Corrosion: Specimens cut from castings, after sensitizing treatment, shall show no evidence of intercrystalline surface attack when examined microscopically after being exposed to the copper/copper sulfate/sulfuric acid test performed in accordance with ASTM A262, Practice E.

3.7 Quality:

- 3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.
 - 3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted by purchaser.
- 3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.
- 3.7.3 When specified, castings shall be subjected to magnetic particle inspection in accordance with AMS 2640 or to fluorescent penetrant inspection in accordance with AMS 2645, or both.

3.7.4 Radiographic, magnetic particle, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and as preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, on each melt or lot as applicable, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction castings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4 or a casting from each melt.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.4 Approval:

4.4.1 Sample castings from new or reworked patterns or molds and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample castings. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing castings include, but are not limited to, the following:

- Type of furnace
- Furnace atmosphere
- Fluxing or deoxidation procedure
- Gating and risering practices
- Pouring temperature (variation of $\pm 50^{\circ}\text{F}$ ($\pm 30^{\circ}\text{C}$) from the established limit is permissible)
- Solidification and cooling procedures
- Solution and precipitation heat treatment cycles
- Cleaning operations
- Methods of inspection

4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.5 Reports:

4.5.1 The vendor of castings shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of at least one casting or of specimens as in 3.4 from each melt represented and stating that the castings conform to the other technical requirements of this specification. This report shall include the purchase order number, melt number, AMS 5369D, part number, and quantity from each melt.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5369D, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, the vendor shall inspect castings from each lot represented to determine conformance to the requirements of this specification and shall include in the report either a statement that the castings conform or copies of laboratory reports showing the results of tests to determine conformance.